

This is a digital copy of a book that was preserved for generations on library shelves before it was carefully scanned by Google as part of a project to make the world's books discoverable online.

It has survived long enough for the copyright to expire and the book to enter the public domain. A public domain book is one that was never subject to copyright or whose legal copyright term has expired. Whether a book is in the public domain may vary country to country. Public domain books are our gateways to the past, representing a wealth of history, culture and knowledge that's often difficult to discover.

Marks, notations and other marginalia present in the original volume will appear in this file - a reminder of this book's long journey from the publisher to a library and finally to you.

Usage guidelines

Google is proud to partner with libraries to digitize public domain materials and make them widely accessible. Public domain books belong to the public and we are merely their custodians. Nevertheless, this work is expensive, so in order to keep providing this resource, we have taken steps to prevent abuse by commercial parties, including placing technical restrictions on automated querying.

We also ask that you:

- + *Make non-commercial use of the files* We designed Google Book Search for use by individuals, and we request that you use these files for personal, non-commercial purposes.
- + Refrain from automated querying Do not send automated queries of any sort to Google's system: If you are conducting research on machine translation, optical character recognition or other areas where access to a large amount of text is helpful, please contact us. We encourage the use of public domain materials for these purposes and may be able to help.
- + *Maintain attribution* The Google "watermark" you see on each file is essential for informing people about this project and helping them find additional materials through Google Book Search. Please do not remove it.
- + *Keep it legal* Whatever your use, remember that you are responsible for ensuring that what you are doing is legal. Do not assume that just because we believe a book is in the public domain for users in the United States, that the work is also in the public domain for users in other countries. Whether a book is still in copyright varies from country to country, and we can't offer guidance on whether any specific use of any specific book is allowed. Please do not assume that a book's appearance in Google Book Search means it can be used in any manner anywhere in the world. Copyright infringement liability can be quite severe.

About Google Book Search

Google's mission is to organize the world's information and to make it universally accessible and useful. Google Book Search helps readers discover the world's books while helping authors and publishers reach new audiences. You can search through the full text of this book on the web at http://books.google.com/


FRICTION,


LUBRICATION,

FATS AND OILS.

DIETERICHS.

Library of the University of Wisconsin





.

· .

			•		
	•				
TITO:	FOMTON.	ANÎD TI	TDDTO	MICH	
FR	ICTION A	AND LU	JBRICA	TION	•
$\mathbf{F}\mathbf{R}$	ICTION A	AND LU	JBRICA	TION	
FR	ICTION A	AND LU	JBRICA	ATION	
FR	ICTION A	AND LU	JBRICA	ATION	
FR		AND LU	JBRICA	ATION.	•
FR		AND LI	JBRICA	ATION	•
FR			JBRICA	ATION	•
FR			JBRICA	TION	•
FR				•	•
FR				TION	•

. .

FRICTION AND LUBRICATION.

•

A PRACTICAL TREATISE

ON

FRICTION, LUBRICATION, FATS AND OILS,

INCLUDING

THE MANUFACTURE OF LUBRICATING OILS, LEATHER OILS, PAINT OILS, SOLID LUBRICANTS AND GREASES; MODES OF TESTING OILS, AND THE APPLICATION OF LUBRICANTS.

BY

EMIL F. DIETERICHS,

MEMBER OF THE FRANKLIN INSTITUTE, PHILADELPHIA, MEMBER OF THE NATIONAL ASSOCIATION OF STATIONARY ENGINEERS, AND INVENTOR OF THE DIETERICHS'S "VALVE-OLEUM" LUBRICATING OILS.

PHILADELPHIA:

HENRY CAREY BAIRD & CO., INDUSTRIAL PUBLISHERS, BOOKSELLERS AND IMPORTERS, 810 WALNUT STREET. 1906.

COPYRIGHT, BY
EMIL F. DIETERICHS,
1906.

105149 APR 23 1907 TES 1156

6935276

PREFACE.

From observation during a period of nearly fifty years as a practical Chemist and Manufacturer of Chemical Products and all kinds of Oils, and my close connection with Engineers and Manufacturers, and experience with the endless varieties of Engines and Machinery in use, I have long felt the need of some work that would collectively treat in a condensed and comprehensive form the subjects of Friction, Lubrication, the origin and characteristics of Fats and Oils, their Uses, their Adulterations and their Practical Testing, all of such vital importance in the mechanical world.

In the effort to produce a book to fill these wants and make it useful as well as easily understood by Mechanics and Manufacturers not very familiar with these subjects, I have throughout avoided as much as possible all scientific technology, as well as technical terms and theories familiar only to the experienced chemist, and have endeavored to write in such language and manner as can be readily comprehended by anybody with an ordinary school education.

I would here take occasion to acknowledge the endorsement given to my former writings and to my lectures on these subjects, and to the generous patronage extended to my "valve-oleum" lubricating oils.

My theories on lubrication, which led to the production of the "valve-oleum" oils, at first met with much derision. But notwithstanding the fact that I have made many efforts to arouse, by my publications and lectures, more attention to, and to elicit information upon, the subject, thus far no sound argument has been advanced to refute these theories or to uphold those other ones, older and long persistently held.

Should I have been successful in producing such a treatise as will meet the demands of the time, and with this faith, I hereby dedicate this volume to manufacturers, and mechanics, and to my brother engineers of the National Association of Stationery Engineers of America, I shall feel myself amply repaid for my labor.

As is the practice of the publishers, the book has been supplied with a full table of contents and a thorough index, rendering reference to any subject in it prompt and accurate.

E. F. DIETERICHS.

CLEVELAND, OHIO, September 15, 1906.

I.

FRICTION.	
· · · · · · · · · · · · · · · · · · ·	PAGE
Definition of friction; Various kinds of friction; Explana- tion of the laws of friction	1
Moving force required when wood on iron, iron on iron, or iron on brass press on each other; Co-efficient of friction and rule for finding it; Friction of quiescence; Friction	
of motion	2
Rolling friction; Traction of a cart on a macadamized road;	
Traction on a railway	3
Value and usefulness of friction; Frictional heat	4
п.	
LUBRICATION.	
Necessity of lubricating; What is lubricating? Laws of lubrication as taught by nature; Lubrication of the	5
joints of the bones in the body by the joint water Absorption of frictional heat by metal; Effect of overheat-	6
ing the bearings	7
Creation of frictional heat as shown by Count Rumford's experiments	8
Accumulation and disposal of frictional heat; Capacity of inert matter for absorbing and carrying away frictional	
heat	9
Necessity of renewing the lubricant; Lubricating a chemical process	10
(vii)	

·	PAGE
The chemical process which takes place when oil is used for lubricating	11 12
III.	
OIES AND FATS.	
Definition of oils; Classes of oils	13
Fixed oils; Volatile or essential oils; Drying oils; Non-	
drying or fatty oils; Vegetable oils	14
Animal oils; Drying oils; Volatile or essential oils	15
Mineral oils and petroleum oils, and the manner of obtaining them	16
ing them	10

IV.	
OILS AND FATS OF ANIMAL AND VEGETABLE ORIGIN, TE CHARACTERISTICS, AND HOW THEY ARE OBTAINED.	EIR
Lard and lard oil; Preparation and properties of lard;	
Separation of olein from lard	18
Lard oil and its properties; Commercial grades of lard oil;	
Tallow and tallow oil; Mode of obtaining tallow	19
Tallow oil and its properties	20
Neatsfoot oil and horse tallow oil; Neatsfoot oil and its prop-	
erties; Bone fat, bone grease, or marrow tallow	21
Horse tallow and its properties; Elain or red oil and its	
properties	22
Spermaceti and fish oils; Spermaceti	23
Spermaceti, its constitution and properties	24
Sperm oil and its properties; Seal oil	25 26
Wool fat; Degras	27
Factitious degras; Constitution of degras	28
Castor oil and its properties	29
Olive oil and its properties	30
Sunflower oil; Sesame or gingelly oil	31

CONTENTS.	ix
	AGE
Cottonseed oil; Rapeseed or colza oil	32
Hempseed oil; Palm oil and cocoanut oil	33
Copra; Palm oil or palm butter and its properties	34
Almond oil; Poppyseed oil	35
Corn oil and mode of obtaining it	36
Peanut oil and its properties	37 38
Mustardseed oil; Nigerseed oil; Linseed oil Linolein; Driers	39
Rosin, rosin oil and turpentine; Mode of obtaining rosin and	
its properties; Distillation of rosin oil	40
Rosin or pine oil and its properties; Glycerin	41
Properties of glycerin	42
v.	
CLARIFYING, REFINING, AND BLEACHING OILS AND FAT	8.
·	
Various processes of bleaching vegetable oils; Clarifying oils Refining oils by treatment with sulphuric acid; Refining	
oils and fats with caustic soda	44
Freeing oils from free fatty acids; Bleaching oils with chlorine	45
Process for deodorizing oil	46
Bleaching and deodorizing degras	47
Cleaning and bleaching tallow and other fat; Cleaning and bleaching and deodorizing train oil; Bleaching grease .	48
bleaching and deodorizing train on; bleaching grease .	40
777	
VI.	
MINERAL OILS.	
Mode of obtaining mineral oils; Distillation of mineral oils.	50
Green oil; Paraffine oil; Treatment of shale oil	51
Grades of illuminating oils; Tar oils	52
Distillation of wood and products obtained thereby; Products obtained by the distillation of tar from the gas works;	•
•	53
Difference between benzol and benzine	54
Conversion of nitro-benzol into anilin oil; Uses of coal tar .	94

VII.	AGE
PETROLEUM OILS.	
Deposits of petroleum	55
Petroleum oils of Pennsylvania; Ohio crude oils and mode	
of desulphurizing them	56
Use of aluminium chloride for desulphurizing Ohio	
petroleum	57
Distillation of petroleum	58
Classification of the proceeds of distillation	59
Neutral distillates and their division	60
Purifying and bleaching the neutral oils; Extraction of par-	
affine wax from the crude paraffine oils	61
Uses of paraffine wax; Golden machine oil; Steam refined	
cylinder oil; Production of a good cylinder oil from crude	
oil	62
Black lubricating oil or West Virginia oil; Filtered cylinder stock; Vaseline, cosmoline, petrolatum; Petroleum oils for	
lubricating	63
Petroleum oils for various lubricating purposes; Signal oil	00
for lanterns	64
Deblooming petroleum oils; Deodorizing petrol oil	65
· · · · · · · · · · · · · · · · · · ·	•
VIII.	
MANUFACTURE OF LUBRICATING OILS.	
Lubricants for heavy pressure and low-speed machinery .	67
Compounding of petroleum oils to give them a viscous con-	
sistency; Compounding cylinder oil	68
Various fats and oils used in the compounding of cylinder and other oils; Mode of compounding petroleum with	
fatty oils.	69
Use of rosin oils in the compounding of lubricating oils .	70
Thickened oils	71

	٠
	1

IX.	AGE
"VALVE-OLEUM" OILS.	
Materials which form the foundation of "Valve-Oleum" oils Preparation of oleate of alumina	73 74 77 78 79 80
x.	
LEATHER OILS.	
Necessity of lubricating leather belts, harness, boot and shoe leather	81 82 83 84
XI. ADULTERATIONS OF FATTY OILS.	
Materials used in the adulteration of lard oil, olive oil, sperm oil, and linseed oil	85 86
XIL	
TESTING OILS.	
Alkali tests for detecting the presence of a hydrocarbon oil in fatty oils	87 88

Test for cottonseed oil in lard oil; Preliminary test for neu-	PAGE
tral oil in lard oil	89
To detect small quantities of fatty oils in a sample of min-	
eral oil; To detect soap dissolved in mineral oil; To de-	•
tect acidity or alkali in mineral oil	90
Simple and practical methods for testing oils and oil mixtures	91
Detection of the admixture of petroleum oil in large propor-	
tion to fatty oils	92
Mode of ascertaining with what proportion of petroleum a	
fatty oil has been adulterated	93
Mode of telling the presence of petroleum in fatty oils, even	
in very small proportions; Means employed to prevent de-	
tection of adulteration of fatty oils by the hydrometer test.	94
Testing the comparative efficiency of oils for lubricating; To	
ascertain the gumming propensities of an oil; Viscosity,	0.5
and modes of ascertaining it	95
Fire test	96
Simple way of testing lubricating eils	97
Practical tests of lubricating oils	98
Necessity of cleaning cylinders and bearings before testing	
or using a new oil	99
Advantage of the stringy character of "Valve Oleum" oils.	100
<u>.</u>	

XIII.	
SOLID LUBRICANTS. GREASES.	
Constitution of solid lubricants and their application; Constitution of grease	101
Character of machinery for which lubricating grease is used;	
Wear and abrasion of the metal with grease lubricants .	102
Manufacture of greases	103
<u> </u>	100
Preparation of lime paste for rosin grease; Manufacture of	104
8	104
Formulas after which nearly all grease lubricants are manu-	105
factured: Preparation of a "cup grease"	105

CONTENTS.	xiii
	PAGE
Dark axle grease; Linseed oil grease	. 106
Various receipts	. 107
XIV.	
SOME PRACTICAL SUGGESTIONS.	
Cause of injuries to a cylinder	. 109
Lubrication not effected by inert matters; Decomposition	
all fatty oils and fats by the absorption of steam and fri	
tional heat; Injurious action from the use of tallow i	
cylinders	. 110
Formation of marble-like balls by the motion of the pistor	
Consequences of the softening and dissolving of hardene	
deposits	~ . 111
Injury to cylinders caused by poor packing; Other causes	
cutting and scarring of the metal	. 112
Necessity of keeping clean and carefully examining the	
parts of machinery where oil is used for lubricating.	. 113
•	
xv.	
LUBRICATORS AND CUPS.	
Trouble caused to engineers by lubricators; Pumps for a)-
plying cylinder oils	. 114
Automatic pumps; The "Moses pump;" Feeding cylinder	er
oil through the sight-feed cup	. 115
Consequences of cleaning the cup by blowing live steam	m ·
through it; Cleaning sight-feed cups	. 116
Regulating the flow of oil in the cups	. 117
Cups feeding with a wick; Oils to be used in cups expose	d
to varying temperatures	. 118
Cups for feeding grease	. 119
Only reliable lubricating with grease	. 120

·

PAGE

XVI.

SPECIFIC GRAVITY.

Definition of specific gravity; Stands	rd fe	or so	lid ar	nd liq	uid	
bodies; Mode of ascertaining the sp	ecifi	c gra	vity o	f liqu	ids	
by means of the specific gravity bo	ttle	•	•	•		121
Use of the Baumé hydrometer; Tal						
the specific gravity they represent,	and	the	corre	pond	ing	
weight of the liquids per gallon						122
Index						127

FRICTION.

THE force which is felt to resist the motion when one body rubs against another while in motion is called friction. Of all mechanical power used, a large amount is spent or lost to overcome the obstructive force of friction, and means are looked for to reduce this as much as possible. Friction is either sliding or rolling. The laws regarding friction are explained as follows:

When placing a block of wood or iron on a smooth surface of wood or metal, it requires a force of some two-fifths of the weight of the block to make it move along the surface, thereby indicating the friction between the surfaces, as has been established by carefully conducted experiments. It has been established that two such blocks placed on the plate side by side, so as to form one of double size, require double the force to

, ,1

move them, and when the blocks are placed on top of each other, there is no difference in the amount of force necessary to move them. friction between any two surfaces increases in proportion to the force with which they are pressed together, regardless of the extent of the surface in contact. A difference, however, exists when wood on iron, iron on iron or, iron on brass press on each other. For oakwood on iron, the moving force required is about two-fifths, or exactly thirty-eight per cent; for iron on iron fortyfour per cent, and for cast-iron upon brass about twenty-two per cent, in a dry state and without lubrication. The proportion expressed between the pressure of two surfaces and their friction is called their co-efficient, and is found by dividing the power by the weight moved. The friction of quiescence, or the resistance to the commencement of motion, is greater than the resistance to its continuance, and more so if the surfaces have for a considerable time rested in contact with each The friction of motion is entirely independent of the velocity of the motion. The resistance of friction to a shaft turning in its bearings, or of an axle in its box, has evidently a

greater leverage the thicker the journal or the axle is, and axles of wheels are accordingly made as small as is consistent with their required strength. The resistance that takes place between the circumference of the wheel on the road is called "rolling friction." In front of the wheel there is always an eminence or obstacle which it is at every instant surmounting and crushing; so also on iron rails, but to a much lesser extent than on other roads. On the principle of the lever, it shows that a larger wheel has the advantage over a smaller one, and it has been fully established that on a horizontal road the traction varies directly as to the load, and inversely as to the radius of the wheel. On a perfectly good and level macadamized road, the traction of a cart is found to be one-thirtieth of the load, so that a horse to draw a ton must pull with a force equal to seventy-five pounds. On a railway the traction is reduced to one two-hundred-and-eightieth of the load, or to eight pounds per ton. Friction is akin to and as important as is gravitation in every motion in the universe.

While friction on railways is diminished, further dimunition would stop motion entirely, as

4 FRICTION, LUBRICATION, OILS AND FATS.

the driving wheels of the locomotive would slide around on the rails without advancing.

Friction is most valuable when machinery with great momentum has to be checked or suddenly arrested in its motion, as by a brake against the wheels on railways. It is useful in communicating motion by means of belts, ropes or chains; it is the force that holds the knot in the rope, and it is the power that stops the momentum of cars in rapid motion. Friction is the constant opponent of motion, which creates heat, which is known as "Frictional Heat."

TT.

LUBRICATION.

To overcome friction and put its resisting power to as low a point as possible, we use Lubricants that can absorb the frictional heat and, becoming vaporized by it, will carry the heat into space.

Lubricating is a necessity, and is the most important factor in the mechanical world. Without lubrication all the power we can obtain from Steam, Electricity, Gas, Water, Air and Horse Power, Spring and Wind Power could be of no use to us, and travel on railroads and steamboats, the running of factories, the riding in automobiles, in carriages and wagons, the use of sewing machines, the riding on bicycles, the keeping record of time by our watches; in short, the using of anything that is dependent on mechanical motion would be utterly impossible.

We have then to investigate, "What is Lubricating?"

Nature teaches us the laws of lubrication by its wonderful workings in the human body and in the bodies of all animals. All the joints of the bones in the body would be useless and stiff were it not for their being constantly lubricated by the so-called "Joint Water," an unctuous fluid which surrounds all the joints of the skeleton part of the body. This "Joint Water" is constantly produced and supplied by nature, and is constantly consumed by the frictional heat created by our exertions and movements, and is likewise constantly disposed of and frees the body from the otherwise accumulating frictional heat by transferring it, with the perspiration and exhalations from the body, into space. When the recuperating powers of the body fail to operate properly, from one cause or another, the inflammatory condition of the joints gives evidence of the absence of proper lubrication, and the final failing and drying up of this lubricating "Joint Water" under diminished generating power in advanced age cause the joints to move with difficulty and pain, and in the end make them lose their usefulness altogether.

So it is with machinery.

Whenever the surface of one part of machinery in motion is bearing on the surface of another, friction is created and friction creates heat. This heat is evolved and increases with the velocity and continued motion, and if not taken up and carried away by lubrication, will finally increase and accumulate to such an extent that the machinery will have to be stopped to allow the metal to cool off.

Metal is able to absorb a large amount of frictional heat, but it is unable to free itself of it as fast as it is generated by continued and rapid motion, and the heat finally accumulates to such an extent as to overheat the bearings, and if further continued will so increase and expand the metal as to cause the parts to weld themselves tightly together. This has frequently been the case with the old style flour-mill spindles, which, after becoming overheated, were found to be so tightly welded in their steps, that they had to be chiseled out. To avoid this we have to keep the revolving parts well lubricated in their bearings, and we have to continue doing this as long as the machinery is kept in motion and in exact proportion to the frictional heat evolved and the amount of work we expect to have done.

That frictional heat is created by motion and that it vaporizes the lubricant, is shown by the following convincing experiments made many years ago by the celebrated scientist, Count Rumford:

He had a metal vessel constructed, with hollow bottom, had a perpendicular shaft fitted to it, and had it rapidly moved by mechanical power. He then filled the vessel with water, and in the course of four hours ascertained that the water, by the absorption of the frictional heat generated, had attained a temperature of 140° F., and in eight hours had reached the boiling-point. After this he found the water to evaporate and gradually diminish in bulk as long as he kept the shaft in rapid motion.

If we now substitute oil for the water, we will find the oil also gradually attain the temperature of its evaporating point, commonly known as "flash or fire test," and will find it also to vaporize and gradually reduce its bulk until the shaft be stopped moving.

This shows conclusively that frictional heat

accumulates, and that it is disposed of by evaporating into space; this evaporation, though con-Lubricating, therefore, tinuous, is invisible. cannot be simply an interposition of some substance, as a sort of cushion, between the metallic surfaces of machinery in motion. Soft metallic compounds, such as plumbago and some of the finer grades of inert matter, asbestos, mica, sulphur, lime and soapstone, have been recommended and have been tried for 'that purpose, but it has been found that while all such substances serve well, in small quantities, to fill the interstices which exist in all metallic surfaces of bearings however highly polished, and thereby presenting a smoother bedding for the revolving shaft, they can only absorb as small a portion of the heat created by the friction as the metal itself of which the machinery is constructed.

The capacity of plumbago and other inert matter for absorbing and carrying away the frictional heat is very low, as they cannot vaporize, while the capacity of oil and fatty matter is very great, and we are, therefore, compelled to use oil and fatty matter for lubricating.

If lubricating would be simply a mechanical

action and a cushion of soft metal or other inert matter, or of oil or fat, would be sufficient to prevent the gradual increase and accumulation of frictional heat, then a very limited amount of oil, fat or other inert matter, once applied, should be sufficient. We find, however, that we are obliged to renew the lubricant with regularity and in exact proportion to the frictional heat created by the motion, and in exact proportion to the amount of work we expect to do, and we have to do this as long as the machinery is kept in motion.

We have then to ask: What has become of the large quantities of oil which we were compelled to constantly apply to the bearings of the machinery?

As coal and water are constantly consumed to keep the supply of steam up to move the machinery, so is oil constantly consumed to draw the frictional heat away from the bearings. We can see how the coal and water are consumed, but we are unable to see how the oil is consumed. We can, however, find silent proof that it is so, and that lubricating is a strictly chemical process and not a mechanical one.

We know that metal cannot absorb oil, and

we allow most liberally for all possible wasting and for transformation of much of it into gummy accumulations around the bearings and in cylinders, we must admit that a very limited number of gallons from every barrel of oil used could thus be accounted for, and it remains to be seen what has become of the balance.

We well know at what temperature water is evaporated and converted into steam, and after serving its purpose to move the machinery is lost into space. Precisely the same chemical process, the transformation from a fluid into a gaseous state, takes place when oil is used for lubricating.

When the oil becomes heated by the frictional heat until its evaporating temperature is reached, it becomes, like steam, a gas, and is lost into space with the heat it has absorbed.

This transformation takes place on every bearing, although on so small a scale as to be almost entirely imperceptible to our senses. Where the revolving shaft rests heaviest in the hollow of the bearing, there is the line to be drawn where this invisible transformation of the oil from the liquid into the gaseous state takes place. This line is exceedingly small—perhaps no more than

the thickness of the finest sheet of paper—but on this small line the frictional heat starts to be generated, and being taken up by a few atoms of the oil at a time, is carried with their vapors into space. When from neglect or insufficient lubrication bearings become overheated, and under the rapidly increasing temperature the few particles of oil vaporize too fast and become decomposed under the increased heat, the arising vapors, with a penetrating burning smell, prove to us the slow and mysterious process by which the oil disappears.

Lubricating is, therefore, a chemical process, and requires the interposing of such substances between the moving parts of machinery as are qualified to absorb the frictional heat, and vaporized by it, carry it into space. Such qualifications are best possessed by oil and fatty matter, and we, therefore, use them for lubricating our machinery.

A continuous stream of water or the application of ice will likewise absorb and vaporize with the frictional heat, but not possessing sufficient adhesive body, cannot prevent the gradual abrasion of the metal.

III.

OILS AND FATS.

THE next question arises: What are oils and what is fatty matter? What are their characteristics, and from what sources of nature do they come, and how are they obtained?

Oils are liquid and semi-solid substances, derived from the animal and the vegetable kingdoms. They are unctuous to the touch, are insoluble in water, and possess the power of supporting combustion with flame. They are obtained from the roots, seeds, fruits and flowers of plants and trees, and from the fat of animals, by extraction, by pressure, by rendering, by boiling with water, or by distillation. They are also obtained from the mineral kingdom, from shale, and out of receptacles in the bowels of the earth.

Oils are divided into two classes: They are either oxyhydro-carbons, that is, compounds of oxygen, hydrogen and carbon, and are known as

"fixed oils," or they are hydro-carbons, composed of hydrogen and carbon only, and are known as volatile or essential oils. The "fixed oils" do not sensibly evaporate at ordinary temperature. They stain paper permanently and render it translucent. They do not distil or evaporate at the temperature of boiling water, and they have only a faint odor, like that of the substance from which they have been extracted. The volatile or essential oils evaporate freely. They have a caustic, acrid taste and an aromatic odor, and when distilled with water they pass over at 212° F.

All of the "fixed oils" have an attraction more or less powerful for oxygen. Exposed to the atmosphere, some of them become hard and resinous, and they are called "drying oils;" others thicken only slightly and become sour and rancid, and they are known as non-drying or "fatty oils." The fatty oils in general use for lubricating and in the manufacture of Lubricating Oils are:

Vegetable Oils: Olive Oil, Rapeseed Oil or Colza Oil, Cocoanut Oil, Palm Oil and Almond Oil, and many others seldom used for lubricating.

Animal Oils: Lard Oil, Tallow Oil, Neatsfoot Oil, Wool Fat, Sperm Oil and the many varieties of Fish Oils.

For lubricating purposes these oils, vegetable as well as animal, are largely compounded with mineral oils of all grades and colors and in endless proportions.

Drying Oils, more or less, are: Lindseed Oil, Nut Oil, Poppy Oil, Hempseed Oil, Castor Oil, Cottonseed Oil and Rosin Oil. Some of them are used in the manufacture of greases for lubricating purposes, but all of them are unfit for lubricating machinery on accout of their resinous nature.

The volatile or essential oils are: The Oils of Amber, Bergamot, Cloves, Lemon, Rose, Orange Flower and many others, all derived from the vegetable kingdom. They are usually more limpid and less unctuous than the fatty oils, with which they mix in all proportions. They are more or less soluble in alcohol and ether, and are sparingly soluble in water, to which, however, they impart their peculiar flavor. Nearly all the volatile oils resist saponification, and do not combine with the alkaline bases to form soapy com-

pounds. They are not used for lubricating purposes.

The Mineral Oils and the Petroleum Oils are Hydro-carbons, and belong to the class of volatile and essential oils. They have little affinity for oxygen or moisture. They will not saponify, and they do not ferment or become rancid. The Mineral Oils are derived from bituminous coal and shale by distillation, and have been entirly superseded by the Petroleum Oils since the utilization of the latter.

The Mineral Oils obtained by distillation of coal tar, which is the product of the dry destructive distillation of coal at gas works, are chiefly used for dissolving rubber, in the manufacture of the beautiful aniline colors, and in making printing inks, varnishes and paints.

The Petroleum Oils have been placed by nature within easy reach of mankind, and have been of great use for lighting, heating and lubricating purposes. In their natural state they are found in all forms of consistency, from a solid to a thin oily liquid, and from the darkest to the lighest shades of color. This peculiar product of nature is composed of endless series of Hydro-carbon

compounds, from a light, incondensible gas, to a solid body. They are similar in characteristics to the Mineral Oils obtained from coal tar and shale, but differ materially in their chemical composition.

2

OILS AND FATS OF ANIMAL AND VEGETABLE ORIGIN, THEIR CHARACTERISTICS AND HOW THEY ARE OBTAINED.

Lard and Lard Oil.

Lard is the prepared fat of the hog. The fat freed from membranous matter is cut up into small pieces and boiled with water. It is then carefully separated from the water and melted over a slow fire. Lard is a soft, white, unctuous fat, with a faint odor, is free from rancidity and has a bland taste and a neutral reaction. Its specific gravity is about 0.938, or about 20° to 21° by Baumé's hydrometer. Lard is entirely soluble in ether, in benzine, and in disulphide of carbon. It melts at or near 95° F., and when melted it readily unites with oils, wax or resins. Like most animal fats, it consists of stearin, palmitin and olein. Olein, the liquid principle of lard, can be readily separated from the stearin

and palmitin by subjecting it, at a cold temperature, to strong pressure, when the liquid olein is pressed out, leaving the solid stearin, which is principally used in the manufacture of stearin Exposed long to the air, lard and candles. lard oil will absorb oxygen and become rancid. Lard oil as obtained from lard is a colorless or pale vellowish oily liquid: it becomes opaque at or below the temperature of 32° F. It has a slightly fatty odor and a bland taste. Its specific gravity is from 0.900 to 0.920, or from 22° to 24° by Baumé's hydrometer. It contains varying proportions of stearin, and is much adulterated with cottonseed oil and refined petroleum neutral oils. Lard oil is sold in the market as "Extra Winter Strained" lard oil when obtained by pressure at a cold temperature; as "No. 1" when pressed at a warmer temperature, and as "No. 2" when obtained from impurer lard, and by the rendering pro-The better qualities are often used to adulterate olive oil.

Tallow and Tallow Oil.

Tallow is obtained from the fat of sheep and

It is prepared by cutting the fat into pieces, melting it at moderate heat and straining through coarse cloth. It is sometimes previously purified by boiling with a little water. fat is of a firmer consistency, and fuses at a higher temperature than fat from other animals. Tallow is very white, sometimes brittle; it is inodorous, has a bland taste, and is insoluble in water. consists of about seventy per cent of stearin and palmitin and thirty per cent of olein. It gradually dissolves in two parts of benzine, from which it slowly separates in a crystalline form on standing. It melts between 113° and 122° F. and congeals between 98° and 104° F. Its specific gravity lies between 0.937 and 0.952 or 18° to 20° by Baumé's hydrometer.

Tallow oil, i. e., the percentage of liquid olein in tallow, is obtained by melting the tallow and keeping it in a warm room at a temperature of about 80° to 90° F. for some hours; the stearin which the tallow contains crystallizes in a granular form, and in this state it is placed in canvas or hair-cloth bags and subjected to hydraulic pressure. The olein is thus separated from the stearin. It still contains stearin in various pro-

portions, and the oil is of more or less fluidity, and for that reason its specific gravity varies from 0.911 to 0.915, or from 23° to 24° by Baumé's hydrometer.

Tallow oil is of an almost white color when cold, or, at the most, of a faint yellow tint. It has a slight odor of animal fat. Varying with its quality, it has a flash point of from 475° to 500° F.

Neatsfoot Oil and Horse Tallow Oil.

Neatsfoot oil is obtained from the feet of cows, sheep and horses. The hoofs are trimmed and boiled in water, when the oil collects on the surface and is skimmed off, and is further purified by repeated boiling with water. Neatsfoot oil appears either as a turbid or a limpid liquid of a yellow-brownish color, has a pleasant odor and a sweet taste, and has little tendency to become rancid; it becomes solid in cold weather from deposition of stearin, has a specific gravity of about 0.912 or 23° Baumé at 60° F., and solidifies at about 32° to 33° F.

Bone fat, bone grease or marrow tallow comes from the shank bones of cows, bullocks and horses. They are either boiled in water, and the rising oil skimmed off, or they are subjected to steam heat of from 50 to 60 pounds pressure in digesters for from half an hour to an hour. At the end of the operation the fat is drawn off.

Horse tallow, or fat obtained from the rendering of dead horses, is much like the tallow obtained from cows and sheep, and under pressure furnishes an oil which is known in the market as horse tallow oil, and is often sold under the name of "Neatsfoot Oil." It has at 60° F. a specific gravity of 0.915 to 0.980, or 22° Baumé.

Elain or Red Oil. .

The oil known as elain or red oil gets its name from the dark reddish color it derives from its contact with the hot iron press plates and the high temperature to which it is subjected in its production by the saponification process with lime or sulphuric acid, or by high steam pressure or by distillation, whereby the fat is decomposed into oleic acid, stearic acid and glycerin. The fatty acids are allowed to solidify, and are pressed between hot iron plates, whereby the Red Oil (liquid olein or elain) is separated from the solid stearin. The latter is used in the manufacture

of the well-known "Adamantine Candles," and the red oil in the manufacture of soaps and in the compounding of lubricating oils and lubricating for carding wool. By the saponification of solid fats by the lime, sulphuric acid or steam process, the fatty acids are set free from their combination with glycerin, and are allowed to solidify, and are pressed. According to the temperature, more or less stearin and palmitic acid go into the product, and can be separated by distillation. The oil is often semi-solid, resembling tallow grease; the distilled varieties are light brown to deep red; specific gravity at 60° F. is from .899 to .909, or 24° to 25° Baumé.

SPERMACETI AND FISH OILS.

Spermaceti.

The cavities in the upper part of the head of the sperm whale contain an oily liquid, which, after the death of the animal, concretes into a white, spongy mass, consisting of spermaceti mixed with oil. This mass is removed and allowed to separate by draining or pressure in the cold. Common whale oils and the oils from other cetaceous animals contain also small quantities of spermaceti, which on standing they slowly deposit.

Spermaceti is a concrete, fatty substance, a white, pearly, semi-transparent mass of neutral reaction and crystalline foliaceous texture, friable and somewhat unctuous to the touch, slightly inodorous and insipid; it is insoluble in water, but soluble in the fixed oils; its specific gravity is 0.945, or 18° Baumé, and it melts at about 122° F. and congeals near 113° F. It is soluble in ether, chloroform, disulphide of carbon, and in boiling alcohol, from which latter, however, it separates in crystalline scales on standing. is seldom found pure in commerce, but is adulterated with fixed oils. Continelain acid is the main constituent of spermaceti, and is different from oleic acid. Spermaceti also contains small quantities of stearic acid, myristic and laurostearic acids. Pure spermaceti does not produce When old it becomes fatty spots on paper. darker colored and rancid. Different from stearin, spermaceti is not affected by boiling in diluted solution of carbonate of soda.

Sperm Oil

is the limpid liquid separated from the spermaceti, the spongy mass in the head of the dead sperm whale. It is a pale, yellowish-colored liquid, with a smell of fishy nature, and will, when exposed to the cold, deposit but little solid matter. It is not liable to become rancid, has no corrosive action on metal, and no tendency to dry and become gummy. It retains its viscosity under influence of heat better than any other oil. Sperm oil is a compound of fatty acids with alcohol radicals, the acids belonging to the oleic Sulphuric acid gives rise to an inacid series. crease of heat of some 120° F., and produces a yellowish-brown mass, which distinguishes sperm oil from other fish oils. It differs from other fish oils also by its chemical constitution and its low specific gravity, 0.884 at 60° F., 28° to 29° by Baumé. It is the lightest of all natural oils.

Seal Oil

Is obtained from the blubber of the hooded seal, the barbed seal and the harp seal of the polar regions. The oil is extracted from the blubber the same as from that of the whale, and its properties are similar to the whale oil. Its color varies from a light straw to a brown. It is a strongly odorous oil, of a specific gravity of 0.924 to 0.929, or 21° Baumé.

Whale and Train Oils.

These include cod liver oil, tanners cod oil from different fish, menhaden oil, porpoise oil, shark oil and whale oil.

The whale and train oils are obtained from the blubber of various species of whale, the polar whale, the humpback whale, the common whale. The blubber varies in thickness from 8 to 20 inches around the body of the whale, and after being cut into pieces, is boiled with water for about an hour, to liberate the oil from it. The specific gravity of the oil is from 0.920 to 0.931, at about 60° F., or 20° to 22° Baumé.

A large amount of oil of similar character as the foregoing fish oils is obtained from endless varieties of the smaller salt and fresh water fishes, which is used in the manufacture of soaps and lubricating oils, and known in the market as "Fish Oils." They are all oxyhydrocarbons and belong to the class of "fixed oils."

Wool Fat.

Wool fat is obtained by the washings of the wool of sheep. It is the fatty substance produced by the absorption of large amounts of alkali with the feeding of the sheep, thereby producing a secretive matter in the body of the sheep, which is discharged through the skin by transpiration and is deposited as in the wool suint, a quasi-saponified compound of stearic, oleic, and some palmitic acids. Weak alkaline solutions are used to extract this suint from the wool, from which in turn it is obtained by precipitating the alkali with sulphuric acid.

The wool fat when first obtained is a creamlike mass, which requires purification and freeing from moisture. As this is usually accomplished over an open fire, it imparts to the product a dark color.

A considerable amount of wool fat is also obtained from the soapsuds used in the washing process of woolen goods, by precipitating the alkali with sulphuric acid to liberate the fat.

Degras.

Degras is the fatty matter obtained in the pro-

cess of chamoising skins in the manufacture of chamois leather. The fermentation produced during the manipulation of the skins with fat or fish oils, train oils, causes the fat or oil to be split into fatty acids and glycerin. About fifty per cent of the fat or oil employed in the process is recovered in the form of a greasy, fatty mass by wringing and pressing it from the skins. This constitutes the best quality of degras.

A large amount of fatty mass is still retained in the skins, which is obtained by treating them in a warm solution of potassa, whereby the fatty matter is partially saponified, and is separated from the resulting white bath by treatment with sulphuric acid. •

An inferior, factitious degras is made from the elain obtained in the manufacture of stearin for candles mixed with train oils and other fatty matter, by agitation with strong decoctions of tanbark and partial saponification with alkalies and subsequent separation by means of sulphuric acid.

Degras contains 80 per cent of fatty acids, 10 per cent of glutinous and extract-like substances, 2 per cent of lime, 0.5 per cent of potassa, besides water.

Castor Oil.

Castor-oil is obtained from the seeds of the castor-oil plant, Ricinus Communis, which contain from 50 to 60 per cent oil when separated from the capsules in which they are enclosed. The seeds are roasted over a slow fire and boiled with water, from which the oil is skimmed off; later the seeds are subjected to cold or hot pressure, a better quality and of lighter color being obtained by cold pressure than when pressed warm or extracted with solvents. Castor-oil is the most viscid of all the fixed oils. By long exposure to the air it becomes rancid and thick, and is ultimately transformed into a yellow mass. It has a mild, finally acrid taste, and a nauseous odor, and it is of a somewhat semi-drying character. Exposed to cold a solid, white crystalline fat (margaritine) separates from the liquid portion, and when cooled to 0° F. it congeals to a yellow, transparent mass, which does not liquefy again until the temperature rises to about 18° F. It consists of resin-stearic, oleic and palmitic acids. Its specific gravity is 0.961, or 15° Baumé. It is soluble in alcohol and in four volumes of rectified spirit.

It mixes with fatty oils, but will not mix with mineral oils.

Olive Oil.

Olive oil is obtained from the fleshy part and the kernels of the fruit of the olive tree of southern Europe, Palestine and California. They furnish from thirty to fifty per cent. of oil. The olives are subjected to a gentle pressure, whereby the best qualities of olive oil are obtained. The resulting cake is treated with hot water, from which an inferior oil is skimmed off.

Most of the olive oil of commerce is obtained by allowing the olives to ferment in heaps, and then subjecting them to heavy pressure. The remaining cake or mark is boiled with water, and more oil is obtained of a darker yellowish or brownish-green color. Olive oil is also obtained by extraction from the crushed and dried pulp with hydrocarbon solvents.

Olive oil is of a pale, greenish-yellow color, with scarcely any smell or taste, except a sweetish, nutty flavor. Its specific gravity is from 0.915 to 0.920 at 60° F., or 23° Baumé. Olive oil mixes with disulphide of carbon, benzol and chloroform in all proportions. When cooled down it deposits

stearin and solidifies at 25° F. Its boiling-point is about 600° F.

Sunflower Oil.

Sunflower oil is obtained from the seeds of the sunflower, especially from the Black Sea regions. The seeds are roasted and crushed, and the pulp separated from the wood-like shells. They contain from twenty-eight to thirty per cent of oil. The oil obtained by cold pressure is of a clear yellow color, nearly odorless, and of a pleasant, mild taste. Its specific gravity at 60° F. is about 0.9260, or 21° Baumé. It thickens in the cold and solidifies at 60° F. to a white, yellowish mass. It is a very slightly drying oil, and is mostly composed of oleic, stearic and palmitic acids.

Sesame or Gingelly Oil.

Obtained from the seeds of Sesamum Indicum of India and from the seeds of the plant cultivated in southern Europe and the Orient.

The seeds furnish from 40 to 50 per cent of oil of a bright yellowish color and agreeably sweet taste. It is much used as a substitute and adulterant of olive oil, and is very similar to it in its

characteristics. Its specific gravity at 60° F. is 0.9235, or 22° Baumé.

Cottonseed Oil.

Cottonseed oil is obtained from the seeds of the cotton plant. The seeds contain from fifteen to twenty per cent. of oil, a thickish liquid of a straw-yellow color, with nut-like taste and smell. It is of a semi-drying character, consists of palmitin and olein, and is from twenty-eight to thirty times less fluid than water. Like all the oils obtained from seeds, the latter are first slightly roasted and separated from their outside shells by mechanical power, and the oil is secured by pressure or by extraction with solvents.

The specific gravity of cottonseed oil is 0.9306 at 60° F., or 20° Baumé. It separates palmitin and stearin at about 55° F., and solidifies at about 40° F.

Rapeseed or Colza Oil.

Rape or colza oil is produced from rapeseed, turnips, and other species of brassia. It is obtained from the seeds by cold and hot pressure, and they yield from thirty to forty-five per cent. of oil. The first pressings are known under the name of colza oil; the second pressings are usually sold as rapeseed oil. Colza oil has a pale yellow color. Rapeseed oil a greenish-brown color. They are limpid oils, with a peculiar and characteristic odor, and an unpleasant and harsh taste. Exposed to the air, the oil becomes more viscid. Its specific gravity at 60° F. ranges from 0.913 to 0.915, or 23° Baumé. It is a semi-drying and gumming oil.

Hempseed Oil.

Hempseed oil is obtained from the seeds of the Cannabis Indica plant. The seeds when crushed have a peculiar odor, and yield by pressure or extraction from thirty to thirty-five per cent of an oil of a greenish-yellow color. The oil remains fluid to 10° F., and thickens when cooled down to 5° F., to a brownish-yellow mass. Its specific gravity is 0.9276, or 21° Baumé, at 60° F., and about 0.9240 at 70° F.

The oil consists of lineolic acid, oleic acid and palmitin and stearic acids. It is somewhat less drying than linseed oil.

Palm Oil and Cocoanut Oil.

Palm oil is obtained from the fruit of the oil

palm and the cocoanut palm of tropical Africa, and is known as palm fat, palm butter or palm oil. The oily pulp of the fruit of the oil palm, after being bruised and boiled in water, yields an oil which, when fresh, has a pleasant odor of violets, and assumes in the cold the consistency of butter of an orange-yellow to a dirty, reddish color.

From the dried kernels of the cocoanut (copra) a fixed oil is extracted, which is the cocoanut oil of commerce. The kernels are ground, and the resulting paste is boiled with water. The paste is then submitted to high pressure, whereby a large quantity of milky juice is obtained. This is boiled, and when the oil separates from the water it is skimmed off.

Palm oil or palm butter consists chiefly of stearin and palmitin, both of which have a comparatively high fusing point of about 115° to 120° F., and are preponderate in the solid fat, while olein, which is fluid at 32° F., is the chief constituent of the oil.

The specific gravity is 0.968, or 15° Baumé.

Cocoanut oil is of a bright white color. Its specific gravity is .952, or 17° Baumé.

Almond Oil.

Almond oil is obtained from the kernels of bitter and sweet almonds, the seeds of the almond plant. The sweet almonds contain more fatty oil than the bitter almonds. The almonds contain from forty-five to fifty-five per cent of oil. For pressing the bitter and sweet almonds are mixed. The oil obtained is a thick liquid, little affected by cold, possesses a purely oleaginous taste and solidifies at 5° F. to a buttery mass. Almond oil is more limpid than olive oil and is thicker than poppyseed oil. It consists almost of pure olein. Its specific gravity is about 0.917 or 23° Baumé.

Poppyseed Oil.

Poppyseed oil is obtained from the seeds of the poppyshower by cold and by warm pressure. It is imported from India and the plant is largely cultivated in France and Southern Europe. The seeds yield about forty-seven to fifty-five per cent of oil of a pale-yellow to a gold-yellow color. It is a clear, limpid oil, with an agreeable taste and a peculiar, slight odor, somewhat like olive oil. Its specific gravity at about 60° F. is 0.9250 or 21° Baumé. It remains liquid until cooled down

to 0° F. when it forms a thick, whitish mass. Once solidified by cold, it remains solid to about 30° F., when it begins rapidly to become liquid again. Poppyseed oil is almost as quick drying as linseed oil, and is composed of linolein, oleic, stearic and palmitic acids.

Corn Oil.

Corn oil is obtained from the kernels of the corn (maize) plant, and is almost entirely found in the shells of the kernels.

To separate the shells from the farinaceous part of the kernels, and to make the latter better available for the mashing process, the kernels are first subjected to the malting process. They are then crushed and the shells separated from the farinaceous part by a sifting or centrifugal operation, whereby the parts of lighter specific gravity are easily separated from the heavier ones, and thereby nearly eighty per cent of cornmeal, almost entirely free from oily matter, is obtained. Otherwise the oily matter would greatly interfere with the fermentation of the mash, and impart an unpleasant flavor to the alcohol manufactured therefrom.

The hulls thus separated are subjected to heavy pressure, and about fifteen per cent of pure corn oil obtained.

Corn oil is of a light to a gold-yellow color, and has a peculiar, agreeable odor. It is a thickish liquid of 0.9215, or 22° Baumé at 60° F. It is composed of oleic, stearic and palmitic acids, with a small percentage of a volatile oil, and solidifies at about 50° to 60° F. to a quite solid, white mass. It is used as a wool oil, for the manufacture of soaps, and in the manufacture of lubricating oils.

Peanut Oil.

Peanut oil is obtained from the kernels of the peanut. They yield by pressure from thirty to forty per cent of an oil of a light yellowish, almost white, color, and of an agreeable, particularly nutty, taste and odor. When obtained by extraction the seeds furnish from forty to fifty per cent of oil. The specific gravity is 0.915, or 23° Baumé, at 60° F. The older and last pressed oils have at 60° F. a specific gravity of 0.9202, or 22° Baumé. The oil is more limpid than olive oil, which it resembles much. It is a slightly drying oil. It contains palmitin, olein, stearin

and archidic acids the latter being peculiar to this oil.

Mustardseed Oil.

Mustardseed oil is obtained from the seeds of the mustard plant. The seeds yield by pressure or extraction about thirty per cent of oil of dark yellow-brownish color, of a mild taste, and when obtained by pressure, with a very slight odor of mustard. Its specific gravity at 60° F. is 0.917, or 23° Baumé. It solidifies at about 18° F., and is composed of stearic, palmitic and a peculiar oleic acid called mustardseed acid.

Nigerseed Oil

Is obtained from the seeds of guizotia. It has a pale yellow color, little odor and a sweet taste. Is more limpid than rapeseed oil and of a semi-drying character. Its specific gravity is 0.924, or 22° Baumé.

Linseed Oil.

Linseed oil is a drying fixed oil obtained from flaxseed, which yield about thirty-four per cent of oil. The seeds are roasted before being pressed or extracted, and furnish a light colored oil of best quality under cold pressure. When pressed warm or obtained by extraction with solvents it is more highly colored and more acid, has a brownish-yellow color, a disagreeable odor, a nauseous taste, and a neutral reaction. Its specific gravity is 0.932 to 0.936, or 20° Baumé. It boils at 600° F., does not congeal at 0° F., and dries and solidifies on exposure to the air and acquires a strong odor and taste.

The drying property of linseed oil resides in a constituent called "linolein," to distinguish it from the olein of the non-drying oils. Spread out in thin layers and exposed to the air it becomes thicker and resinous, and increases as much as twelve per cent of its weight, owing to the formation of linoxyn by atmospheric oxidation. Boiled with litharge, red lead, lead acetate, manganese dioxid or borate and other chemicals, so-called dryers, it absorbs oxygen still more rapidly, and increases to some fourteen per cent in weight. Its acrimony is due to the presence of a small proportion of an acrid oleoresin. It is much adulterated with other oils when used in the manufacture of printer's ink.

Rosin, Rosin Oil and Turpentine.

Rosin is obtained by distillation of the crude turpentine obtained from several species of pine and fir trees, especially the pine trees of the States of North and South Carolina and Georgia.

The crude turpentine resin is distilled with water, and yields about one-fourth of spirits of turpentine, the remainder being the common rosin of commerce.

Rosin is a semi-transparent solid and brittle product of smooth and shining fracture of a yellowish-brown, sometimes almost black, color. It has a somewhat acrid and bitter taste, and is insoluble in, and rather heavier than, water.

Rosin melts at about 275° F., and is completely liquid at 306° F. It is soluble in the fixed and in the volatile oils. Rosin distilled by itself yields rosin oil.

The first distillate below 674° F. is the lighter, at a specific gravity of about .987, or 12° Baumé, at 60° F., and that over 675° F. being the second and heavier oil at a specific gravity of about .981 to .985, or 12° Baumé, 60° F. Rosin oil readily resinifies by absorption of oxygen, and is much used as an adulterant of linseed oil and in

the manufacture of printer's inks. Rosin oil consists of sylvic and pinic acids. When distilled with superheated steam, rosin yields benzol and toluol.

Oil of turpentine is also obtained by distillation of the cones of the pine trees. Its specific gravity is about 0.903 at 60° F., or 25° Baumé.

Pine tar is obtained by charring the wood of pine and other coniferous trees.

Deodorized rosin oil is that freed from the "spirits" by fractional distillation.

Rosin or pine oil (kidney oil) is a somewhat thickish fluid of a brownish-yellow color, aromatic, turpentine-like odor and taste. Its specific gravity is about 0.985 at 60° F., or 12° Baumé. At that temperature it is about ten times thicker than water, becomes whitish turbid at about 16° below Zero F., and solidifies at about 20° below Zero F. It is a slow-drying, gummy oil.

Glycerin.

Glycerin, also called the sweet spirit of the fatty oils and fats, is a trihydric alcohol, and is not found readily formed in the fatty matter. All fats and fatty oils are considered glycerides,

that is, compositions of fatty acids with a weak base called glyceryle. By the process of hot saponification the stronger alkaline bases unite with the fatty acids to form soapy compounds, thereby separating and setting the weaker base, "glycerin," free, and from ten to twelve per cent of it is thus obtained. Glycerin is also obtained from fatty matter by the action of superheated steam.

Under cold treatment of fatty matter with alkaline bases, the latter unite with the fatty acids and form oleites, stearates and palmitates of soda or potassa, but no glycerin.

Glycerin is a water-white, viscid liquid. It has no odor, but a very sweet taste. It boils at 550° F., is not volatile at ordinary temperature, but will vaporize at 212° F. When mixed and boiled with water it readily absorbs water from the air, and will mix with water in all proportions. It is miscible with alcohol in all proportions, but is insoluble in petroleum and benzine. A mixture of nitric acid and sulphuric acid forms with it "nitro-glycerin," a most powerful explosive.

CLARIFYING, REFINING AND BLEACHING OILS AND FATS.

THE clarifying and bleaching process must necessarily vary, as the oils may be more or less colored or mixed with impurities than others. The animal oils and fats require bleaching or clarifying only when obtained from impure material or offal. The vegetable oils, however, are generally more or less colored and permeated with vegetable and albuminous matter. many cases it will suffice to blow hot dry air of a temperature of from 120° to 130° F. through the oil to remove the undesirable color and impurities. Others may be bleached by exposure to the sunlight in bright, shallow vessels, or by agitating the oil mixed with animal charcoal, at a temperature of about 120° F., and then filtering it. In many cases, however, one or the other of the following processes may be required:

Oils are clarified by the admixture of from

five to ten per cent of fuller's earth, stirring well at a temperature of 140° to 150° F. The mixture is then allowed to rest and settle. The fuller's earth carries down with it all impurities in suspension, and the sediment can be treated with benzine to recover any oil rémaining mixed with the fuller's earth.

Oils are also refined by treatment with sulphuric acid, which destroys all extraneous vegetable matter. The oil is heated to about 110° to 115° F., and from one to two per cent of sulphuric acid, usually previously diluted with an equal proportion of water, is added, with constant agitation for about half an hour. It is then allowed to rest and settle for about twenty-four hours. From twelve to fifteen gallons of water, heated to about 150° F., to every twenty gallons of oil, is then stirred with the oil and the oil allowed to rest and settle for a few days, when it is drawn off and washed with water to remove all traces of acid.

Oils and fats, especially cottonseed oil, are also refined with caustic soda, which, like acid, destroys all extraneous vegetable, mucilaginous and resinous matter, and all acidity in the oil.

A caustic lye of from fifteen to twenty degrees Baumé is used for cottonseed oil, from eight to twelve degrees for most other fatty oils, and a lye from five to six degrees strength is generally found sufficient for cocoanut and like oils, and often a lye of from one-half to one per cent strength only will be sufficient for the purpose.

Oils containing much of free fatty acids can be effectively treated with weak solutions of caustic or carbonate of soda, or with milk of lime or magnesia, and the oil filtered from the lime and magnesia soap thereby formed.

Strong solution of chloride of zinc, from one to two per cent of the oil, is also used. It destroys and precipitates all albuminous and vegetable matter suspended, without injury to the oil, but it is more expensive than sulphuric acid.

It is advisable to avoid treating oils to be bleached with too large proportions of chemicals at once, as repeating the operation with smaller proportions will generally secure better results.

Oils can be bleached and thereby also deodorized with chlorine, a powerful bleaching agent.

The oil is heated to a temperature of about 140° to 150° F., and a solution of chloride of

lime, "bleaching powder," in the proportion of about one pound to a thousand pounds of oil, is mixed with the oil. Hydrochloric (muriatic) acid is then added in about twice the quantity of the bleaching powder used, and the oil is thoroughly agitated. It is then allowed to settle and the oil or fat is drawn off. Chloride of potassa or peroxide of manganese, with hydrochloric acid, can also be used in the same manner as the chloride of lime.

Oil can also be deodorized by shaking 1,000 parts of it with 120 parts of water, holding in solution 3 parts of permanganate of potassa, keeping it warm for some hours, and then filter. For bleaching lard oil, palm oil, and similar oils and fats, the bichromate of potassa process is much used. The oil or fat is heated to a temperature of about 130° to 140° F., and a concentrated solution of bichromate of potassa in the proportion of about 10 to 12 pounds of the bichromate to a thousand pounds of the oil or fat is added and thoroughly stirred into the oil. Hydrochloric acid in the proportion of from two to three per cent of the oil is then added, and the whole well stirred for from ten to fifteen minutes. The oil,

which at once assumes a reddish-green color, soon changes to a pale-green one. Boiling water is then added, and the agitation continued for a few minutes more, or live steam is blown through the oil and then allowed to settle. The oil is then drawn off and washed with water to remove all traces of acid.

Degras is bleached and deodorized in the following manner. The degras is melted by heating with live steam and thoroughly agitated by paddling or blowing with air. A solution of bichromate of potassa in water—one pound or more of bichromate of potassa for a hundred pounds of degras—is added, and after agitating for a few minutes a solution of two pounds of sulphuric acid, previously diluted with six pounds of water, is poured in. Next three pounds of black oxide of manganese are added and agitated for half or three quarters of an hour. blower is then turned off and the acid and water allowed to separate, and are drawn off from underneath the fat. The grease is now sprayed with hot water, which is again allowed to settle, and is drawn off. This is repeated until all sour taste is removed. When cold, stir thoroughly and allow still adhering water to run off.

Tallow and other fat can be cleaned and bleached by boiling some fifty pounds of the fat with about five to ten pounds of alum dissolved in about ten gallons of water for about an hour, constantly stirring and skimming. Draw off the clear fat and add one pound of sulphuric acid diluted with three pounds of water. Boil and add some eight ounces of bichromate of potassa; continue boiling, and if necessary add a little more acid; then allow to settle, draw off and wash with boiling water; finally spray with a little cold water to accelerate the clearing of the fat.

To clean and bleach and deodorize train oil, boil with salt water, consisting of about one-fourth its weight of chlornatrium (salt), and stir briskly for about half an hour; then allow to settle, draw off the oil and mix with a decoction of nutgalls. After briskly stirring for about fifteen minutes or so, add about four ounces aqua fortis (nitric acid) to every hundred pounds of the oil; stir for a little while longer and allow to settle; draw off the clear oil and wash with water.

Grease is bleached by melting and agitating with about three per cent of sulphuric acid and

two per cent of a saturated aqueous solution of bisulphite of soda. The mixture is then run into a narrow cylindrical vessel and violently agitated with dry steam for half an hour, and is then run off and allowed to cool slowly, and while still fluid the fat is drawn off without disturbing the sediment. It is again agitated with steam and about 20 per cent water and left standing to separate and harden.

4

VI.

MINERAL OILS.

THESE oils are obtained by distillation from Scotch shale, a black, somewhat flaky mass of homogeneous structure, with an irregular, glossy surface. It is usually soft enough to be cut, and when ignited burns with a flame. The better qualities yield from thirty to thirty-three per cent of oil; the poorer grades are stony and slate-like and produce little oil.

When submitted to distillation in large vertical stills, an uncondensable gas and water containing a large proportion of ammonia first come over; then a crude oil of a thickish dark reddishbrown, with a peculiar odor and of a specific gravity of from 0.865 to 0.890, or 32° to 27° Baumé, is obtained. This is again subjected to distillation, and naphtha and light colored oil, which gradually becomes darker, is obtained. Solid paraffine begins to show itself, followed by

a thick, brown oil, and finally coke is left in the still.

The oil is treated with sulphuric acid and with a solution of caustic soda. When again distilled the oil yields a light spirit known as green naphtha, a light oil known as "second run oil," and a dark-colored, heavy oil, known as "green oil," and coke is left as residuum in the still.

The naphtha is treated with sulphuric acid and solution of caustic soda, and is separated into several grades of illuminating oil.

The "green oil" is subjected to a freezing temperature, and paraffine wax is obtained from it by pressure. The solid paraffine wax obtained is about twelve to fifteen per cent. The remaining oil is known as "paraffine oil," and was formerly used in the manufacture of lubricating oils.

The specific gravity of the light oils from shale is about 0.730 to 0.760; that of the heavier oils is about .810 to .820. The oil from the paraffine pressings has a specific gravity of about 0.872 or about 30° Baumé.

Shale oil is treated with a small proportion of sulphuric acid and caustic soda, about one per cent, and redistilled, yielding the following grades of illuminating oils:

No. 1, best, with a specific gravity of 0.800 and 100° F. flash point.

No. 2, first quality, with a specific gravity of 0.810 and 103° F., flash point.

No. 3, second quality, with a specific gravity of 0.815 and 120° F., flash point.

No. 4, lighthouse oil, with a specific gravity of 0.820 and 160° F., flash point.

No. 5, marine sperm oil, with a specific gravity of 0.830 and 230° F., flash point.

A fuel oil is left of about 0.840 specific gravity.

Steam is used in the still and controls the distillation; it lowers the temperature of the distillate and facilitates the passing of the vapors from the still.

The mineral oils have been entirely superseded by the petroleum oils since the discovery and utilization of the latter.

Tar Oils.

Tar oils are obtained from tar, being the result of the destructive distillation of wood and bituminous coal.

Wood is distilled in iron retorts and in milers. to obtain thereby the resulting charcoal. lighter products of the distillation are wood alcohol, naphtha and pyrolignic acid, the latter being used in the manufacture of acetic acid and other acetate products. The tar obtained by the destructive distillation of wood is re-distilled and wood-tar oil is obtained, from which picric acid is made by treatment of the oil with nitric acid. The oil is also used in the manufacture of leather oils, medicinal soaps and ointments. Creosote, another product obtained by the distillation of wood-tar, is in its chemical composition very different from the carbolic acid, often misnamed creosote, obtained by the distillation of tar from the destructive distillation of bituminous coal at the gas-works.

By the distillation of tar from the gas-works we obtain benzol and coal-tar oil. This benzol is a product of far different chemical composition than the benzine obtained from petroleum, although often confounded with it. Benzol, when treated with nitric acid, is converted into nitrobenzol (or myrbane oil), which has a strong odor, like oil of bitter almonds. This oil is much used

in perfumery and for scenting soaps and greases, for lubricating, and for deblooming petroleum oils.

When acted upon with nascent hydrogen this nitro-benzol or myrbane oil is converted into anilin oil, from which the many beautiful anilin colors are made by the use of powerful oxidizing agents. Coal-tar oil, too, contains large amounts of anilin oil, which is separated from it by agitation with strong mineral acids, which combine with the anilin oils.

Coal-tar is also used in the manufacture of coal-tar paints for painting roofs, smokestacks and iron structures. The product left in the still is the well known asphaltum, extensively used in roofing and for paving purposes.

VII.

PETROLEUM OILS.

WHEREVER and however nature carries on its mysterious process of producing the various grades of petroleum found all over the globe, the lighter and the heavier grades, the brighter and the darker colored ones, all are found in shallow places, above ground or near the suface, or deep down in the bowels of the earth, those found lowest being generally of lighter consistency than those found on or nearer to the surface. are all hydrocarbon compounds of like characteristics, differing only in their specific gravity, in their color, odor or in cleanliness. The deposits found above ground or near the surface, which are almost solid or are liquids of heavy specific gravity, appear to be the result of evaporation of their lighter constituents or of a gigantic filtering process, by which the liquid constituents have percolated to a lower stratum, leaving the heaviest

ones retained where they are found in an upper stratum or on the surface, as Ozokerite wax.

The petroleum oils of Pennsylvania, in Venango, Clarion and Butler counties, in Warren and McKean counties, vary in color from light amber-yellow to dark black, and vary in specific gravity from 30° to 55° Baumé; from thick lubricating oils to nearly pure benzine. Franklin county oils are celebrated for their fine bright, dark ruby color, their fine lubricating quality and excellent cold test, which makes them valuable as lubricants on refrigerator machinery.

The Ohio crude oils, containing sulphur and having an unpleasant sulphurous odor, are desulphurized during the process of distillation by placing a desulphurizing chamber between the retort and the cooler. This chamber is separately heated and is filled with iron oxide, copper sulphate, porous lime coke, or other desulphurizing agents, and hot air can be driven through the oil. When a temperature of 130° F. is attained in the desulphurizing chamber, the still is fired and the heating of the chamber is increased to prevent the passing vapors of the oil from condensing in the chamber before passing through the cooler. In-

troducing nascent hydrogen into the still or the desulphurizing chamber, and its vapors mingling with those of the distilling oil, improves the color and odor of the distillate and changes the product into one of lighter gravity and purer odor.

Aluminium chloride also is used to desulphurize Ohio petroleum. One hundred parts of the oil are heated and while agitated, 0.8 part of aluminium chloride is gradually added, whereby a little muriatic acid and much sulphureted hydrogen are evolved. When no more gas is eliminated, the oil is allowed to cool and is drawn off from over the aluminium residuum and washed with water and soda lye, and is distilled with the addition of a little lime.

In order to enhance the value of the various forms of petroleum and to make them adapted and available for their manifold uses in the market, they are either purified, condensed or distilled. Some require only straining or settling and exposure to the atmosphere, for a period of time, to vaporize all traces of inflammable, light hydrocarbon compounds and to settle all gritty matter and impurities, to make them serviceable for lubricating purposes. Others are condensed

and the lighter vapors driven off and settling of gritty impurities is effected by application of steam heat. The greater bulk, however, is subjected to distillation, in order to separate the different grades of hydrocarbon compounds from each other and thus obtain various useful products.

Distillation of Petroleum.

When crude petroleum is subjected to distillation and the uncondensable gases and moisture have gone over, a series of light hydrocarbon compounds known as "benzine" are first obtained, about 15 per cent. Then a number of grades of burning oil, known as "distillates," come over and are collected separately. They are treated and bleached and freed from adhering scorched impurities with sulphuric acid and solutions of caustic soda. From 50 to 60 per cent of these oils is obtained and the remaining residuum oil forms the basis for the petroleum lubricating oils.

The lighter products of the distillation, the crude benzine, are subjected to redistillation with steam heat and are separated to their respective degrees of specific gravity and characteristics re-

quired to the manifold demands for their use. They are purified, deodorized and bleached by treatment with chemicals and are sold as naptha, gasoline, benzine, and under many fancy names.

The "distillates," which are next obtained, are likewise purified and bleached by treatment with sulphuric acid and solution of caustic soda and by exposure in bright and shallow tanks to the bleaching influence of sunlight. Numerous grades of distillates are produced by being carefully separated from each other during distillation.

The proceeds of distillation at specific gravities are the benzine series, from the highest gravity (the first distillate obtained) down to about 56° to 58°, standard white or export oil of 110° F. flash or 70° Abel test, from 56° to 54° and then from 42° to 39°. Water white oil, 120° flash or 150° fire test, the legal test of Ohio and now the generally accepted test of most states, from 54° to 46°, or until the distillate begins to show color. Prime white oil, 150° fire test, from 46° to 42°, and headlight oil, 175° fire test, from 46° to 39°.

In case 110° standard white and 175° headlight oils are not desired, there will be but two separations between 56° and 39°, viz., 150° water-white oil and 150° prime white oil, the necessary fire test being obtained by driving off the lighter vapors by redistillation in a steam still, or by steaming and spraying in an agitator or open tank, but preferably in a steam still, in which case what is known as a "Straight Run" (distillate from 58° to 46°) water-white oil, the requirement of almost any State law as to flash or fire test, can be made. These gravity separations are not absolute, but flexible within a few degrees, dependent upon the nature of the crude oil used and the grade of oil desired.

The continued distillations from 39° down to 29° constitute the neutral distillates, and are divided by separation into what is known as 300° F. or mineral seal oil and 34° to 36° neutrals, or by redistillation into a small percentage of prime white or headlight, 300° or mineral seal, 34° to 36° neutral, and a residual oil known as "Spindle Oil," of 30° to 32° Baumé, possessing considerable viscosity.

If the distillation from the crude still is carried from 29° to 20° and the product afterwards redistilled, the residual of the second distillation will be the commercial red oils of high viscosity and gravity of from 30° to 23°.

The residual oil in the crude still at 24° to 19° is usually pumped hot into a tar-still and the distillation continued down to coke, producing the paraffine distillates hereafter to be described.

The carbonaceous residuum or coke left in the still is used in the manufacture of carbons for electric lighting.

The neutral oils are purified and bleached by treatment with sulphuric acid and solution of caustic soda. They are deodorized by air-blast and their fluorescence skillfully removed with chemicals. They are largely used for adulterating the more costly animal and vegetable "fatty oils."

The crude paraffine oils hold crystalline paraffine wax in suspension, produced by the disintegration of hydrocarbon compounds during the process of distillation. It is extracted from the oil by freezing and pressure, and is purified by treatment with sulpuric acid and caustic soda while being kept in a liquid state by heat. It is bleached with benzine and then cast into solid blocks.

Paraffine wax is largely used in waterproofing fabrics, for insulating and in the manufacture of candles and matches, and numerous other manufactures. The paraffine oil left after separation from the wax is treated with acid and solution of caustic soda and is filtered through animal charcoal. It is used for lubricating and is known as "Golden Machine Oil." The paraffine oils of varied degrees of specific gravity form the basis for many engine lubricating oils and are compounded with fatty oils in endless proportions.

In order to make the residuum oil left in the still, after distilling off the burning oils, directly useful for the purpose of lubricating engine cylinders, the oil is put into tall vessels, surrounded by steam, and the impurities, produced by the scorching influence on the oil against the heated bottom and sides of the still during the process of distillation, are allowed to settle. This kind of residual is sold under the name of "Steam Refined Cylinder Oil."

Crude oil of proper character will also produce a good cylinder oil by introducing steam during distillation in the bottom of the still, sufficient to prevent scorching or carbonizing by running down to 23° to 27° in the still. The lower the gravity the higher the fire test. If run slowly and carefully and strained while hot, a second steaming and settling will not be necessary to produce a good steam refined cylinder oil.

Crude oil not suited for cylinder oil produces a black lubricating oil or "West Virginia oil," as it is sometimes erroneously called.

Residuum oil is also filtered, while hot, through animal charcoal, to give it a brighter color and deprive it of all charred impurities held in suspension. As such it is known in the market as "filtered cylinder stock." Repeated filtration produces the products well known under the names of "vaseline," "cosmoline," "petrolatum" and many other fancy names. They are all compounds of paraffine wax in an amorphous state, to which the original crystalline wax of the residuum oil has been converted by chemical action during the repeated filtering through animal charcoal.

Petroleum Oils for Lubricating.

Petroleum oils for lubricating should have a flash point above 300° F. On general principles, the most fluid oil that will stay in place should

be used; the oil that possesses the greatest adhesion and the least cohesion is the best. conditions are possessed first by the petroleum oils and second by sperm oil, neatsfoot oil, and lard For light pressure and high speed machinery, mineral oils of a specific gravity of 30° Baumé and 350° F. flash point, mixed with sperm oil, olive oil or rape oil, should be used. For ordinary machinery, oil of a specific gravity of 25° to 29° Baumé, with a flash point of 350° to 400° F., mixed with lard oil, whale oil, neatsfoot, tallow, or with vegetable oils, should be used. on spindles in cotton mills, oils of 350° F. are quite safe, and the flash for cylinder oil should not be below 500° F.

For gas engines and gasoline engines, a pure hydrocarbon oil, of high vaporizing point, about 260° F., a flash point of 430° F. and a fire test of 550° F., should be considered best.

A compound of lard oil and petroleum burning oil, used in lanterns as signal oil, should not contain less than 40 per cent of prime lard oil and have a flashing point not below 200° F., and a burning point or fire test not above 300° F.

Deblooming Petroleum Oils.

For adulterating animal or vegetable fatty oils with petroleum, neutral oils are debloomed, which means freeing them from their fluorescent appearance, by refining them with chromic acid, or more readily as follows:

The oil is heated to about 140° to 160° F., and nitro-naphthaline, binitro-benzol or binitro-toluol, known as myrbane oil, is added and well stirred into the oil in proportions of about three ounces to from twenty to twenty-five gallons of oil with a slight bloom, and from fifteen to twenty ounces for oil with heavier bloom. There is thereby no material influence exerted on the oil and no tendency of the bloom to reappear remains.

For test, boil one part of the oil with three parts of a ten per cent solution of potassium hydrate in alcohol for one or two minutes. If either of the nitro-compounds is present, a blood or violet-red coloration will be produced. A pure oil is changed by this test to a yellow color only.

Devdorizing Petrol Oil.

Kerosene oil and benzine can be deodorized from their bad odor as follows:

The kerosene oil is mixed with chloride of zinc and then poured into a vessel which contains burnt lime, and after stirring well, is left standing for some time, to settle, when the pure kerosene is drawn off.

The benzine is mixed and well stirred with a mixture composed of alkali manganese oxide, some water and sulphuric acid. After some twenty-four hours' standing the benzine is drawn off again, treated with permanganate and soda in water.

Benzine and kerosene oil can also be deodorized and bleached, and their specific gravities improved, by a treatment with nascent or fixed hydrogen gas. One per cent of amyl acetate will also deodorize petroleum oils.

VIII.

MANUFACTURE OF LUBRICATING OILS.

THE manufacture or compounding of lubricants is manifold. For cylinder oils, mineral or petroleum oils of a specific gravity of about 27° Baumé and a fire test of about 550° F., either alone or with additions of from one to ten or fifteen per cent of animal or vegetable oils, are used. The fatty oils that such lubricants are generally compounded with are lard oil, neatsfoot oil, tallow oil, linseed oil, cottonseed oil, rapeseed oil, or degras. For heavy pressure and low-speed machinery, lard, tallow and other compounded greases, either by themselves or mixed with graphite (plumbago), mica and soapstone (talc), are used.

On account of their great propensity for absorbing oxygen, the fatty oils are now seldom used alone for lubricating, but are more or less compounded with petroleum oils. The viscosity

or lubricating power of spindle oils and red oils depends on the amount of amorphous paraffine wax they hold in suspension, which, however, loses much of its consistency under the influence of frictional heat.

To give petroleum oils a viscous consistency they are often compounded with proportions of oleate of lead (lead plaster) dissolved in the oil while heated to from 140° to 160° F. One to two per cent of unvulcanized caoutchouc or rubber are also often dissolved in the oil, heated and stirred together until thoroughly diffused. Soap in various proportions and thoroughly dried is also compounded in petroleum lubricating oils by heating and stirring until fully dissolved and diffused and the oil has become perfectly bright and clear. Four ounces of soap to a gallon of oil will cause it to gelatinize at 60° F., and one pound of soap to the gallon will convert it into grease.

For cylinder oil, steam refined residuum stock or medium filtered cylinder stock is heated to about 130° to 140° F. and stirred or blown until free from moisture and scum, and from one to five gallons, or even more, of tallow oil, lard oil.

neatsfoot oil, rapeseed oil, olive oil, or #th oil added to each barrel of stock. To give common filtered stock a better cold test for winter use. paraffine oil or red oil, of 28° to 30° Baumé is added in the proportion of about five gallons, more or less, to a barrel of stock.

Degras (woolfat) is also used in the compounding of this kind of cylinder oils, in the proportion of from one to three gallons to a barrel of filtered The degras should be previously heated and all arising scum removed before mixing with the cylinder stock.

Castorbean oil, well heated together with yellow lard grease, and combined with well heated cylinder stock, is compounded for cylinder lubricating oils.

For engine and machinery oil, paraffine, spindle or red oils of a gravity from 28° to 33° Baumé, are compounded and well stirred together with a few gallons of filtered stock to improve the viscosity of the lighter petroleum oils.

The compounding of petroleum with fatty oils, for engine and machinery lubricating purposes, should always be conducted at a temperature of about 140° to 160° F. and with a thorough mixing, else the oils, being only a mechanical, and and not a chemical, mixture, when resting will separate from each other, on account of their differences in specific gravity. This explains the fact that such compounded oil, when imperfectly mixed, when kept in tanks and gradually drawn off by the faucet placed near the bottom, appear at first to be of a satisfactory consistency, but drawing towards the end are complained of as being too thin and deficient in body, the oil in the course of time having separated and the lighter oil having gradually risen to the top.

Crude rosin oils are refined by distillation and the resulting products are treated and bleached with chemicals and skillfully deodorized so that not the slightest odor would betray their origin, unless partially decomposed under application of heat. As the rosin oils are of a very low gravity, they are used in the compounding of lubricating oils to give the petroleum oils a body and to pass 'the lighter oils off for lubricating oils of lower gravity and greater viscosity. Lard oils and other fatty oils are often adulterated with petroleum oils, and to reduce the lighter gravity of the latter, have been compounded with such deodor-

ized rosin oils, to equalize the specific gravity of such compounded oils to that of genuine lard oil.

Lubricating oils have also been made by avaricious and ignorant compounders by mixing heavy rosin oils with lighter petroleum oils or even simply dissolving common rosin in them, in the proportion of from two to four pounds to a gallon. The viscosity or body of such compounded oils appears deceptively superior to some of the best lubricating oils, but like all rosin oils and rosin and rosin oil mixtures, which form resinous deposits under the influence of frictional heat or on exposure to the air, they are entirely unfit for lubricating purposes, they gumming up the machinery and retarding the motion by their sticking propensities.

Thickened Oils.

Rapeseed oil, cottonseed oil and other fatty oils can be thickened and their viscosity increased by heating them to from 160° to 170° F. and forcing or blowing air heated to a like temperature through the oil for several hours. The propensity of the fatty oils for absorbing oxygen allows of turning them by this process into heavy, vis-

72 FRICTION, LUBRICATION, OILS AND FATS.

cous oils, which are largely used to impart greater viscosity to lighter petroleum oils used for lubricating purposes.

Blown rapeseed oil has a specific gravity of 0.967 at 60° F., or 15° Baumé.

Blown cottonseed oil has a specific gravity of 0.974 at 60° F., or 14° Baumé.

IX.

"VALVE-OLEUM" OILS.

THE fatty oils and fats are composed of either oleic, margaric or palmitic and stearic acids, which, when treated with caustic soda, form compounds soluble in water. Precipitated with mineral salts, such as sulphate of alumina, magnesia, lime, or acetate of lead, etc., they form insoluble compounds, which are only soluble in other fatty oils or petroleum oils. In this state the oils possess uncommon lubricating power, without the injurious effect the otherwise free fatty acids would exert on the metal of which the machinery requiring lubrication is made. They form the foundation of the manufacture of the "Valve-Oleum" Oils ("Valve-Oleum" is their trademark), patented by the author, and they combine the excellent lubricating qualities of fatty oils with the great cleanliness and diffusing qualities of mineral oils. To manufacture the valveoleum oils, lard oil, cottonseed oil, neatsfoot oil or lard-grease, or even fish oils, can be used to make the "Valve-Oleum" Gelatine, the mineral. castor and the so-called honeydrop engine oils. Neatsfoot oil is used to make the finest grades of "Valve-Oleum," cylinder oil, and for a heavier and coarser grade cake-tallow can be used. strained white lard oil or extra prime lard-grease is used to make the so-called "Valve-Oleum" white castor oil and the oil known as "Commercial Castor Oil," a cheaper substitute for the more costly castor bean oil. The oleate, margarate or palmitate, or stearate of alumina, is the combination preferably used in the manufacture of the "Valve-Oleum" Oils, although oleate of lime and oleate of lead can be used in like manner, the latter especially in the manufacture of paints, paint oils and factitious linseed oils.

Oleate of alumina is made in the following manner:

A solution of caustic soda is first prepared by dissolving caustic soda (some 160 pounds for a batch of 1,200 pounds of oil or fat) in about 90 gallons of water, thus making about 110 gallons of a caustic soda lye of from 22° to 23° Baumé.

If the lye is freshly made, it will be heated by the chemical action which takes place between the dry soda and the water. In that case, if fat or tallow is to be used, it is only melted with heat so that the combined temperature of the fat with that of the hot lye will not exceed 250° F. If the lye has been previously prepared and has become cold, the temperature of the oil or fat should be increased to about 200° F.

While constantly stirring, the lye is slowly run into the oil or fat and the stirring continued until the mixture has become a soapy, mushy compound and has assumed a perfectly neutral and soapy taste to the tongue. This will be accomplished in from one to two hours, depending much on the quality of the fat or oil, being fresh The resulting product is the oleate of soda, which is next dissolved with boiling water. Previously from 550 to 600 pounds of alum (sulphate of alumina) are dissolved in about 6 barrels of boiling water, and when all is dissolved and the solution is perfectly clear, it is, while constantly stirring, gradually run into the solution of oleate of soda, enough of it until the oleate of alumina thus formed floats as a pasty compound on a

clear, watery solution of sulphate of soda, the sulphuric acid of the sulphate of alumina having united with the soda of the oleate of soda, while the oleic acid of the oleate of soda has united with the alumina and formed "oleate of alumina." The whole mass is now started boiling and if any lathery foam still appears on the surface, some more alum solution is added, until all the foam has disappeared and the liquor remains perfectly Next one barrel of 25° paraffine oil is clear. added, and the whole briskly boiled and stirred for about one hour. Then the steam is turned off and stirring is stopped and the pasty mass allowed to subside over the clear, watery liquid. This is then drawn off and replaced with fresh boiling water, and the boiling and stirring are resumed and several times repeated, until all taste of alum or sulphate of soda has been removed. The last wash-water is then drawn off, and heating and slow stirring continued for a short time, and then discontinued, to allow of some more water, freely separating, to be drawn off from underneath the pasty mass. Heating and stirring are now again resumed, keeping the heat at a high and uniform temperature, until the

pasty mass becomes turned from its white to a brownish color and has become perfectly clear and transparent and is pulling heavily, like molasses candy.

When a small sample of the mass, thrown onto a glass plate, shows perfectly clear and transparent and free from all moisture, paraffine oil, which has been previously heated to about 140° to 160° F. and kept at that temperature until all hygroscopic moisture and adhering light hydrocarbon vapors have been expelled, is then added by slowly running it into the batch while constantly stirring and keeping the temperature at from 150° to 160° F. for from two to three hours or more.

To make the "Valve-Oleum Gelatine" not too heavy and so as to allow it to be drawn off into barrels, but still warm enough to prevent it from chilling, from $3\frac{1}{2}$ to 4 barrels of the paraffine oil to every barrel of fat or oil used in the making of the aluminate, are required.

To make a heavy and stringy mineral castor for use on heavy bearings and machinery, some 40 to 45 barrels of paraffine oil to a 1,200-pound (or 3 barrels) batch of fat or fatty oil, are required, and more if a lighter grade is desired.

"Valve-Oleum" engine, so-called "Honey-drop" oil, is made in precisely the same manner, but in order to cut the stringy nature of the heavy castor oil to a honey-drop one, better adapted for oiling engines and lighter machinery, from 30 to 40 gallons of degras to a 1,200-pound batch are added together with the barrel of paraffine oil when boiling the compound, after the precipitation with alum and before the repeated washings.

For "Valve-Oleum" cylinder oil, a barrel of cylinder stock and from 40 to 50 gallons of degras are used at the boiling with the compound, if the cylinder stock to be used is of a reasonable cold test, otherwise a barrel of 25° paraffine oil is used. The batch is then finished up with from 40 to 45 barrels of filtered cylinder stock, which has also to be previously heated until all hygroscopic moisture and arising scum have been removed, as otherwise the combination will not remain uniform. Imitations of the "Valve-Oleum" oils, for the sole purpose of giving to light distillates or poor paraffine oils some lubricating qualities, such as the so-called "Eldorado" oil and others, will easily thin out, separate and

lose their consistency, as they are only crudely mixed with distillates or light paraffine oils not previously freed from their adhering hygroscopic moisture and light hydrocabon vapors in suspension.

White "Valve-Oleum" castor oil is made precisely like the "Valve-Oleum" engine oils, but extra white winter strained lard oil or prime white lard grease is used in the making of the oleate alumina compound, and 300° white mineral oil is used in place of the paraffine oil.

"Valve-Oleum" castoroleum, also known as "Commercial Castor Oil," a cheap substitute for castorbean oil, is made by using white tallow or prime white lard grease for making the alumina compound, adding some 300° F. white mineral oil, to be boiled with the alumina bath, and, after washing and roasting the alumina compound down to a perfectly clear and transparent product, it is mixed with white summer cottonseed oil, previously blown at a low temperature, to a consistency of about 15° to 18° Baumé.

"Valve-Oleum" Linoleum is made by using linseed oil, fish oil, rapeseed oil or corn oil for making the alumina compound, boiling with an addition of neutral oil and mixing with linseed oil previously blown at a moderate heat to a consistency of about 18° Baumé. In place of alum, acetate of lead can be used to precipitate the linoleate of soda with, thereby forming a linoleate of lead.

To detect one part of oleate of alumina in ten parts of mineral oil, heat the sample with diluted hydrochloric acid over a water-bath and stir it well. The hydrochloric acid absorbs the alumina and the fatty acids remain in the mineral oil. The mineral oil is drawn off and treated with soda lye, which unites with the fatty acids and separates from the mineral oil.

LEATHER OILS.

LEATHER belts, harness, boot and shoe leather require as much attention in regard to lubrication as does machinery. Hides when deprived of their natural lubricating moisture, become dry and easily break. When converted into leather for belts, harness, boots and shoes, it would soon become useless for wear were it not for the interposition of the fatty lubricants known as "leather stuffings," which relieve the frictional action of fiber against fiber of which leather is composed. The more volatile these fatty lubricants are the oftener they require renewal, lest the frictional heat and the abrasion of the fibers against each other, heat, burn and destroy the leather. as we have recourse to processes by which we harden and strengthen metal to make it more durable, so we try to protect leather and make it more durable, by the different finishing processes to which it is subjected, but unless the frictional action of fiber against fiber is relieved by constant lubrication, the frictional heat will destroy the fiber. For this purpose leather oils for lubricating, water-proofing, softening and preserving leather are generally compounded after one or the other of the following formulæ:

" Valve-Oleum" Leather Preserving and Water-Proofing Oil.

Two barrels of "Valve-Oleum" gelatine made from neatsfoot oil, as described on page 74 et seq., are compounded and well mixed with two barrels of coon oil, neatsfoot oil or fish oil (tanners' oil). Thereto are added five pounds of Para-gum, cut into fine shreds and dissolved by heat in five gallons of coon oil or neatsfoot oil. It can be colored with a sufficient amount of black West Virginia or Mecca oil, or with fine lampblack ground in fatty oil. The fatty oils used should previously be heated until all their hygroscopic moisture is driven out, and the arising scum skimmed off, before mixing with the gelatine.

An oil for tanners' use is made also with "Valve-Oleum" gelatine and fish oil (train oil)

with additions of paraffine oil of low specific gravity.

A cheap harness oil is made with one barrel of "Valve-Oleum" gelatine and eight to ten barrels of heavy black petroleum oil and colored with gilsey (Egyptian asphalt), gum or lampblack ground in neatsfoot or fish oil.

A black harness oil is also made with fifty barrels of dip oil, fifteen barrels of spindle or red oil, five barrels of degras and two barrels of lampblack ground in neatsfoot oil or fish oil.

A good belt oil can be made by dissolving by heat 150 pounds of rosin in one barrel of castor-bean oil and scenting it with citronella or myrbane oil. Paraffine oil, in which four to five pounds of rosin to the gallon have been dissolved, can be substituted for part of the castor-bean oil.

For belt oil Para-gum also is dissolved in neatsfoot oil and compounded with "Valve-Oleum" heavy castor oil.

A "Belt Grease" is made by dissolving in fifteen parts of fish oil and five parts of tallow, with heating and stirring, five parts of India rubber (Para-gum), cut into fine shreds, and adding four parts of rosin and four parts of beeswax; stir well until congealed to proper consistency.

Factitious Paint Oil.

A cheap substitute for linseed oil is made by dissolving rosin oil in neutral oil and mixing it with linseed oil—2½ gallons of linseed oil, 2½ gallons of neutral oil, with from 2½ to 3 pounds of rosin, the whole being improved by boiling with oxidizing agents or acetate of lead until all the acetic acid of the latter has been expelled and the oil has become bright and clear.

A cheap paint oil is also produced by compounding blown linseed oil with neutral oil and a sufficient amount of dryer made from rosin spirits.

XI.

ADULTERATIONS OF FATTY OILS.

When the market price of lard oil is high and that of cottonseed oil is low, lard oil is often adulterated with the latter. It is also adulterated with petroleum oils, especially prepared for that purpose, and with addition of refined and deodorized rosin oil, to equalize the specific gravity of the mixture to that of pure lard oil. No. 1 lard oil is adulterated with white neutral oil and No. 2 lard oil is adulterated with yellow neutral oil.

Olive oil is also much adulterated with cottonseed oil, sunflower oil and others, when their market prices, being lower than that of olive oil, warrant such adulteration.

Sperm oil is much adulterated with cheaper fish oils, well refined, deodorized and bleached.

Linseed oil is adulterated with corn oil, cottonseed oil, rapeseed oil, hempseed oil and rosin oil. Sperm oil should not contain less than four per cent of cetin unless adulterated. Shake one part by weight of sulphuric acid of 1.84 specific gravity, with four parts of the oil; allow to stand for about twenty minutes, shaking twice; add three ounces of distilled water, shake well and allow to stand sixteen to twenty hours; dilute then with three or four times its volume of distilled water and mix thoroughly. On standing the cetin floats on top and can readily be skimmed off; then wash, dry and weigh. It is soluble in chloroform.

Castor oil is adulterated with blown oils, such as linseed, rape or cottonseed and rosin oils. If only ten per cent of them be present, they cause a turbidity with absolute alcohol, with which castor oil is miscible in every proportion.

XII.

TESTING OILS.

ALKALI tests are made to ascertain first if an oil is a pure fatty oil, or a hydrocarbon oil, or a mixture of both. A solution of caustic soda or potash of a specific gravity of 1.340 is prepared and two volumes of this solution are shaken up with four volumes of the oil to be tested. After standing, the oil separates out, leaving an aqueous layer clean or slightly clouded. If hydrocarbon oils are in large proportion in the sample, they will form a layer on the top and the aqueous layer will be emulsified. If the fatty oil is in largest proportion, the smaller proportion of hydrocarbon oil will be more difficult to detect. To ascertain this, dissolve a piece of caustic potash, the size of a pea, in 5 c.c. of alcohol. Then add a few drops of the oil to be tested and boil for two to three minutes and add from 3 to 4 c.c. of distilled water. If the solution remains clear,

only fatty oil is present. Mineral oil will cause the solution to be turbid and even as small a quantity as 2 per cent present will show itself this way.

The amount of mineral oil in fatty oils is also ascertained by mixing 25 grammes of the oil with 10 to 15 c.c. of the caustic solution and 25 c.c. of water and 5 c.c. of alcohol. This is boiled, constantly stirring, for about one hour. By that time the fatty oil is saponified. Put the whole in a separating funnel and add more warm water and 25 c.c. petroleum ether; shake for a few minutes and allow to stand. The upper stratum is composed of the petroleum ether and the mineral oil and the lower stratum of the aqueous layer of soap formed by the fatty matter. This is run off, clean water is added, stirred together and again allowed to stand and the aqueous liquor run off. This is repeated until the latter runs off perfectly clear. Now put the ethereal layer into a weighed vessel, evaporate the ether and weigh the remaining oil; the weight multiplied by four gives the percentage of mineral oil in the sample.

A color test can be made by placing some 20 drops of the oil in a porcelain cup and adding

two drops of strong sulphuric acid. As the acid drops through the oil, streaks of color are shown, and a tint of characteristic color gradually spreads through the oil. Then stir the whole and again note the coloring. Vegetable oils give various colors, shades of yellow-brown or green; fish oils turn to violet or purple, animal oils to a reddish-brown, and hydrocarbon oils turn slightly to a blackish-brown. The test should first be made with samples of known pure quality and compared with the action of the sample under test.

Agitating 4 c.c. of the oil to be tested with 10 c.c. colorless nitric acid will show, after settling, when olive oil has been adulterated with cotton-seed oil, by a brownish color, while pure olive oil will not become darkened.

For a test of cottonseed oil in lard oil put ½ ounce of nitro-sulphuric acid and ½ ounce of the oil to be tested in a glass vessel and stir well. Pure lard oil becomes hard in two to three hours, but when adulterated with cottonseed oil the sample may thicken but will not become hard.

For a preliminary test for neutral oil in lard oil, shake the suspected sample violently in a bottle. If it contains neutral oil it will form beads or bubbles that will pass away when the oil is pure, but if adulterated with much neutral oil it will have a tendency to foam.

To detect small quantities of fatty oils, of ½ to 2 per cent, in a sample of mineral oil, some of the oil is heated for about fifteen minutes, with bits of sodium or sodium hydrate, to about 230° to 250° F. Fatty acid present will solidify to a jelly of more or less consistency, according to the amount of fatty oil therein.

To detect soap dissolved in mineral oil, five to ten per cent of the oil is dissolved in about fifteen parts of gasoline or ether, and solution of phosphoric acid added. The formation of a flocculent precipitate indicates the presence of soap.

To detect acidity or alkali in mineral oil, shake a sample of the oil with an equal quantity of warm water, pour off the oil when settled, and test the water with litmus paper. Acidity will turn blue litmus paper red, and if alkaline, will turn red litmus paper blue, and yellow turmeric paper brown.

We will not follow any further into the inexhaustible field of chemical and technological testing of oils, but would call attention to some simple and practical methods for testing oils and oil mixtures, as to their purity and efficiency as lubricants, that can be carried out by the most inexperienced investigator.

First are to be secured samples of known purity of the different kinds of animal and vegetable oils used in the manufacture of lubricants, and then proceed with the testing of the oils to be investigated as follows:

All fatty oils of animal or vegetable origin possess an odor and taste peculiar to themselves, which becomes more distinctly noticeable when the temperature of the oil is increased. fore a few drops of the oil, to be investigated as to its characteristics or origin, are placed in the palm of one hand and vigorously rubbed by the other until a burning sensation is experienced, we can ascertain the individuality of the oil by the smell from the flavor known to be peculiar to it and corresponding with that of one of the samples of known origin and purity. We can thereby tell if it is lard oil, cottonseed oil, tallow oil, fish oil, palm oil or rosin oil, etc., and by this method we can in many cases also ascertain which of these oils may be intermixed with another.

When the oils are fresh and pure and carefully purified and bleached, their peculiar odor is not so readily noticed as when they are older; but by slightly heating between the hands we are enabled to recognize their characteristic odor.

Tasting oils will also enable us to ascertain their individuality, when we make comparison of their taste with that of the samples of oils, the purity and character of which is known to us.

The intermixing of fatty oils for purposes of adulteration, when the one oil can be bought in the market at lower price than the other, is not very detrimental in their use for manufacturing purposes, but when fatty oils have been adulterated with petroleum oils, the difference in value and the thereby lowered quality of the oil, demands investigation. Lard oil, cottonseed oil, neatsfoot oil and other fatty oils, are more or less adulterated with high fire test petroleum oils, and with such of them as has been especially prepared and deodorized for that purpose. Such adulterations can be detected by the following simple tests:

When petroleum oil has been admixed in large proportion, the simple pouring of some of the oil on a dark ground, or, into a smoked glass plate, in a place where the sunlight can fall on it, will give sufficient proof of the presence of petroleum oil, by its bluish, fluorescent shining. Its presence can also be ascertained by the use of the hydrometer. As the specific gravity of petroleum is so much higher than that of fatty oils, the hydrometer cannot fail to indicate by the so much increased specific gravity of the mixture above the well known lower gravity of pure fatty oils, that petroleum is present and how much of it. Its presence in fatty oil compounds can further be ascertained by slowly heating a sample of the suspected oil in a porcelain dish over a spirit lamp, with a thermometer suspended in it, and by applying from time to time a lighted match to it and note the temperature at which the oil Petroleum used for compounding will ignite. with fatty oils will vaporize and ignite at from 110° to 300° F. while fatty oils require for ignition twice as much heat.

To ascertain with what proportion of petroleum a fatty oil has been adulterated, samples are prepared and mixed in various definite proportions. Mark on each sample the proportion of petroleum added to the oil, the specific gravity ascertained by the hydrometer, and the temperature at which it became ignited. By submitting a sample of the oil to be investigated to the same test, we can easily ascertain the proportion of petroleum it contains, by comparing the result of the test with those marked on the prepared samples.

We can tell of the presence of petroleum in fatty oils, even in very small proportions, by placing a small quantity of the suspected oil on our tongue and subjecting it to the motion of mastication, the same as if we were tasting some other fatty nutriment, such as butter or lard. The alkaline saliva in the mouth will act upon and unite with the fatty oil of the sample but not with the petroleum oil it contains, and after the fatty oil has become absorbed by the system, the presence of petroleum will manifest itself by its remaining nauseating taste.

To prevent detection of adulteration of fatty oils by the hydrometer test, fatty oils are often mixed with petroleum and refined rosin oil, to equalize by the low specific gravity of the latter the lighter specific gravity of the petroleum. Their presence, however, is easily detected by taste and likewise by smell, when heated by friction between the hands, as before explained.

The comparative efficiency of oils for lubricating can be tested in many ways without the use of costly testing machines. To ascertain the gumming propensities of an oil we need only to spread some of it in a very thin layer over a glass plate, protect it against dust, and expose it to the sunlight or other slow, dry heat. In a short time the gumming propensity of the oil will be indicated by the tough and sticky appearance of what of the sample remains on the glass.

Viscosity.

Viscosity is the degree of fluidity of an oil. The greater viscosity or body one oil possesses over another can be ascertained by allowing a given amount of the oils to be tested to drop out of the narrowed end of a glass tube, or count the drops falling from them in one or more minutes and compare the difference. By varying the test at a colder or warmer temperature, the uniform consistency of the oils can likewise be ascertained and compared.

By pouring a drop of oil to be examined on a

well-cleaned glass plate placed on an incline, alongside of another placed likewise, and noting the time it takes for each oil to reach a mark made on the bottom of the inclined plane, we can observe to some extent the greater viscosity or body and clinging power one oil possesses over the other. By increasing the temperature by means of an alcohol lamp or otherwise we can likewise judge of the uniform consistency one oil maintains over another, or compare it with like tests made with oils of known efficiency.

Fire Test.

The test often made with cylinder oil, by pouring some of it into a cylinder chest, cannot be considered conclusive, as the temperature on the outside of a cylinder chest is dry and scorching, while the temperature inside the cylinder, where the oil is expected to perform its work, is moist. That an oil would show less tendency to evaporate in the dry and scorching heat on top of the cylinder chest, would only indicate its higher fire test, but high fire test is no criterion as to its qualities, as the temperature inside of the cylinder can never be a dry and scorching one. The fire test

of an oil should always be in proper proportion to its heat-absorbing quality, or it will suffer decomposition and produce gummy deposits by its inability to vaporize fast enough under the frictional heat and carry its vapors diffused with the exhaust steam into space.

Simple Way of Testing Lubricating Oils.

A very handy and simple way of testing oils is to place them side by side on white blotting paper and place this for a short time on a cylinder chest or a steam heater. The oil which penetrates the blotting paper quickest and spreads widest over it, is always the poorest and thinnest oil, as it shows by its lightness and the quick disappearance of its outer ring, that it is compounded from material of very light specific gravity. If by giving it some time, or by longer exposure to heat, the whole of the oil on the blotting paper disappears, the sample must be composed entirely of petroleum, and when an inner ring, with a well discernible line, is formed and remains longer, a proportion of paraffine holding stock must have been compounded with lighter petroleum, and when a center ring, with decided outline and

darker color, is formed, but no permanent translucency is imparted to the paper, the compound must be made of a light hydrocarbon oil, with an addition of still residuum stock, however well refined or bleached. If the oil to be examined has been compounded from petroleum, with an addition of lard oil or tallow oil or other fatty matter, the blotting paper will retain its translucency in the center long after the petroleum, which at first spread rapidly over and through the paper, has disappeared. Petroleum penetrates blotting paper faster than fatty oils and spreads wider over it at first, but dries off rapidly and its translucency disappears, while that of fatty oils remains, as one of the principal characteristics of fatty oils is their faculty to render paper permanently translucent.

Practical Tests of Lubricating Oils.

Tests made by the practical use of the oil are by far the best, but we must not allow ourselves to be deceived and be led to attribute too rashly any unsatisfactory results at first obtained, to the oil we are testing. If the oil previously used was an impure one and of a gumming qua-

lity, however satisfactory it may have appeared to work, it will have left its gummy deposits in crevices and joints and in the interstices in the metal, which is commonly regarded as a bearing which the oil has made for itself, and when the new oil to be tested is applied in too small a quantity, we fail to observe that such a small amount of purer oil has at first to contend with and dislodge the deposits, which may be the result of long standing and the accumulations of large quantities of the oil formerly used. It is this fact that misleads and often causes the better oil to be condemned, until a larger and longer application proves the correctness of this statement.

These same facts will appear when we apply for a test a poorer and impure oil, after having used an oil of purer and better quality. The poorer oil finding all the bearings or the cylinder clean and no gummy deposits to contend with will, for a time, appear to work equally as well as the good oil that was in use before.

Cylinders and bearings, as well as the feeding cups, should be carefully cleaned before testing or using a new oil, if we wish to be able to judge correctly as to its quality.

Objection is sometimes made by engineers to

the stringy character of the "Valve-Oleum" oils, but this stringy nature, while perhaps somewhat inconvenient under careless handling, constitutes the very life of the oils, secures their uniform consistency in cold as well as in warm weather, and enables them to cling tenaciously to the metal, absorb the frictional heat as fast as it is generated by the motion, and permits their body to be of light enough character to vaporize rapidly into space with the heat they have absorbed.

Unscrupulous parties, making imitations of the "Valve-Oleum" oils, use their stringy characteristics solely for the purpose of artificially thickening light and otherwise unsalable petroleum oils, but such mixtures do not stay together; they separate and are not neutral and contain free fatty acids, and are but little more efficient for lubricating than the cheap petroleum distillates.

By the blotter test, the "Valve-Oleum" oils show their fatty characteristics by leaving permanent, translucent center spots on the paper; they show their uniform consistency by being slowly absorbed by the paper and spreading over it without separating, and they show their cleanliness by leaving no deposit of impurities on the paper.

XIII.

SOLID LUBRICANTS. GREASES.

Solid lubricants consist principally of filtered stock or vaseline, and they are fed to the bearings through cups especially devised for that purpose, and furnished with screw pressure, or provided with copper rods, which latter, touching the shaft, cause feeding of the vaseline or other greases by communicating the frictional heat to them, whereby they are liquified, and caused to flow onto the shaft and into the bearing.

Greases for lubricating consist principally of tallow or lard, of either or both, together with palm oil, rapeseed oil, degras, rosin oil and petroleum oils brought to a proper consistency by semi-saponification with weak lye, limewater, or lime-soap, or lime-paste.

Fatty matter of all kinds and quality, residuum and tar from refineries, in short all that can be worked into this kind of lubricant, and can be given a greasy appearance and consistency, is worked into what is known and sold in the market under the name of "Lubricating Grease."

The character of the machinery for which this kind of lubricant is used is of the coarser, heavier kind; hence less attention is generally given to ascertain the indirect advantage that would result from the use of grease of best quality, cost being generally the only point considered.

Here also, as with the lubricating oils, it is the fatty acid alone which is the lubricating, that is, the heat-absorbing and eradiating principle, held to the moving surfaces by medium of the stearin, palmitin, rosin or, paraffin, the latter being ultimately left as concentrated and charred gummy deposits.

With grease lubricants the wear and abrasion of the metal is always greater than with oil lubrication, as the consistency of the grease requires greater accumulation of frictional heat to melt and convert it into a liquid state before it is enabled to reach the place where it is expected to do its work.

Carefully conducted experiments have demonstrated the fact that it takes some twenty-five per

cent less power to move machinery lubricated with oil than when lubricated with grease, and at a some thirty to thirty-five per cent lower temperature.

The additions of lime, graphite (plumbago), lead, asbestos, mica, sulphur, soapstone (talc) and all other inert matter, to grease, used on machinery moving under great pressure and heat, act only as a medium, filling the interstices in the metal, and serve only as a sort of cushion for the real lubricant, the fatty matter contained in the grease. These inert substances cannot vaporize with the frictional heat and must, therefore, remain as gummy accumulations and metallic abrasions on the bearings.

Manufacture of Greases.

Most greases for lubricating are made in the following manner: Common red rosin oil, say five hundred pounds, is heated for about one hour with about two pounds of calcium hydrate. It is then allowed to cool and is skimmed, and from ten to fifteen pounds of rosin oil-lime soap slowly stirred in until the mixture assumes a buttery consistency. Lime soap is made by

slowly heating and mixing 100 pounds of crude rosin oil with some 80 pounds of hydrate of lime, and boiling into a molasses-like consistency.

For rosin grease, lime paste is made by slaking say 10 pounds of quicklime with about 40 pounds of water, passed through a sieve to separate all coarse particles, and for the fine lime paste to be allowed to settle. The water is then poured off and from 6 to 8 gallons of crude rosin oil are stirred into the lime paste and allowed to stand for a few hours. All accumulated water is then drawn off and from 8 to 10 gallons of mineral or heavy petroleum oil are added. The whole is then heated to about 230° to 240° F., stirred and well mixed and allowed to cool and set to proper consistency.

A rosin grease, without heating, in the cold way, is made by mixing and stirring well together 20 gallons of crude paraffine or other mineral oil, in which some 80 pounds of rosin have previously been dissolved by heat, with a lime-paste made by slaking one-half to three-quarters of a bushel of lime, sifting it from all coarse particles and separating most of the water from it. It is stirred until a smooth, uniform

consistency is obtained. From 3 to 5 gallons of crude rosin oil are then slowly added and stirred to a proper buttery consistency. The product of this process is the well known "Valve-Oleum Zola Axle Grease." Additions of fats or fatty oils improve its quality.

The following are some formulas after which nearly all grease lubricants are manufactured:

Half a pound of caustic soda is dissolved in one gallon of water; from three to five pounds of tallow and one-half to one gallon rosin oil are added, and the whole is heated to about 210° F. and well mixed, and then stirred, as it cools, to its proper consistency.

Forty gallons petroleum oil, fifty pounds of yellow grease or tallow and sixty pounds of rosin are heated together at a temperature of about 240° F. From two to two-and-a-half gallons of soda lye are then gradually added, and all is mixed and stirred well. When cold it will have set in about twelve hours and will be ready for use.

For a "cup grease," seventy-five pounds of tallow, thirty to fifty pounds of rosin, some thirty to forty gallons of paraffine oil, and about ten to fifteen pounds of oleate of soda or common soap are melted together and stirred until a uniform and smooth buttery consistency is obtained.

Also: One part of tallow or yellow grease, four parts of cylinder stock or paraffine oil of a low gravity, and one-quarter part of caustic lye of from fifteen to twenty degrees Baumé, are heated and stirred until cold and of proper consistency.

Dark axle grease: Thirty-five gallons West Virginia black oil, in which some fifty pounds of rosin have been dissolved by heat, and lime-paste from half a bushel of lime, are well stirred and brought to a proper consistency by the slow addition of from four to six gallons of crude rosin oil.

Linseed oil grease: One hundred pounds of tallow, one hundred pounds of rosin and ten to twelve gallons of linseed oil, with from six to eight gallons of caustic soda-lye of about five degrees Baumé, are boiled together and allowed to cool and set to proper consistency.

One gallon petroleum oil, one-half pound tallow, one-half pound palm butter, one-half pound plumbago and one-quarter of a pound of soda are heated and kept for about an hour at a temperature of about 180° F., then allowed to cool down, and are stirred until well setting to consistency.

Or: Water, one gallon, one-half pound soda, three to five pounds of tallow, from six to ten pounds of palm oil and sufficient rosin to give the desired consistency, are heated to about 250° F., well stirred until cooled down to about 70° F., and allowed to set.

Or: Ten pounds of common soap well dried and cut in small pieces, from fifteen to twenty pounds of filtered cylinder stock and about fifteen pounds of heavy petroleum oil, are heated to about 230° to 240° F., and well stirred until all the soap is dissolved, and the whole is then allowed to cool to proper consistency.

Or: Palm oil, tallow, or tallow oil and soda, dissolved in as little water as possible, are heated and stirred into a uniform buttery mass.

Or: One gallon crude rosin oil, two to three pounds of quicklime slaked with about one gallon of water are mixed and allowed to settle and the adhering water drawn off. Heavy petroleum oil and from three to five pounds of graphite (plumbago) are then added, and all well mixed and stirred to a uniform and buttery consistency.

108 FRICTION, LUBRICATION, OILS AND FATS.

One per cent of castor oil soap will solidify paraffine oils in vacuum to a solid grease.

An endless number of like formulas could be mentioned, but they are all based on a semi-saponification of fatty matter or oils used in the manufacture of "Grease" for lubricating.

XIV.

SOME PRACTICAL SUGGESTIONS.

When a cylinder becomes partly worn, or ridges and scars are cut on its bright surfaces, or a partial wearing of the piston rod takes place, it is absurd to lay such results to the oil. The cause of such injuries is a purely mechanical one; some parts are loose or out of line or otherwise defective in construction and no amount of oil or fat of whatever quality is capable of preventing gradual increase of the injury and final necessity for extensive repairs.

No kind of oil or fat can cut ridges or scars in metal. It requires metal or inert substances, such as silica, lime, emery or mica to do it. They do it suddenly and violently when dry and by themselves, and they do it slowly and silently when intermixed and saturated with oil or fat. The idea that mixing plumbago, silex, sulphur or plumbago (graphite), etc., with oils or fats, to

give them increased lubricating power, is erroneous. These inert matters have nothing whatever to do with the lubricating, which is alone done by the fatty, oily part of the compound, leaving the inert matter behind, to accumulate with every new application, which by and by will fairly choke the cylinder and the valve-chest.

All fatty oils and fats, without exception and of however excellent quality, either alone or compounded with mineral oil, when applied as lubricants, are decomposed by the steam and by the frictional heat they absorb, and their lighter constituents vaporize and leave the heavier ones to form gummy deposits with the fine metallic particles, the result of abrasion, and with the impurities in the water used.

Such deposits cause dragging of the machinery and waste of power, accumulate gradually in crevices and fill the smallest interstices in the surface of the metal; they settle all around the joints and are found in abundance behind the rings and piston.

The injurious action from the use of tallow in cylinders is well known. The action of the stearin on the metal increases the abrasion, and injury is wrought slowly but entirely uniformly and by no means in cutting ridges and scars in the iron.

When tallow or very impure fatty oils have been used, or they have been further compounded with inert matter, such as plumbago, etc., the accumulations are still more abundant and detached parts are frequently found worked into marble-like balls by the continuous churning motion of the piston; they dry against the heated metal and gradually assume the hardness of stone or iron.

Lubricating oils which are not so constituted as to decompose readily and form gummy deposits, are capable of softening and gradually dissolving such hardened deposits. Some particles partly dissolved become detached and get between the piston and the cylinder and commence cutting and scraping into the smooth sides of the latter. A groaning noise gives audible warning and, if the impediment is not removed or relieved by speedy softening and dissolving with more copious application of better oil, the injury inflicted may become very serious and may necessitate the stopping of all machinery and require expensive repairing.

There are also numerous instances on record where small particles of metal broke off from worn out springs with too sharp and not properly rounded edges, or from careless keying of the valves, and finding their way between the sides of the cylinder and piston, cut heavy ridges in the iron.

Another source of injury in cylinders, otherwise perfectly clean, arises often from the use of poor packing, overdone with sulphur or overheated in vulcanizing, which has become brittle from exposure and age, or being burnt from long contact with the heated metal. The ragged edges of such packing will become detached, contaminate the oil, and cause injury.

If a babbit or other metallic lining has been placed in a bearing in a bungling manner, or small particles of the metal have broken loose from a raggedly bored hole through which the oil is to be applied, and such particles find their way between the moving parts, cutting and scarring of the metal cannot be prevented with the best of lubricants.

If an employee forgets and fails to apply oil in proper time, and the parts run dry, get heated and cutting takes place, the trouble is generally attributed to the lubricant, but all this proves that it is impossible for an oil to "cut metal," but that impurities in oils, accidentally or intentionally combined with inert matter, will do it.

The parts of machinery where oil is used for lubricating should be kept clean and carefully examined, to see if they are in proper condition; that no foreign matter has by chance got between the moving parts or is liable to do so; that keys on wristpins and bolts on bearings, hangers, etc.; have not gradually been loosened by the constant jarring of the machinery; that flooring has not settled under heavy weight and thereby the shafting, attached to it, been put out of line or otherwise interfered with.

All these points are generally only thought of after some accident has happened or warning is given by a groaning or squeaking noise, and when some parts are found heated and cut, and the blame is unjustly laid to the oil, until investigation reveals the real cause.

XV.

LUBRICATORS AND CUPS.

THE many contrivances commonly called "Lubricators," by which lubricants are applied to machinery, are often much trouble to engineers, as the adaptation of these contrivances is, with many, as much a consideration of price only as it is in the purchasing of lubricants, but with lubricators as well as with lubricants the best are always the cheapest. It is a great oversight to make the lubricant subject to the manner of applying it, as it is the lubricant that is to do the work and not the mechanical contrivance through which it is forced to do it. There are numberless such contrivances, many very ingenious ones and others of faulty construction, rather interfering with, than assisting, the lubricant to do its work properly.

Cylinder oils are applied by the hand-pump, by the automatic pump, or through the well known sight-feed lubricators. The hand-pump admits the oil too irregularly, too much at one time, not enough at another, either from neglect or oversight.

The automatic pump, such as the first and well known "Moses Pump," and the later improved styles are the best means for applying oils to cylinders with proper regularity. With the automatic pump the oil is not brought in contact with water or steam before entering the cylinder. It supplies the oil with the starting of the engine and ceases to do so when the engine is stopped, and all the attention that is required is to keep the pump supplied with oil. Any kind of oil, if clean and free from grit, can be fed through these pumps, and the amount to be fed is easily regulated by the shorter or longer stroke that is given at its connection with the engine.

The proper feeding of cylinder oil through the modern sight-feed cup, now generally used, depends entirely on the understanding by the engineer as how to use it properly. All the many sight-feed cups are devised on the principle of displacing the oil from the cup, drop by drop, by the water condensed from the steam before the latter reaches the cup. It requires a little time

and patience when starting or refilling these cups, to wait until sufficient steam has been condensed and enough water been accumulated to operate the cup properly and get the oil to feed with proper regularity; otherwise the steam will rile the oil. Introducing some water in the cup before filling with the oil, and slowly turning the steam on and regulating the feeding, will prevent overheating and allow of regulating at once the proper condensing of the steam and the regular displacement of the oil.

The use of impure oils should be carefully avoided and the cleaning of the cup not attempted by blowing live steam through it, as thereby the fatty deposits from the oil, in connection with impurities in the water used for the steam, are baked to the sides and openings of the tubes in successive layers by the latent heat held there by the metal, in precisely the same manner as the scale in boilers is produced from the slimy, earthy deposits of the water, by baking and incrusting them on the iron by the latent heat under the prevalent and injudicious practice of "blowing off boilers." Sight-feed cups should be taken off from time to time and carefully cleaned with benzine or coal oil and a swapper.

It is, however, not a question alone of merely getting the oil into the cylinder, but the oil must possess sufficient power to cling to the metallic surfaces of the cylinder and the valves, in order to resist its being blown out with the exhaust before its work has been done.

An oil that does its work satisfactorily when applied direct with a pump, but will not do so through any of the many patent sight-feeding devices, proves conclusively that the lubricator or the wrong handling of it should be blamed, not the oil.

There is an endless number of cups of all kinds of construction to apply lubricants to the bearings of shafting and all kinds of machinery. For feeding oils, those will command the most attention that will allow the operator to see at a glance if the feeding is regular and uninterrupted. They all require more or less adjusting to properly regulate the amount to be fed and allow the oils to pass through the aperture, according to their limpidity or viscosity.

In some of them the flow of oil is regulated by controlling the width of the aperture with opening and closing devices; in others a wick is placed over the aperture, to secure regular and slow feeding on capillary principle, and still in others a rod, with flattened side, is placed to prevent a too rapid flow of the oil. If they are properly handled and attended to and proper judgment is used in adjusting them, in accordance with the characteristics of the oil used, most of them will answer their purpose satisfactorily.

In those cups which feed with a wick, it is important that the number of strands in the wick should be in proper proportion to the limpidity or viscosity of the oil used, and in those cups separated with metallic stem, with a flattened side, the latter should be filed still flatter or the stem removed entirely when a change is made from a limpid and easy-flowing oil to one which has a heavy body of uniform consistency.

In all cups exposed to varying temperatures, only such oils should be used as will not congeal and thereby become unable to flow and feed through the aperture. Frequently when changing from one oil to another, and especially when the oil first used was of a gummy character, and the new oil does not possess this objectionable quality, the oil may at first feed well enough

through the aperture, without the necessity of changing its adjustment, but on account of its gradual loosening the almost imperceptible coating or gummy film on the sides of the cup, the latter is apt to obstruct the opening and the oil will be unable to force its passage through, and the bearing, running warm, the oil will unjustly be condemned as being a poor lubricant.

Cups especially designed for feeding grease are also of varied construction and character. These cups should also have apertures proportionate to the melting quality of the grease used.

There are cups where it is intended to force the grease down by pressure or by springs, which consequently require much attention and adjusting and cannot be considered automatic feeders.

Those cups provided with metallic stems, resting on the shaft, to work on the principle that the frictional heat conveyed through these stems will melt the grease and make it limpid enough to flow down on them, also fail to secure perfect lubrication, as they can only begin and continue to lubricate after sufficient heat has accumulated by which to keep the grease melting.

As running machinery under increased heat

means expansion of the metal, abrasion of the parts and waste of power, the deficiency of grease lubrication is apparent. The only reliable lubricating with grease is through long-slotted apertures in the box, which allow the grease to lay directly on the parts in motion.

XVI.

SPECIFIC GRAVITY.

Weight is the measure of gravity. The specific gravity of any body is the proportion which the weight of a certain amount of that body bears to the same amount of another body which is taken as standard. The standard adopted for solid and liquid bodies is water, at the temperature of 60° F.

The specific gravity of liquids is most accurately ascertained by means of the specific gravity bottle, which is so constructed as to hold exactly 1000 grains of distilled water. The water being emptied out and the bottle filled with the liquid to be tested, is weighed on a correct scale. The result gives the weight of a volume of the fluid equal in bulk to 1000 grains of water, and this weight, divided by 1000, represents the specific gravity of the liquid.

The specific gravity of oils and fats, which are (121)

all lighter than water, except some of the tar oils, is handily ascertained by means of the Baumé Hydrometer, constructed for the weighing of liquids lighter than water. The oil is put in the hydrometer jar—a tall glass vessel—and the hydrometer placed in it so that it will float upright. The specific gravity of the oil is exactly indicated by the degree on the scale of the hydrometer to which the latter sinks. measure is always taken at 60° F., and for every ten degrees above that temperature, one degree is subtracted from the reading, and for every ten degrees below 60° F., one degree is added to the reading on the hydrometer scale. Fats and oils, solid at ordinary temperature, should be heated until liquid enough to allow the hydrometer to float easily in them, to indicate their specific gravity.

Table of Baumé degrees, the specific gravity they represent and the corresponding weight of the liquids per gallon:

Degree Baumé.	Specific Gravity.	Pounds in One Gallon.
10	1.000	8.33
11	.9929	8.27

	^^
ł	.,.,
1	40

SPECIFIC GRAVITY.

12	.9859	8.21
13	.9790	8.16
14	.9722	8.10
15 (castor oil)	.9655	8.04
16	.95 89	7.99
17	.9523	7.93
18	.9459	7.8 8
19	.9395	7.83
20 .	.9333	7.78
21	.9271	7.72
22	.9210	7.67
23	.9150	7.62
24	.9090	7.57
25 .	9032	7.53
26	.8974	7.48
27	.8917	7.43
28	.8860	7.38
29	.8805	7.34
30	.8750	7.29
31	.8695	7.24
32	.8641	7.20
33	.8588	7.15
34	.8536	7.11
35	.8484	7.07
36	.8433	7.03

124 FRICTION, LUBRICATION, OILS AND FATS.

37	.8 3 83	6.98
38	.8333	6.94
39	.8284	6.90
40	.8235	6.86
41	.8187	6.82
42	.8139	6.78
43	.8092	6.74
44	.8045	6.70
45	.8000	6.66
46	.7954	6.63
47	.7909	6.59
48	.7865	6.55
49	.7821	6.52
50 .	.7777	6.48
51	.7734	6.44
52	.7692	6.41
53	.7650	6.37
54	.7608	6.34
55	.7567	6.30
56	.7526	6.27
57	.7486	$\boldsymbol{6.24}$
58	.7446	6.20
59	.7407	6.17
60	.7368	6.14
61	.7329	6.11

	SPECIFIC GRAVITY.		125
62	.7290	6.07	
63	.7253	6.04	
64	.7216	6.01	
65	.7179	5.98	
66	.7142	5.95	
67	.7106	5.92	
68	.7070	5.89	
6 9	.7035	5.86	
70	.7000	5.83	
75	.6829	5.69	
80	.6666	5.55	
85	.6511	5.42	
90	.6363	5 .30	
95	.6222	5.18	

•

INDEX.

CIDITY, detection of, in NABT, traction of a, 3 mineral oil, 90 Castor oil, adulteration of, Adamantine candles, 23 Adulterations of fatty oils, 85, 86 commercial, pre-Alkali, detection of, in mineral paration of, 79 oil, 90 occurrence and tests, 87, 88 properties Almond oil, occurrence and **2**9, 30 properties of, 35 Castoroleum, preparation of, 79 Alumina, oleate of, detection of, Cetin, test for content of, in in mineral oil, 80 sperm oil, 86 oleate of, preparation of, Clarifying, refining and bleaching oils and fats, 43-49 74-77 Aluminium chloride, use of, for Coal-tar oil, 53 desulphurizing petroleum, 57 uses of, 54 Cocoanut oil and palm oil, 33, 34 Anilin oil, 54 Axle grease, dark, preparation occurrence of. 106 properties of, 34 Coefficient of friction, 2 RAUMÉ degrees, the specific Color test, 88, 89 gravity they represent Colza oil, occurrence and properties of, 32, 33 and the corresponding Copra, 34 weight of the liquids per gallon, table of, 122-125 Corn oil, occurrence and prophydrometer, use of, 122 erties of, 36, 37 Cosmoline, 63 Bearings, overheating of, 7 Belt grease, 83 Cottonseed oil, blown, 72 oil, 83 occurrence Benzine, 58, 59 properties of, 32 refining of, 44, 45 deodorizing of, 65, 66 test for, in lard oil, 89, 90 series, 59 Benzol, 53 Black lubricating oil, 63 thickening of, 71, Blotter test, 97, 98 Cup grease, manufacture of, Blown cottonseed oil, 72 rapeseed oil, 72 105, 106 Bone fat, 21, 22 Cups and lubricators, 114-120 grease, 21, 22 feeding with a wick, 118

Cups for feeding grease, 119 Fats and oils, clarifying, refin regulation of the flow of oil in, 117, 118 Cylinder, causes of the wearing of the, 109, 110 oil, compounding of, 68, 69 preparation of 78, 79 production of, 62, 63 steam refined, 62 oils, pumps for the application of, 114, 115 stock, filtered, 63 Cylinders, injurious action from the use of tallow in, 110, sources of injury in, 112, 113 DARK axle grease, preparation of, 106 Deblooming petroleum oils, 65 Degras, bleaching and deodorizing of, 47 factitious, 28 production and properties of, 27, 28 Deodorizing petrol oil, 65, 66 Desulphurizing petroleum, 56, Distillates, neutral, 60 purification and bleaching of, 59 Distillation of petroleum, 58-63 of wood, 53 Drying oils, 14, 15 ELAIN or red oil, production and properties of, 22, 23 Engine oil, compounding of, 69-71 preparation of, 78 Essential oils, 15, 16 MAT, cleaning and bleaching

of, 48

Fats and oils, 13-17

ing and bleaching of, 43-49 oils of animal and vegetable origin, their characteristics, and how they are obtained, 18-42 Fatty oil, detection of mineral oil in, 88, 89 detection of petroleum oil in, 92-94 oils, 14 adulterations of, 85, 86 compounding petroleum with, 69, 70 decomposition of, 110 detection of small quantities of, in mineral oil, precipitation of, with mineral salts, 73 sweet spirit of the, 41, 42 testing of, by odor and taste, 91, 92 thickening of, 71, 72 Filtered cylinder stock, 63 Fire test, 96, 97 Fish oils and spermaceti, 23-26 Fixed oils, 14 Friction, 1-4 coefficient of, 2 definition of, 1 laws of, 1-3 of motion, 2 of quiescence, 2 rolling, 1, 3 sliding, 1 Frictional heat, 4 absorption of, by metal, 7 creation of, 8

GINGELLY oil, occurrence and properties of, 31, 32 Glycerin, occurrence and properties of, 41, 42

Gravity bottle, use of, 121 Grease, bleaching of, 48, 49 cups for feeding, 119 lubricants, formulas for the manufacture of, 105-108 reliable lubricating with, 120 Greases, 101-108 manufacture of, 103-108 Green oil, 51 ARNESS oil, black, 83 cheap, 83 Headlight oil, 59 Heat, frictional, 3 absorption by of, metal, 7 creation of, 8 Hempseed oil, occurrence and properties of, 33 Horse tallow and neatsfoot oil, 21, 22 production and properties of, 22 Hydrocarbons, 14

TOINT-WATER, 6

KEROSENE oil, deodorizing of, 65, 66 Kidney oil, 41

LARD and lard oil, 18, 19
occurrence and properties of, 18, 19
oil, adulteration of, 85
grades of, 19
preparation and properties of, 19
test for cottonseed oil
in, 89, 90
Laws of friction, 1-3
Leather oils, 81-84
preserving and waterproofing oil, 82, 83
stuffings, 81

Lime paste for rosin grease, preparation of, 104 Linolein, 39 Linoleum, preparation of, 79,80 Linseed oil, adulteration of, 85 grease, preparation of, 106, 107 occurrence and properties of, 38, 39 Lubricants, solid, 101-108 Lubricating, necessity of, 5 oil, black, 63 oils, manufacture of, 67-72 practical tests for, 98-100 simple way of testing, 97, 98 petroleum oils for, 63, 64 test of the comparative efficiency of oils, for, 95 Lubrication, 5-12 laws of, taught by nature, 6 Lubricators and cups, 114-120 trouble caused by, 114

ACHINERY oil, compounding of, 69-71 Marrow tallow, 21, 22 Metal, absorption of frictional heat by, 7 Metallic compounds, soft, lubricating with, 9 Mineral castor, heavy and stringy, preparation of, oil, detection of acidity and alkali in, 90 detection of, in fatty oils, 88, 89 detection of oleate of alumina in, 80 detection of small quantities of fatty oils in, 90 detection of soap in, 90 oils, 16, 50-54 seal oil, 60

Moses pump, 115 Motion, friction of, 2

Mustard seed oil, occurrence Oil, rosin, 40, 41 and properties of, 38 seal, 25, 26 sesame, 31, 32 -Mutton fat, 20 signal, 64 Myrbane oil, 53, 54 sperm, 25 NEATSFOOT oil and horse sunflower, 31 tallow, 20, 21 tallow oil, 21, 22 train, 26 oil, preparation and properties of, 21 turpentine, 41 Neutral distillates, 60 whale, 26 oils, purification and wood tar. 53 bleaching of, 61 Oils and fats, 13-17 Nigerseed oil, occurrence and clarifying, refining properties of, 38 and bleaching of, Nitrobenzol, 53, 54 43-49 Non-drying oils, 14 of animal and vegetable origin, their HIO crude oils, 56, 57 character istics, Oil, almond, 35 and how they are anilin, 54 obtained, 18-42 castor, 29, 30 and oil mixtures, practical chemical process in the methods for testing, 91transformation of, 11 coal tar, 53 bleaching and deodorizing cocoanut, 34 of, 45-47 colza, 32, 33 clarifying of, 43, 44 consumption of, 10 classes of, 13, 14 corn, 36, 37 definition of, 13 cottonseed, 32 drying, 14, 15 fatty, 14 fixed, 14 gingelly, 31, 32 green, 51 hempseed, 33 lubricating, manufacture kidney, 41 of, 67-72 lard, 19 mineral, 16, 50-54 linseed, 38, 39 neutral, 61 mustard seed, 38 non-drying, 14 petroleum, 16, 17, 55-66 myrbane, 53, 54 neatsfoot, 21 refining of, 44 nigerseed, 38 tar, 52-54 olive, 30, 31 test of the comparative effipalm, 33, 34 ciency of, for lubricatparaffine, 51 ing, 95 peanut, 37, 38 testing of, 87-100 thickened, 71, 72 valve-oleum, 73-80 pine, 41 poppyseed, 35, 36 rapeseed, 32, 33 vegetable, 14

volatile or essential, 15, 16

red, 22, 23

Oleate of alumina, detection of, in mineral oil, 80 of alumina, preparation of, 74-77 Olein, separation of, from lard, 18, 19 Olive oil, adulteration of, 85 occurrence and properties of, 30, 31 Oxyhydro-carbons, 13, 14 DAINT oil, factitious, 84 Palm butter, 34 oil and cocoanut oil, 33, occurrence and proper ties of, 33, 34 Paraffine oil, 51 wax, extraction of, 61 Peanut oil, occurrence and properties of, 37, 38 Pennsylvania, petroleum oils of, 56 Petrolatum, 63 Petroleum, compounding of, with fatty oils, 69,70 desulphurizing of, 56, 57 distillation of, 58-63 occurrence of, 55, 56 oil, detection of, in fatty oil, 92-94 oils, 16, 17, 55-66 deblooming of, 65 for lubricating, 63, 64 imparting a viscous consistency to, 68 Pine oil, 41 tar, 41 Plumbago, absorption of frictional heat by, 9 Poppyseed oil, occurrence and properties of, 35, 36 Practical suggestions, 109-113 Pumps for the application of cylinder oils, 114, 115

RAILWAY, traction on a, 3 Rapeseed oil, blown, 72 and properties of, 32, thickening of, 71, 72 Red oil or elain, production and properties of, 22, 23 Residuum oil, filtering of, 63 Rolling friction, 1, 3 Rosin grease, preparation of, 104, 105 occurrence and properties of, 40 oil and turpentine, 40, 41 occurrence and properties of, 40, 41 Rumford, Count, experiments by, 7 SCOTCH shale, distillation of, 50, 51 50, 51 Seal oil, occurrence and properties of, 25, 26 Sesame oil, occurrence and properties of, 31, 32 Shale oil, grades of, 52 Sight-feed cups, 115, 116 Signal oil, 64 Sliding friction, 1 Soap, detection of, in mineral oil, 90 Solid lubricants, 101-108 Specific gravity, 121-125 Spermaceti and fish oils, 23-26 occurrence and properties of, 23, 24 Sperm oil, adulteration of, 85 occurrence and properties of, 25 test for content of cetin in, 86 Spindle oil, 60 Standard white or export oil, 59 UIESCENCE, friction of, 2 Steam refined cylinder oil, 62

Straight run, 60
Sunflower oil, occurrence and properties of, 31
Sweet spirit of the fatty oils, 41, 42

MABLE of Baumé degrees, the specific gravity they represent, and the corresponding weight of the liquids per gallon, 122-125 Tallow and tallow oil, 19-21 cleaning and bleaching of, injurious action from the use of, in cylinders, 110, oil, production and properties of, 20, 21 properties of, 20 Tar oils, 52-54 Test, alkali, 87, 88 Testing lubricating oils, simple way of, 97, 98 oils, 87-100 and oil mixtures, practical methods for, 91-

Tests, practical, for lubricating oils, 98-100
Thickened oils, 71, 72
Traction of a cart, 3
on a railway, 3
Train and whale oils, 26

Train oil, bleaching and deodorizing of, 48 Turpentine, oil of, 41

VALVE-OLEUM castoroleum, preparation of,
79
Oleum, castor oil, preparation of, 79
cylinder oil, preparation of, 78, 79
engine oil, preparation of, 78
leather preserving and
waterproofing oil,
82, 83
linoleum, preparation
of, 79, 80
oils, 73-80
foundation of, 73

Vaseline, 63
Vegetable oils, 14
bleaching of, 43
Viscosity, test for, 95, 96
Volatile oils, 15, 16

WATER white oil, 59
West Virginia oil, 63
Whale and train oils, 26
Wood, distillation of, 53
tar oil, 53
Wool fat, production and properties of, 27

• • •

CATALOGUE

OF

Practical and Scientific Books

PUBLISHED BY

HENRY CAREY BAIRD & CO.

INDUSTRIAL PUBLISHERS, BOOKSELLERS AND IMPORTERS.

810 Walnut Street, Philadelphia.

- Any of the Books comprised in this Catalogue will be sent by mail, free depostage, to any address in the world, at the publication prices.
- ♣ Descriptive Catalogue, 90 pages, 8vo., will be sent free and free of postage, to any one in any part of the world, who will furnish his address.
- Where not otherwise stated, all of the Books in this Catalogue are bound in muslin.

AMATEUR MECHANICS' WORKSHOP:

ANDES.—Animal Fats and Oils:

Their Practical Production, Purification and Uses; their Properties, Falsification and Examination. 62 illustrations. 8vo.

ANDES .- Vegetable Fats and Oils:

Their Practical Preparation, Purification and Employment; their Properties, Adulteration and Examination. 94 illustrations. 8vo.

ARLOT.—A Complete Guide for Coach Painters:

Translated from the French of M. ARLOT, Coach Painter, for eleven years Foreman of Painting to M. Eherler, Coach Maker, Paris. By A. A. FESQUET, Chemist and Engineer. To which added an Appendix, containing Information respecting the Materials and the Practice of Coach and Car Painting and Varnishing in the United States and Great Britain 12mo.

(1)

ARMENGAUD, AMOROUX, AND JOHNSON.—The Practical Draughtsman's Book of Industrial Design, and Machinist's and Engineer's Drawing Companion;

Forming a Complete Course of Mechanical Engineering and Architectural Drawing. From the French of M. Armengaud the elder, Prof. of Design in the Conservatoire of Arts and Industry, Paris, and MM. Armengaud the younger, and Amoroux, Civil Engineers. Rewritten and arranged with additional matter and plates, selections from and examples of the most useful and generally employed mechanism of the day. By WILLIAM JOHNSON, Assoc. Inst. C. E. Illustrated by fifty folio steel plates, and fifty wood-cuts. A new edition, 4to, cloth.

ARMSTRONG.—The Construction and Management of Steam Boilers:

By R. Armstrong, C. E. With an Appendix by ROBERT MALLET, C. E., F. R. S. Seventh Edition. Illustrated. 1 vol. 12mo. .60

ARROWSMITH.—The Paper-Hanger's Companion:

Comprising Tools, Pastes, Preparatory Work; Selection and Hanging of Wall-Papers; Distemper Painting and Cornice-Tinting; Stencil Work; Replacing Sash-Cord and Broken Window Panes; and Useful Wrinkles and Receipts, By James Arrowsmith. A New, Thoroughly Revised, and Much Enlarged Edition. Illustrated by 25 engravings, 162 pages. (1905)

ASHTON.—The Theory and Practice of the Art of Designing Fancy Cotton and Woollen Cloths from Sample:

Giving full instructions for reducing drafts, as well as the methods of spooling and making out harness for cross drafts and finding any required reed; with calculations and tables of yarn. By FREDERIC T. ASHTON, Designer, West Pittsfield, Mass. With fifty-two illustrations One vol. folio

ASKINSON.—Perfumes and their Preparation:

A Comprehensive Treatise on Perfumery, containing Complete Directions for Making Handkerchief Perfumes, Smelling-Salts, Sachets, Fumigating Pastils; Preparations for the Care of the Skin, the Mouth, the Hair; Cosmetics, Hair Dyes, and other Toilet Articles. By G.W. ASKINSON. Translated from the German by ISIDOR FURST. Revised by CHARLES RICE. 32 Illustrations. 8vo. \$3.00

BAIRD.—The American Cotton Spinner, and Manager's and Carder's Guide:

A Practical Treatise on Cotton Spinning; giving the Dimensions and Speed of Machinery, Draught and Twist Calculations, etc.; with notices of recent Improvements: together with Rules and Examples or making changes in the sizes and numbers of Roving and Yarn. Compiled from the papers of the late ROBERT H. BAIRD. 12mo.

BAKER.-Long-Span Railway Bridges:

Comprising Investigations of the Comparative Theoretical and Practical Advantages of the various Adopted or Proposed Type Systems of Construction; with numerous Formulæ and Tables. By B. BAKER. 12mo. 00.1

BRANNT.-A Practical Treatise on Distillation and Rectification of Alcohol:

Comprising Raw Materials; Production of Malt, Preparation of Mashes and of Yeast: Fermentation; Distillation and Rectification and Purification of Alcohol; Preparation of Alcoholic Liquors, Liqueurs, Cordials, Bitters, Fruit Essences, Vinegar, etc.; Examination of Materials for the Preparation of Malt as well as of the Malt itself; Examination of Mashes before and after Fermentation; Alcoholometry, with Numerous Comprehensive Tables; and an Appendix on the Manufacture of Compressed Yeast and the Examination of Alcohol and Alcoholic Liquors for Fusel Oil and other Impurities, By WILLIAM T. BRANNT, Editor of "The Techno-Chemical Receipt Book." Second Edition. Entirely Rewritten. Illustrated by 105 engravings. 460 pages, 8vo. (Dec., 1903). \$4.00

BARR.—A Practical Treatise on the Combustion of Coal: Including descriptions of various mechanical devices for the Economic Generation of Heat by the Combustion of Fuel, whether solid, liquid or gaseous, 8vo. .

BARR.—A Practical Treatise on High Pressure Steam Boilers: Including Results of Recent Experimental Tests of Boiler Materials, together with a description of Approved Safety Apparatus, Steam Pumps, Injectors and Economizers in actual use. By Wm. M. BARR. 204 Illustrations. 8vo. .

BAUERMAN.-A Treatise on the Metallurgy of Iron:

Containing Outlines of the History of Iron Manufacture, Methods of Assay, and Analysis of Iron Ores, Processes of Manufacture of Iron and Steel, etc., etc. By H. BAUERMAN, F. G. S., Associate of the Royal School of Mines. Fifth Edition, Revised and Enlarged. Illustrated with numerous Wood Engravings from Drawings by J. B. JORDAN. 12mo,

BRANNT.—The Metallic Alloys: A Practical Guide For the Manufacture of all kinds of Alloys, Amalgams, and Solders, used by Metal-Workers: together with their Chemical and Physical Properties and their Application in the Arts and the Industries; with an Appendix on the Coloring of Alloys and the Recovery of Waste Metals. By WILLIAM T. BRANNT. 34 Engravings. A New, Revised, and Enlarged Edition. 554 pages. 8vo. \$4.50

BEANS.-A Treatise on Railway Curves and Location of Railroads:

By E. W. BEANS, C. E. Illustrated. 12mo. Tucks. . \$1.50 **BELL.—Carpentry Made Easy:**

Or, The Science and Art of Framing on a New and Improved System. With Specific Instructions for Building Balloon Frames, Barn Frames, Mill Frames, Warehouses, Church Spires, etc. Comprising also a System of Bridge Building, with Bills, Estimates of Cost, and valuable Tables. Illustrated by forty-four plates, comprising nearly 200 figures. By WILLIAM E. BELL, Architect and Practical Builder. 8vo.

BEMROSE.—Fret-Cutting and Perforated Carving:
With fifty-three practical illustrations. By W. BEMROSE, JR. I voluments

BEMROSE.—Manual of Buhl-work and Marquetry:

BEMROSE.—Manual of Wood Carving:

With Practical Illustrations for Learners of the Art, and Original and Selected Designs. By WILLIAM BEMROSE, JR. With an Introduction by LLEWELLYN JEWITT, F. S. A., etc. With 128 illustrations, 4to. \$2.50

BERSCH.—Cellulose, Cellulose Products, and Rubber Substitutes:

Comprising the Freparation of Cellulose, Parchment-Cellulose, Methods of Obtaining Sugar, Alcohol and Oxalic Acid from Wood-Cellulose; Production of Nitro-Cellulose and Cellulose Esters; Manufacture of Artificial Silk, Viscose, Celluloid, Rubber Substitutes, Oil-Rubber, and Faktis. By Dr. JOSEPH BERSCH. Translated by WILLIAM T. BRANNT. 41 illustrations. (1904.) \$3.00 BILLINGS.—Tobacco:

BIRD.—The American Practical Dyers' Companion:
Comprising a Description of the Principal Dye-Stuffs and Chemicals used in Dyeing, their Natures and Uses; Mordants and How Made; with the best American, English, French and German processes for Bleaching and Dyeing Silk, Wool, Cotton, Linen, Flannel, Felt, Dress Goods, Mixed and Hosiery Yarns, Feathers, Grass, Felt, Fur, Wool, and Straw Hats, Jute Yarn, Vegetable Ivory, Mats, Skins, Furs, Leather, etc., etc. By Wood Aniline, and other Processes, together with Remarks on Finishing Agents, and instructions in the Finishing of Fabrics, Substitutes for Indigo, Water-Proofing of Materials, Tests and Purification of Water, Manufacture of Aniline and other New Dye Wares, Harmonizing Colors, etc., etc.; embracing in all over 800 Receipts for Colors and Shades, accompanied by 170 Dyed Samples of Raw Materials and Fabrics. By F. J. BIRD, Practical Dyer, Author of "The Dyers' Hand-Book." 8vo. \$7.50

BLINN.—A Practical Workshop Companion for Tin, Sheet-Iron, and Copper-plate Workers;

Containing Rules for describing various kinds of Patterns used by Tin, Sheet-Iron and Copper-plate Workers; Practical Geometry; Mensuration of Surfaces and Solids; Tables of the Weights of Metals, Lead-pipe, etc.; Tables of Areas and Circumference of Circles; Japan, Varnishes, Lackers, Cements, Compositions, etc. By Leroy J. Blinn, Master Mechanic. With One Hundred and Seventy Illustrations. 12mo. \$2.50

BOOTH.-Marble Worker's Manual:

Containing Practical Information respecting Marbles in general, their Cutting, Working and Polishing; Veneering of Marble; Mosaics; Composition and Use of Artificial Marble, Stuccos, Cements, Receipts, Secrets, etc., etc. Translated from the French by M. L. BOOTH. With an Appendix concerning American Marbles. 12mo., cloth \$1.50

BRANNT.—A Practical Treatise on Animal and Vegetable Fats and Oils:

Comprising both Fixed and Volatile Oils, their Physical and Chemical Properties and Uses, the Manner of Extracting and Refining them, and Practical Rules for Testing them; as well as the Manufacture of Artificial Butter and Lubricants, etc., with lists of American Patents relating to the Extraction, Rendering, Refining, Decomposing, and Bleaching of Fats and Oils. By WILLIAM T. BRANNT, Editor of the "Techno-Chemical Receipt Book." Second Edition, Revised and in a great part Rewritten. Illustrated by 302 Engravings. In Two Volumes. 1304 pp. 8vo.

BRANNT.—A Practical Treatise on the Manufacture of Soap and Candles:

Based upon the most Recent Experiences in the Practice and Science; comprising the Chemistry, Raw Materials, Machinery, and Utensils and Various Processes of Manufacture, including a great variety of formulas. Edited chiefly from the German of Dr. C. Deite, A. Engelhardt, Dr. C. Schaedler and others; with additions and lists of American Patents relating to these subjects. By WM. T. Brannt. Illustrated by 163 engravings. 677 pages. 8vo. . . . \$10.00

BRANNT.-India Rubber, Gutta-Percha and Balata:

Occurrence, Geographical Distribution, and Cultivation, Obtaining and Preparing the Raw Materials, Modes of Working and Utilizing them, Including Washing, Maceration, Mixing, Vulcanizing, Rubber and Gutta-Percha Compounds, Utilization of Waste, etc. By WILLIAM T. BRANNT. Illustrated. 12mo. (1900.) . . \$3.00

BRANNT-WAHL.-The Techno-Chemical Receipt Book: Containing several thousand Receipts covering the latest, most important, and most useful discoveries in Chemical Technology, and their Practical Application in the Arts and the Industries. Edited chiefly from the German of Drs. Winckler, Elsner, Heintze, Mierzinski, Jacobsen, Koller and Heinzerling, with additions by WM. T. Brannt and Wm. H. Wahl, Ph. D. Illustrated by 78 engravings. 12mo. 495 pages. BROWN.—Five Hundred and Seven Mechanical Movements: Embracing all those which are most important in Dynamics, Hydraulics, Hydrostatics, Pneumatics, Steam Engines, Mill and other Gearing, Presses, Horology, and Miscellaneous Machinery; and including many movements never before published, and several of which have only recently come into use. By HENRY T. BROWN. **BUCKMASTER.—The Elements of Mechanical Physics:** By J. C. BUCKMASTER. Illustrated with numerous engravings. **BULLOCK.—The American Cottage Builder:** A Series of Designs, Plans and Specifications, from \$200 to \$20,000, for Homes for the People; together with Warming, Ventilation, Drainage, Painting and Landscape Gardening. By JOHN BULLOCK, Architect and Editor of "The Rudiments of Architecture and Building," etc., etc. Illustrated by 75 engravings. 8vo. \$2.
BULLOCK.—The Rudiments of Architecture and Building: For the use of Architects, Builders, Draughtsmen, Machinists, Engineers and Mechanics. Edited by JOHN BULLOCK, author of "The American Cottage Builder." Illustrated by 250 Engravings. 8vo. \$2.50 BURGH.—Practical Rules for the Proportions of Modern Engines and Boilers for Land and Marine Purposes. By N. P. BURGH, Engineer. 12mo. BYLES.—Sophisms of Free Trade and Popular Political Economy Examined. By a BARRISTER (SIR JOHN BARNARD BYLES, Judge of Common Pleas). From the Ninth English Edition, as published by the Manchester Reciprocity Association. 12mo. \$1.25 BOWMAN.—The Structure of the Wool Fibre in its Relation to the Use of Wool for Technical Purposes: Being the substance, with additions, of Five Lectures, delivered at the request of the Council, to the members of the Bradford Technical College, and the Society of Dyers and Colorists. By F. H. Bow-MAN, D. Sc., F. R. S. E., F. L. S. Illustrated by 32 engravings. \$7.50 BYRNE.-Hand-Book for the Artisan, Mechanic, and Engi-

Comprising the Grinding and Sharpening of Cutting Tools, Abrasive Processes, Lapidary Work, Gem and Glass Engraving, Varnishing and Lackering, Apparatus, Materials and Processes for Grinding and

Polishing, etc. By OLIVER BYRNE. Illustrated by 185 wood engravings. 8vo. \$5.00 8YRNE.—Pocket-Book for Railroad and Civil Engineers: Containing New, Exact and Concise Methods for Laying out Railroad Courses Stricks. From Application of Consideration of the Stricks.

BYRNE.—The Practical Model Calculator:
For the Engineer, Mechanic, Manufacturer of Engine Work, Nava.
Architect, Miner and Millwright. By OLIVER BYRNE. 8vo., nearly
600 pages (Scarce.)

CARINET MAKER'S ALBUM OF FURNITURE:

Comprising a Collection of Designs for various Styles of Furniture.

Illustrated by Forty-eight Large and Beautifully Engraved Plates.

Oblong, 8vo. \$1.50

CALLINGHAM.—Sign Writing and Glass Embossing:
A Complete Practical Illustrated Manual of the Art. By James
CALLINGHAM. To which are added Numerous Alphabets and the
Art of Letter Painting Made Easy. By James C. Badenoch. 258
pages. 12mo. \$1.50

CAMPIN.—A Practical Treatise on Mechanical Engineering:
Comprising Metallurgy, Moulding, Casting, Forging, Tools, Workshop Machinery, Mechanical Manipulation, Manufacture of Steam-Engines, etc. With an Appendix on the Analysis of Iron and Iron Ores. By Francis Campin, C. E. To which are added, Observations on the Construction of Steam Boilers, and Remarks upon Furnaces used for Smoke Prevention; with a Chapter on Explosions. By R. Armstrong, C. E., and John Bourne. (Scarce.)

CAREY.—A Memoir of Henry C. Carey.
By Dr. Wm. Elder. With a portrait. 8vo., cloth 7
CAREY.—The Works of Henry C. Carey:
Harmony of Interests: Agricultural, Manufacturing and Commer
cial. 8vo
Manual of Social Science. Condensed from Carey's "Principle
of Social Science." By KATE MCKEAN, I vol. 12mo \$2.00
Miscellaneous Works. With a Portrait. 2 vols. 8vo. \$10.00
Past, Present and Future. 8vo
Principles of Social Science. 3 volumes, 8vo \$7.50
The Slave-Trade, Domestic and Foreign; Why it Exists, and
How it may be Extinguished (1853). 8vo \$2.00
The Unity of Law: As Exhibited in the Relations of Physical
Social, Mental and Moral Science (1872). 8vo \$2.50
CLARK.—Tramways, their Construction and Working:
Embracing a Comprehensive History of the System. With an ex
haustive analysis of the various modes of traction, including horse
power, steam, heated water and compressed air; a description of the
varieties of Rolling stock, and ample details of cost and working ex
penses. By D. KINNEAR CLARK. Illustrated by over 200 wood
engravings, and thirteen folding plates. I vol. 8vo \$5.00
COLBURN.—The Locomotive Engine:
Including a Description of its Structure, Rules for Estimating it
Capabilities, and Practical Observations on its Construction and Man
agement. By ZERAH COLBURN. Illustrated. 12mo \$1.00
COLLENS.—The Eden of Labor; or, the Christian Utopia.
By T. WHARTON COLLENS, author of "Humanics," "The History
of Charity," etc. 12mo. Paper cover, \$1.00; Cloth . \$1.2
COOLEY.—A Complete Practical Treatise on Perfumery:
Being a Hand-book of Perfumes, Cosmetics and other Toilet Articles
With a Comprehensive Collection of Formulæ. By ARNOLD
COOLEY. 12mo
COOPER.—A Treatise on the use of Belting for the Trans.
mission of Power.
With numerous illustrations of approved and actual methods of ar
ranging Main Driving and Quarter Twist Belts, and of Belt Pasten
ings. Examples and Rules in great number for exhibiting and cal
culating the size and driving power of Belts. Plain, Particular and
Practical Directions for the Treatment, Care and Management of
Belts. Descriptions of many varieties of Beltings, together with
chapters on the Transmission of Power by Ropes; by Iron and
Wood Frictional Gearing; on the Strength of Belting Leather; and
on the Experimental Investigations of Morin, Briggs, and others. B
JOHN H. COOPER, M. E. 8vo
CRAIK.—The Practical American Millwright and Miller.
By DAVID CRAIK, Millwright. Illustrated by numerous wood en
gravings and two folding plates 800 (Source)

ODOGO WE COME VI CO
CROSS.—The Cotton Yarn Spinner: Showing how the Preparation should be arranged for Different Counts of Yarns by a System more uniform than has hitherto been practiced; by having a Standard Schedule from which we make all our Changes. By RICHARD CROSS. 122 pp. 12mo
CRISTIANI.—A Technical Treatise on Soap and Candles: With a Glance at the Industry of Fats and Oils. By R. S. CRISTIANI, Chemist. Author of "Perfumery and Kindred Arts." Illustrated by 176 engravings. 581 pages, 8vo.
COURTNEY.—The Boiler Maker's Assistant in Drawing, Templating, and Calculating Boiler Work and Tank Work, etc. Revised by D. K. CLARK. 102 ills. Fifth edition 80
COURTNEY.—The Boiler Maker's Ready Reckoner: With Examples of Practical Geometry and Templating. Revised by D. K. CLARK, C. E. 37 illustrations. Fifth edition. \$1.60
DAVIDSON.—A Practical Manual of House Painting, Graining, Marbling, and Sign-Writing: Containing full information on the processes of House Painting ir Oil and Distemper, the Formation of Letters and Practice of Sign. Writing, the Principles of Decorative Art, a Course of Elementary Drawing for House Painters, Writers, etc., and a Collection of Useful Receipts. With nine colored illustrations of Woods and Marbles, and numerous wood engravings. By Ellis A. Davidson. 12mo. \$2.00
DAVIES.—A Treatise on Earthy and Other Minerals and Mining: By D. C. DAVIES, F. G. S., Mining Engineer, etc. Illustrated by 76 Engravings. 12mo
DAVIES.—A Treatise on Metalliferous Minerals and Mining: By D. C. DAVIES, F. G. S, Mining Engineer, Examiner of Mines, Quarries and Collieries. Illustrated by 148 engravings of Geological Formations, Mining Operations and Machinery, drawn from the practice of all parts of the world. Fifth Edition, thoroughly Revised and much Enlarged by his son, E. Henry Davies. 12mo., 524 pages
DAVIES.—A Treatise on Slate and Slate Quarrying: Scientific, Practical and Commercial. By D. C. DAVIES, F. G. S., Mining Engineer, etc. With numerous illustrations and folding plates. 22mo
DAVIS.—A Practical Treatise on the Manufacture of Brick, Tiles and Terra-Cotta: Including Stiff Clay, Dry Clay, Hand Made, Pressed or Front, and
Roadway Paving Brick, Enamelled Brick, with Glazes and Colors, Fire Brick and Blocks, Silica Brick, Carbon Brick, Glass Pots, Re-

torts, Architectural Terra-Cotta, Sewer Pipe, Drain Tile, Glazed and Unglazed Roofing Tile, Art Tile, Mosaics, and Imitation of Intarsia or Inlaid Surfaces. Comprising every product of Clay employed in Architecture, Engineering, and the Blast Furnace. With a Detailed Description of the Different Clays employed, the Most Modern Machinery, Tools, and Kilns used, and the Processes for Handling, Disintegrating, Tempering, and Moulding the Clay into Shape, Drying, Setting, and Burning. By Charles Thomas Davis. Third Edition. Revised and in great part rewritten. Illustrated by 261 engravings. 662 pages

DAVIS.—A Treatise on Steam-Boiler Incrustation and Methods for Preventing Corrosion and the Formation of Scale: By CHARLES T. DAVIS. Illustrated by 65 engravings. 8vo.

DAVIS .- The Manufacture of Paper:

Being a Description of the various Processes for the Fabrication, Coloring and Finishing of every kind of Paper, Including the Different Raw Materials and the Methods for Determining their Values, the Tools, Machines and Practical Details connected with an intelligent and a profitable prosecution of the art, with special reference to the best American Practice. To which are added a History of Paper, complete Lists of Paper-Making Materials, List of American Machines, Tools and Processes used in treating the Raw Materials and in Making, Coloring and Finishing Paper. By CHARLES T. DAVIS. Illustrated by 156 engravings. 608 pages, 8vo. \$6.00

DAVIS.—The Manufacture of Leather:

Being a Description of all the Processes for the Tanning and Tawing with Bark, Extracts, Chrome and all Modern Tannages in General Use, and the Currying, Finishing and Dyeing of Every Kind of Leather; Including the Various Raw Materlals, the Tools, Machines, and all Details of Importance Connected with an Intelligent and Profitable Prosecution of the Art, with Special Reference to the Best American Practice. To which are added Lists of American Patents (1884–1897) for Materials, Processes, Tools and Machines for Tanning, Currying, etc. By CHARLES THOMAS DAVIS. Second Edition, Revised, and in great part Rewritten. Illustrated by 147 engravings and 14 Samples of Quebracho Tanned and Aniline Dyed Leathers. 8vo, cloth, 712 pages. Price

DAWIDOWSKY—BRANNT.—A Practical Treatise on the Raw Materials and Fabrication of Glue, Gelatine, Gelatine Veneers and Foils, Isinglass, Cements, Pastes, Mucilages,

DE GRAFF.—The Geometrical Stair-Builders' Guide:

Being a Plain Practical System of Hand-Railing, embracing all its necessary Details, and Geometrically Illustrated by twenty-two Steel Engravings; together with the use of the most approved principle of Practical Geometry

By SIMON DE GRAFF, Architect (Scarce.)

DE KONINCK—DIETZ.—A Practical Manual of Chemica Analysis and Assaying: As applied to the Manufacture of Iron from its Ores, and to Cast Iron, Wrought Iron, and Steel, as found in Commerce. By L. L. Da KONINCK, Dr. Sc., and E. DIETZ, Engineer. Edited with Notes, by ROBERT MALLET, F. R. S., F. S. G., M. I. C. E., etc. American Edition, Edited with Notes and an Appendix on Iron Ores, by A. A. FESQUET, Chemist and Engineer. 12mo. UNCAN.—Practical Surveyor's Guide: Containing the necessary information to make any person of common capacity, a finished land surveyor without the aid of a teacher By Andrew Duncan. Revised. 72 engravings, 214 pp. 12mo. \$1.50 DUPLAIS.—A Treatise on the Manufacture and Distillation of Alcoholic Liquors: Comprising Accurate and Complete Details in Regard to Alcohol from Wine, Molasses, Beets, Grain, Rice, Potatoes, Sorghum, Aspho del, Fiuits, etc.; with the Distillation and Rectification of Brandy Whiskey, Rum, Gin, Swiss Absinthe, etc., the Preparation of Aromatic Waters, Volatile Oils or Essences, Sugars, Syrups, Aromatic Tinctures, Liqueurs, Cordial Wines, Effervescing Wines, etc., the Ageing of Brandy and the improvement of Spirits, with Copions Directions and Tables for Testing and Reducing Spirituous Liquors, etc. etc. Translated and Edited from the French of MM. DUPLAIS. By M. McKennie, M. D. Illustrated. 743 pp. 8vo. DYER AND COLOR-MAKER'S COMPANION: Containing upwards of two hundred Receipts for making Colors, on the most approved principles, for all the various styles and fabrics now in evistence; with the Scouring Process, and plain Directions for \$1 00 Preparing, Washing-off, and Finishing the Goods. 12mo. EIDHERR.—The Techno-Chemical Guide to Distillation: A Hand-Book for the Manufacture of Alcohol and Alcoholic Liquors, including the Preparation of Malt and Compressed Yeast. Edited from the German of Ed. Eidherr. EDWARDS.-A Catechism of the Marine Steam-Engine. For the use of Engineers, Firemen, and Mechanics. A Practical Work for Practical Men. By EMORY EDWARDS, Mechanical Engineer. Illustrated by sixty-three Engravings, including examples of the most modern Engines. Third edition, thoroughly revised, with much additional matter. 12 mo. 414 pages EDWARDS.-Modern American Locomotive Engines, Their Design, Construction and Management. By EMORY EDWARDS. Illustrated 12mo. EDWARDS.—The American Steam Engineer: Theoretical and Practical, with examples of the latest and most approved American practice in the design and construction of Steam Engines and Boilers. For the use of engineers, machinists, boilermakers, and engineering students. By EMORY EDWARDS. Fully

419 pages. 12mo.

ilustrated,

EDWARDS.—Modern American Marine Engines, Boilers, and Screw Propellers,
Their Design and Construction. Showing the Present Practice of the most Eminent Engineers and Marine Engine Builders in the
United States. Illustrated by 30 large and elaborate plates. 4to. \$5.00
I DWARDS.—The Practical Steam Engineer's Guide
In the Design, Construction, and Management of American Stationary, Portable, and Steam Fire-Engines, Steam Pumps, Boilers. Injectors,
Governors, Indicators, Pistons and Rings, Safety Valves and Steam
Gauges. For the use of Engineers, Firemen, and Steam Users. By
EMORY EDWARDS. Illustrated by 119 engravings. A20 pages.
12mo
EISSLER.—The Metallurgy of Silver:
A Practical Treatise on the Amalgamation, Roasting, and Lixiviation of Silver Ores, including the Assaying, Melling, and Refining of
Silver Bullion. By M. EISSLER. 124 Illustrations. 336 pp.
12mo
ELDER.—Conversations on the Principal Subjects of Political
Economy. By Dr. William Elder. 8vo \$2.50
ELDER.—Questions of the Day,
Economic and Social. By Dr. WILLIAM ELDER. 8vo \$3.00
ERNI AND BROWN.—Mineralogy Simplified.
Easy Methods of Identifying Minerals, including Ores, by Means of
the Blow-pipe, by Flame Reactions, by Humid Chemical Analysis,
and by Physical Tests. By HENRI ERNI, A. M., M. D. Third Edition, revised, re-arranged and with the addition of entirely new matter,
including Tables for the Determination of Minerals by Chemical and
Pyrognostic Characters, and by Physical Characters. By Amos P.
Brown, E. M., Ph. D. 350 pp., illustrated by 96 engravings, pocket-
book form, full flexible morocco, gilt edges \$2.50
FAIRBAIRN The Principles of Mechanism and Machinery
of Transmission:
Comprising the Principles of Mechanism, Wheels, and Pulleys,
Strength and Proportion of Shafts, Coupling of Shafts, and Engaging and Disengaging Gear. By SIR WILLIAM FAIRBAIRN, Bart.
C. E. Beautifully illustrated by over 150 wood-cuts. In one
volume, 12mo
FLEMING.—Narrow Gauge Railways in America:
A Sketch of their Rise, Progress, and Success. Valuable Statistics
as to Grades, Curves, Weight of Rail, Locomotives, Cars, etc. By
HOWARD FLEMING. Illustrated, 8vo \$1.00
FORSYTH.—Book of Designs for Headstones, Mural, and
other Monuments:
Containing 78 Designs. By JAMES FORSYTH, With an Introduction by CHARLES BOUTELL, M. A. 4to., cloth \$3.50
by Charles Boutell, M. A. 4to., cloth \$3.50
FRIEDBERG. Utilization of Bones by Chemical Means;
especially the Modes of Obtaining Fat, Glue, Manures, Phosphorus and Phosphates.
Illustrated. 8vo. (In preparation.)

GARDNER.—Everybody's Paint Book:

GEE.—The Jeweller's Assistant in the Art of Working in Gold:

A Practical Treatise for Masters and Workmen. 12mo. . 35 00

GEE.—The Goldsmith's Handbook:

Containing full instructions for the Alloying and Working of Gold, including the Art of Alloying, Melting, Reducing, Coloring, Collecting, and Refining; the Processes of Manipulation, Recovery of Waste; Chemical and Physical Properties of Gold; with a New System of Mixing its Alloys; Solders, Enamels, and other Useful Rules and Recipes. By George E. Gee. 12mo. \$1.25

GEE.—The Silversmith's Handbook:

Containing full instructions for the Alloying and Working of Silver, including the different modes of Refining and Melting the Metal; its Solders; the Preparation of Imitation Alloys; Methods of Manipulation; Prevention of Waste; Instructions for Improving and Finishing the Surface of the Work; together with other Useful Information and Memoranda. By George E. Gee. Illustrated. 12mo. \$1.25

GOTHIC ALBUM FOR CABINET-MAKERS:

Designs for Gothic Furniture. Twenty-three plates. Oblong \$1.50

3RANT.—A Handbook on the Teeth of Gears:

Their Curves, Properties, and Practical Construction. By GEORGE B. GRANT. Illustrated. Third Edition, enlarged. 8vo. \$100

GREENWOOD.—Steel and Iron:

Comprising the Practice and Theory of the Several Methods Pursued in their Manufacture, and of their Treatment in the Rolling-Mills, the Forge, and the Foundry. By WILLIAM HENRY GREEN-WOOD. F. C. S. With 97 Diagrams, 536 pages. 12mo. \$1.75

GREGORY.—Mathematics for Practical Men:
Adapted to the Pursuits of Surveyors, Architects, Mechanics, an
Civil Engineers. By OLINTHUS GREGORY. 8vo., plates \$3.0
GRISWOLD.—Railroad Engineer's Pocket Companion for th Field:
Gomprising Rules for Calculating Deflection Distances and Angle Tangential Distances and Angles, and all Necessary Tables for Engineers; also the Art of Levelling from Preliminary Survey to the Construction of Railroads, intended Expressly for the Young Engineer, together with Numerous Valuable Rules and Examples. H. W. GRISWOLD. 12mo., tucks
Mechanic:
Containing Accurate Tables of Logs Reduced to Inch Board Measure, Plank, Scantling and Timber Measure; Wages and Rent, b Week or Month; Capacity of Granaries, Bins and Cisterns; Lan Measure, Interest Tables, with Directions for Finding the Interest o any sum at 4, 5, 6, 7 and 8 per cent., and many other Useful Tables 22 mo., boards. 186 pages
HASERICK.—The Secrets of the Art of Dyeing Wool, Cotton
and Linen,
Including Bleaching and Coloring Wool and Cotton Hosiery an Random Yarns. A Treatise based on Economy and Practice. E. C. HASERICK. Illustrated by 323 Dyed Patterns of the Yarn or Fabrics. 8vo.
HATS AND FELTING:
A Practical Treatise on their Manufacture. By a Practical Hatte Illustrated by Drawings of Machinery, etc. 8vo \$1.00
HERMANN.—Painting on Glass and Porcelain, and Ename Painting:
A Complete Introduction to the Preparation of all the Colors and
Fluxes Used for Painting on Glass, Porcelain, Enamel, Faience and
Stoneware, the Color Pastes and Colored Glasses, together with Minute Description of the Firing of Colors and Enamels, on the
Basis of Personal Practical Experience of the Art up to Date.
illustrations. Second edition.
HAUPT.—Street Railway Motors:
With Descriptions and Cost of Plants and Operation of the Variou
Systems now in Use. 12m?
Systems now in Ose. #2007.

HAUPT.—A Manual of Engineering Specifications and Contracts. By Lewis M. Haupt, C. E. Illustrated with numerous maps. 328pp. 8vo
328pp. 8vo
328pp. 8vo
By Lewis M. Haupt, A. M., C. E. Illustrated with numerous plates, maps and engravings. 247 pp. 8vo
By Lewis M. Haupt, A. M., C. E. Illustrated with numerous plates, maps and engravings. 247 pp. 8vo
plates, maps and engravings. 247 pp. 8vo. \$3.00 HUGHES.—American Miller and Millwright's Assistant: By WILLIAM CARTER HUGHES. 12mo. \$1.50 HULME.—Worked Examination Questions in Plane Geometrical Drawing: For the Use of Candidates for the Royal Military Academy, Woolwich; the Royal Military College, Sandhurst; the Indian Civil Engineering College, Cooper's Hill; Indian Public Works and Telegraph Departments; Royal Marine Light Infantry; the Oxford and Cambridge Local Examinations, etc. By F. Edward Hulme, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto EXVIS.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1.00 KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
By WILLIAM CARTER HUGHES. 12mo. \$1.50 HULME.—Worked Examination Questions in Plane Geometrical Drawing: For the Use of Candidates for the Royal Military Academy, Woolwich; the Royal Military College, Sandhurst; the Indian Civil Engineering College, Cooper's Hill; Indian Public Works and Telegraph Departments; Royal Marine Light Infantry; the Oxford and Cambridge Local Examinations, etc. By F. Edward Hulme, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto Exvis.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 00 KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
For the Use of Candidates for the Royal Military Academy, Woolwich; the Royal Military College, Sandhurst; the Indian Civil Engineering College, Cooper's Hill; Indian Public Works and Telegraph Departments; Royal Marine Light Infantry; the Oxford and Cambridge Local Examinations, etc. By F. Edward Hulme, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto
For the Use of Candidates for the Royal Military Academy, Woolwich; the Royal Military College, Sandhurst; the Indian Civil Engineering College, Cooper's Hill; Indian Public Works and Telegraph Departments; Royal Marine Light Infantry; the Oxford and Cambridge Local Examinations, etc. By F. Edward Hulme, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto
For the Use of Candidates for the Royal Military Academy, Woolwich; the Royal Military College, Sandhurst; the Indian Civil Engineering College, Cooper's Hill; Indian Public Works and Telegraph Departments; Royal Marine Light Infantry; the Oxford and Cambridge Local Examinations, etc. By F. Edward Hulme, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto EXVIS.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 OC KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
wich; the Royal Military College, Sandhurst; the Indian Civil Engineering College, Cooper's Hill; Indian Public Works and Telegraph Departments; Royal Marine Light Infantry; the Oxford and Cambridge Local Examinations, etc. By F. Edward Hulme, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto Exvis.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth EENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 00 KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
gineering College, Cooper's Hill; Indian Public Works and Telegraph Departments; Royal Marine Light Infantry; the Oxford and Cambridge Local Examinations, etc. By F. Edward Hulme, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto EKVIS.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth EENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 00 KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
graph Departments; Royal Marine Light Infantry; the Oxford and Cambridge Local Examinations, etc. By F. Edward Hulme, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto ERVIS.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth EENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. ELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
Cambridge Local Examinations, etc. By F. EDWARD HULME, F. L. S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto ERVIS.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
S., F. S. A., Art-Master Marlborough College. Illustrated by 300 examples. Small quarto ERVIS.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 OC KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
examples. Small quarto EKVIS.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth EENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 OC KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
ERVIS.—Railroad Property: A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 OC KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
A Treatise on the Construction and Management of Railways; designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
designed to afford useful knowledge, in the popular style, to the holders of this class of property; as well as Railway Managers, ()fficers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
holders of this class of property; as well as Railway Managers, Officers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 oc KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
cers, and Agents. By John B. Jervis, late Civil Engineer of the Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distilla tion, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 oc KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
Hudson River Railroad, Croton Aqueduct, etc. 12mo., cloth \$1.50 KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. \$1 oc KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
KEENE.—A Hand-Book of Practical Gauging: For the Use of Beginners, to which is added a Chapter on Distillation, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By James B. Keene, of H. M. Customs. 8vo. SI OC KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
For the Use of Beginners, to which is added a Chapter on Distilla tion, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By JAMES B. KEENE, of H. M. Customs. 8vo. **StockElley.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
tion, describing the process in operation at the Custom-House for ascertaining the Strength of Wines. By JAMES B. KEENE, of H. M. Customs. 8vo. \$1 oc KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
ascertaining the Strength of Wines. By JAMES B. KEENE, of H. M. Customs. 8vo. \$1 oc KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
Customs. 8vo. \$1 oc KELLEY.—Speeches, Addresses, and Letters on Industrial and Financial Questions:
Financial Questions:
Financial Questions: By Hon. William D. Kelley, M. C. 544 pages, 8vo \$2.50
By Hon, William D. Kelley, M. C. 544 pages, 8vo \$2.50
The state of the s
KELLOGG.—A New Monetary System:
The only means of Securing the respective Rights of Labor and
Property, and of Protecting the Public from Financial Revulsions.
By EDWARD KELLOGG. 12mo. Paper cover, \$1.00. Bound in cloth. \$1.25
KEMLO.—Watch-Repairer's Hand-Book: Being a Complete Guide to the Young Beginner, in Taking Apart.
Putting Together, and Thoroughly Cleaning the English Lever and
other Foreign Watches, and all American Watches. By F. KEMLO.
ractical Watchmaker. With Illustrations. 12mo. \$1.25

KENTISH.—A Treatise on a Box of Instruments, And the Slide Rule; with the Theory of Trigonometry and Logs rithms, including Practical Geometry, Surveying, Measuring of Timber, Cask and Malt Gauging, Heights, and Distances. By THOMA "ENTISH. In one volume. 12mo. KERL.—The Assayer's Manual: An Abridged Treatise on the Docimastic Examination of Ores, and Furnace and other Artificial Products. By BRUNO KERL, Professor in the Royal School of Mines. Translated from the German by WILLIAM T. BRANNT. Second American edition, edited with Extensive Additions by F. LYNWOOD GARRISON, Member of the American Institute of Mining Engineers, etc. Illustrated by 87 engravings. 8vo. (Third Edition in preparation.) KICK.-Flour Manufacture. A Treatise on Milling Science and Practice. By FREDERICK KICK Imperial Regierungsrath, Professor of Mechanical Technology in the Imperial German Polytechnic Institute, Prague. Translated from the second enlarged and revised edition with supplement by H. H. P. Powles, Assoc. Memb. Institution of Civil Engineers. Illustrated with 28 Plates, and 167 Wood-cuts. 367 pages. 8vo. . \$10.00 "INGZETT.—The History, Products, and Processes of the Alkali Trade: including the most Recent Improvements. By CHABLES THOMAS KINGZETT. Consulting Chemist. With 23 illustrations. 8vo. KIRK.—The Cupola Furnace: A Practical Treatise on the Construction and Management of Foundry Cupolas. By EDWARD KIRK, Practical Moulder and Melter, Consulting Expert in Melting. Illustrated by 78 engravings. Second Edition, revised and enlarged, 450 pages. 8vo. 1903. \$3.50 CANDRIN.—A Treatise on Steel: Comprising its Theory, Metallurgy. Properties, Practical Working, and Use. By M. H. C. LANDRIN, JR. From the French, by A. A. FESQUET. 12mo. . \$2.5C LANGBEIN.—A Complete Treatise on the Electro-Deposition of Metals: Comprising Electro-Plating and Galvanoplastic Operations, the Deposition of Metals by the Contact and Immersion Processes, the Coloring of Metals, the Methods of Grinding and Polishing, as well as Descriptions of the Electric Elements. Dynamo-Electric Machines, Thermo-Piles and of the Materials and Processes used in Every Department of the Art. From the German of Dr. George Langbein, with additions by Wm. T. BRANNT. Fifth Edition, thoroughly revised and much enlarged. 170 Engravings. 694 pages 8vo. 1905. \$4.00 LARDNER .- The Steam-Engine: For the Use of Beginners. Illustrated. 12mo. . LEHNER.—The Manufacture of Ink: Comprising the Raw Materials, and the Preparation of Writing.

Copying and Hektograph Inks, Safety Inks, Ink Extracts and Powders, etc. Translated from the German of SIGMUND LEHNER, with

additions by WILLIAM T. BRANNT. Illustrated. 12mo.

LARKIN.—The Practical Brass and Iron Founder's Guide: A Concise Treatise on Brass Founding, Moulding, the Metals and their Alloys, etc.; to which are added Recent Improvements in the Manufacture of Iron, Steel by the Bessemer Process, etc., etc. By IAMES LARKIN, late Conductor of the Brass Foundry Department is Reany, Neafie & Co.'s Penn Works, Philadelphia. New edition, revised, with extensive additions. 414 pages. 12mo. LEROUX.—A Practical Treatise on the Manufacture of Worsteds and Carded Yarns: Comprising Practical Mechanics, with Rules and Calculations applied to Spinning; Sorting, Cleaning, and Scouring Wools; the English and French Methods of Combing, Drawing, and Spinning Worsteds, and Manufacturing Carded Yarns. Translated from the French of CHARLES LEROUX, Mechanical Engineer and Superintendent of a Spinning-Mill, by Horatio Paine, M. D., and A. A. Fesquet, Chemist and Engineer. Illustrated by twelve large Plates. To which is added an Appendix, containing Extracts from the Reports of the International Jury, and of the Artisans selected by the Committee appointed by the Council of the Society of Arts, London, on Wooles and Worsted Machinery and Fabrics, as exhibited in the Paris Universal Exposition, 1867. 8vo. \$5.00 LEFFEL.-The Construction of Mill-Dams: Comprising also the Building of Race and Reservoir Embankments and Head-Gates, the Measurement of Streams, Gauging of Water Supply, etc. By JAMES LEFFEL & Co. Illustrated by 58 engravings. (Scarce.) LESLIE.—Complete Cookery: Directions for Cookery in its Various Branches. By MISS LESLIE. Sixtieth thousand. Thoroughly revised, with the addition of New Receipts. 12mo. \$1.50 LE VAN.—The Steam Engine and the Indicator: Their Origin and Progressive Development; including the Most Recent Examples of Steam and Gas Motors, together with the Indicator, its Principles, its Utility, and its Application. By WILLIAM BARNET LE VAN. Illustrated by 205 Engravings, chiefly of Indi-\$2.00 cator-Cards. 469 pp. 8vo. LIEBER.—Assayer's Guide: Or, Practical Directions to Assayers, Miners, and Smelters, for the Tests and Assays, by Heat and by Wet Processes, for the Ores of all th principal Metals, of Gold and Silver Coins and Alloys, and of Coal, etc. By OSCAR M. LIEBER. Revised. 283 pp. 12mc. \$1.50 Lockwood's Dictionary of Terms: Used in the Practice of Mechanical Engineering, embracing those Current in the Drawing Office, Pattern Shop, Foundry, Fitting, Turning, Smith's and Boiler Shops, etc., etc., comprising upwards of Six Thousand Definitions. Edited by a Foreman Pattern Maker, author of "Pattern Making." 417 pp. 12mo.

LUKIN.-The Lathe and Its Uses: Or Instruction in the Art of Turning Wood and Metal. Including a Description of the Most Modern Appliances for the Ornamentation of Plane and Curved Surfaces, an Entirely Novel Form of Lathe for Eccentric and Rose-Engine Turning; A Lathe and Planing Machine Combined: and Other Valuable Matter Relating to the Art. Illustrated by 462 engravings. Seventh edition. 315 pages. Svo. \$4.25 MAIN and BROWN.—Questions on Subjects Connected with the Marine Steam-Engine: And Examination Papers; with Hints for their Solution. By THOMAS J. MAIN, Professor of Mathematics, Royal Naval College, and THOMAS BROWN, Chief Engineer, R. N. 12mo., cloth . MAIN and BROWN.—The Indicator and Dynamometer: With their Practical Applications to the Steam-Engine. By THOMAS . MAIN, M. A. F. R., Ass't S. Professor Royal Naval College, Portsmouth, and THOMAS BROWN, Assoc. Inst. C. E., Chief Engineer R. N., attached to the R. N. College. Illustrated. 8vo. . WAIN and BROWN.—The Marine Steam-Engine. By THOMAS J. MAIN, F. R. Ass't S. Mathematical Professor at the Royal Naval College, Portsmouth, and Thomas Brown, Assoc. Inst. C. E., Chief Engineer R. N. Attached to the Royal Naval College. With numerous illustrations. 8vo. MAKINS.—A Manual of Metallurgy: By GEORGE HOGARTH MAKINS. 100 engravings. Second edition rewritten and much enlarged. 12mo., 592 pages ⊀ARTIN.—Screw-Cutting Tables, for the Use of Mechanics Engineers: Showing the Proper Arrangement of Wheels for Cutting the Threads of Screws of any Required Pitch; with a Table for Making the Universal Gas-Pipe Thread and Taps. By W. A. MARTIN, Engineer. **8v**o. MICHELL.—Mine Drainage: Being a Complete and Practical Treatise on Direct-Acting Under ercund Steam Pumping Machinery. With a Description of a large number of the best known Engines, their General Utility and the Special Sphere of their Action, the Mode of their Application, and their Merits compared with other Pumping Machinery. By STEPHEN MICHELL. Illustrated by 247 engravings. 8vo., 369 pages. \$12 50 MOLESWORTH.—Pocket-Book of Useful Formulæ and Memoranda for Civil and Mechanical Engineers. By GUILFORD L. MOLESWORTH, Member of the Institution of Civil Engineers, Chief Resident Engineer of the Ceylon Railway. Fullbound in Pocket-book form

MOORE.—The Universal Assistant and the Complete Machanic: Containing over one million Industrial Facts, Calculations, Receipts, Processes Trades Secrets, Pulse, Pusiness Forms, Level Items, Fig.

Processes, Trades Secrets, Rules, Business Forms, Legal Items, Fic., in every occupation, from the Household to the Manufactory. By R. Moore. Illustrated by 500 Engravings. 12mo. \$2.50

MAUCHLINE.—The Mine Foreman's Hand-Book

Of Practical and Theoretical Information on the Opening, Ventilating, and Working of Collieries. Questions and Answers on Practical and Theoretical Coal Mining. Designed to Assist Students and Others in Passing Examinations for Mine Foremanships. By ROBERT MAUCHLINE. 3d Edition. Thoroughly Revised and Enlarged by F. ERNEST BRACKETT. 134 engravings, 8vo. 378 pages.

(1905)

WAPIER.—A System of Chemistry Applied to Dyeing.

By JAMES NAPIER, F. C. S. A New and Thoroughly Revised Edition. Completely brought up to the present state of the Science uncluding the Chemistry of Coal Tar Colors, by A. A. FESQUET, Chemist and Engineer. With an Appendix on Dyeing and Calica Printing, as shown at the Universal Exposition, Paris, 1867. Illustrational Company of the Company of

trated. 8vo. 422 pages \$3.00
NEVILLE.—Hydraulic Tables, Coefficients, and Formulæ, for
finding the Discharge of Water from Orifices, Notches
Weirs, Pipes, and Rivers:

Chird Edition, with Additions, consisting of New Formulæ for the Discharge from Tidal and Flood Sluices and Siphons; general infornation on Rainfall, Catchment-Basins, Drainage, Sewerage, Waler Supply for Towns and Mill Power By John Neville. C. E. M R I, A.; Fellow of the Royal Geological Society of Ireland. Thick 12mo.

NEWBERY — Gleanings from Ornamental Art of every style:

Drawn from Examples in the British, South Kensington, Indian, Crystal Palace, and other Museums, the Exhibitions of 1851 and 1862, and the best English and Foreign works. In a series of 100 exquisitely drawn Plates, containing many hundred examples. By ROBERT NEWBERY. 4to. (Scarce.)

ICHOLLS.—The Theoretical and Practical Boiler-Maker and Engineer's Reference Book:

Containing a variety of Useful Information for Employers of Labor Foremen and Working Boiler-Makers Iron, Copper, and Tinsmiths

	Granghtsmen, Engineers, the General Steam-using Public, and for the
	Use of Science Schools and Classes, By SAMUEL NICHOLLS. Illus
	trated by sixteen plates, 12mo. \$2.50
N	ICHOLSON.—A Manual of the Art of Bookbinding:
	Containing full instructions in the different Branches of Forwarding, Gilding, and Finishing. Also, the Art of Marbling Book-edges and
	Paper. By JAMES B. NICHOLSON. Illustrated. 12mo., cloth \$2.25
N	ICOLLS.—The Railway Builder:
•	A Hand-Book for Estimating the Probable Cost of American Ra.l-
	way Construction and Equipment. By WILLIAM J. NICOLLS, Civil
	Engineer. Illustrated, full bound, pocket-book form . \$2.00
N	ORMANDY.—The Commercial Handbook of Chemical An-
	alysis:
	Or Practical Instructions for the Determination of the Intrinsic on
	Commercial Value of Substances used in Manufactures, in Trades,
	and in the Arts. By A. NORMANDY. New Edition, Enlarged, and
	to a great extent rewritten. By HENRY M. NOAD, Ph.D., F.R.S.
	thick 12mo
N	ORRIS.—A Handbook for Locomotive Engineers and Ma
	chinists:
	Comprising the Proportions and Calculations for Constructing Loco
	motives; Manner of Setting Valves; Tables of Squares, Cubes, Areas
	etc., etc. By SEPTIMUS NORRIS, M. E. New edition. Illustrated,
	12mo
•	YSTROM.—A New Treatise on Elements of Mechanics: Establishing Strict Precision in the Meaning of Dynamical Terms
	accompanied with an Appendix on Duodenal Arithmetic and Me
	trology. By John W. Nystrom, C. E. Illustrated. 8vo.
N	YSTROM.—On Technological Education and the Construc-
•	tion of Ships and Screw Propellers:
	For Naval and Marine Engineers. By JOHN W. NYSTROM, late
	acting Chief Engineer, U.S.N. Second edition, revised, with addi
	tional matter. Illustrated by seven engravings. 12mo \$1.28
C	"NEILL.—A Dictionary of Dyeing and Calico Printing:
	Containing a brief account of all the Substances and Processes in
	use in the Art of Dyeing and Printing Textile Fabrics; with Practical
	Receipts and Scientific Information. By CHARLES O'NEILL, Analy-
	tical Chemist. To which is added an Essay on Coal Tar Colors and
	their application to Dyeing and Calico Printing. By A. A. FESQUET,
	Chemist and Engineer. With an appendix on Dyeing and Calico
	Printing, as shown at the Universal Exposition, Paris, 1867 8vo.,
_	491 pages
,	RTON.—Underground Treasures:
	How and Where to Find Them. A Key for the Ready Determination of all the Useful Minerals within the United States. By JAMES
	ORTON, A.M., Late Professor of Natural History in Vassar College
	N. Y; author of the "Andes and the Amazon," etc. A New Edi-
	tion, with An Appendix on Ore Deposits and Testing Minerals (1901).
	Illustrated

OSBORN.—The Prospector's Field Book and Guide. In the Search For and the Easy Determination of Ores and Other Useful Minerals. By Prof. H. S. OSBORN, LL. D. Illustrated by 66 Engravings. Sixth Edition. Revised and Enlarged. 360 pages, (Dec., 1903) \$1.50 OSBORN-A Practical Manual of Minerals, Mines and Min-Comprising the Physical Properties, Geologic Positions, Local Occurrence and Associations of the Useful Minerals; their Methods of Chemical Analysis and Assay: together with Various Systems of Excavating and Timbering, Brick and Masonry Work, during Driving, Lining, Bracing and other Operations, etc. By Prof. H. S. OSBORN. LL. D., Author of "The Prospector's Field-Book and Guide." 171 engravings. Second Edition, revised. 8vo. \$4.50 OVERMAN. - The Manufacture of Steel: Containing the Practice and Principles of Working and Making Steel. A Handbook for Blacksmiths and Workers in Steel and Iron, Wagon Makers, Die Sinkers, Cutlers, and Manufacturers of Files and Hardware, of Steel and Iron, and for Men of Science and Art. By FREDERICK OVERMAN, Mining Engineer, Author of the "Manufacture of Iton," etc. A new, enlarged, and revised Edition. By A. A. FESOLET, Chemist and Engineer. 12mo. OVERMAN.—The Moulder's and Founder's Pocket Guide: A Treatise on Moulding and Founding in Green-sand, Dry-sand, Loam, and Cement; the Moulding of Machine Frames, Mill-gear, Hollowware, Ornaments, Trinkets, Bells, and Statues; Description of Moulds for Iron, Bronze, Brass, and other Metals; Plaster of Paris, Sulphur, Wax, etc.; the Construction of Melting Furnaces, the Melting and Founding of Metals; the Composition of Alloys and their Nature, etc., etc. By FREDERICK OVERMAN, M. E. A new Edition, to which is added a Supplement on Statuary and Ornamental Moulding, Ordnance, Malleable Iron Castings, etc. By A. A. FESQUET, Chemist and Engineer. Illustrated by 44 engravings. 12mo. . PAINTER, GILDER, AND VARNISHER'S COMPANION. Comprising the Manufacture and Test of Pigments, the Arts of Paint ing, Graining, Marbling, Staining, Sign-writing, Varnishing, Glassstaining, and Gilding on Glass; together with Coach Painting and Varnishing, and the Principles of the Harmony and Contrast of Colors. Twenty-seventh Edition. Revised, Enlarged, and in great part Rewritten. By WILLIAM T. BRANNT, Editor of "Varnishes, Lacquers, Printing Inks and Sealing Waxes." Illustrated. 395 pp.

PALLETT.—The Miller's, Millwright's, and Engineer's Guide.

By HENRY PALLETT. Illustrated. 12mo.

PERCY.—The Manufacture of Russian Sheet-Iron. By JOHN PERCY, M. D., F. R. S. Paper. PERKINS.—Gas and Ventilation: 25 cts. Practical Treatise on Gas and Ventilation. Illustrated. 12mo. \$1.25 PERKINS AND STOWE.—A New Guide to the Sheet-iron and Boiler Plate Roller: Containing a Series of Tables showing the Weight of Slabs and Piles to Produce Boiler Plates, and of the Weight of Piles and the Sizes of Bars to produce Sheet-iron; the Thickness of the Bar Gauge in decimals; the Weight per foot, and the Thickness on the Bar or Wire Gauge of the fractional parts of an inch; the Weight per sheet, and the Thickness on the Wire Gauge of Sheet-iron of various dimensions to weigh 112 lbs. per bundle; and the conversion of Short Weight into Long Weight, and Long Weight into Short. POSSELT.—Recent Improvements in Textile Machinery Relating to Weaving: Giving the Most Modern Points on the Construction of all Kinds of Looms, Warpers, Beamers, Slashers, Winders, Spoolers, Reeds, Temples, Shuttles, Bobbins, Heddles, Heddle Frames, Pickers, Jacquards, Card Stampers, etc., etc. 600 illus. POSSELT.—Technology of Textile Design: The Most Complete Treatise on the Construction and Application of Weaves for all Textile Fabrics and the Analysis of Cloth. By E. A. Posselt. 1,500 illustrations. 4to. POSSELT.—Textile Calculations: A Guide to Calculations Relating to the Manufacture of all Kinds

of Yarns and Fabrics, the Analysis of Cloth, Speed, Power and Belt

REGNAULT.—Elements of Chemistry:

Calculations. By E. A. Posselt. Illustrated. 4to.

By M. V. REGNAULT. Translated from the French by T. FORREST BETTON, M. D., and edited, with Notes, by JAMES C. BOOTH, Melter and Refiner U. S. Mint, and WILLIAM L. FABER, Metallurgist and Mining Engineer. Illustrated by nearly 700 wood-engravings. Comprising nearly 1,500 pages. In two volumes, 8vo., cloth. RICHARDS.—Aluminium:

Its History, Occurrence, Properties, Metallurgy and Applications, including its Alloys. By JOSEPH W. RICHARDS, A. C., Chemist and Practical Metallurgist, Member of the Deutsche Chemische Gesellschaft. Illust. Third edition, enlarged and revised (1895) . \$6.00 RIFFAULT, VERGNAUD, and TOUSSAINT .- A Practical

Treatise on the Manufacture of Colors for Painting: Comprising the Origin, Definition, and Classification of Colors; the Treatment of the Raw Materials; the best Formulæ and the Newest Processes for the Preparation of every description of Pigment, and the Necessary Apparatus and Directions for its Use; Dryers; the Testing. Application, and Qualities of Paints, etc., etc. By MM. RIFFAULT, VERGNAUD, and TOUSSAINT. Revised and Edited by M. F. MALEPEYRE. Translated from the French, by A. A. Francisco Chemist and Engineer. Illustrated by Eighty engravings. In one vol., 8vo., 659 pages \$5.00

ROPER.—Catechism for Steam Engineers and Electricians:
Including the Construction and Management of Steam Engines,
Steam Boilers and Electric Plants. By STEPHEN ROPER. Twentyfirst edition, rewritten and greatly enlarged by E. R. Keller and
C. W. Pike. 365 pages. Illustrations. 18mo., tucks, gilt. \$2.00

ROPER.—Engineer's Handy Book:

Containing Facts, Formulæ, Tables and Questions on Power, its Generation, Transmission and Measurement; Heat, Fuel, and Steam; The Steam Boiler and Accessories; Steam Engines and their Parts; Steam Engine Indicator; Gas and Gasoline Engines; Materials; their Properties and Strength; Together with a Discussion of the Fundamental Experiments in Electricity, and an Explanation of Dynamos, Motors, Batteries, etc., and Rules for Calculating Sizes of Wires. By STEPHEN ROPER. 15th edition. Revised and enlarged by E. R. KELLER, M. E. and C. W. PIKE, B. S. (1899), with numerous illustrations. Pocket-book form. Leather.

ROPER.—Hand-Book of Land and Marine Engines:

Including the Modelling, Construction, Running, and Management of Land and Marine Engines and Boilers. With illustrations. By 'STEPHEN ROPER, Engineer. Sixth edition. 12mo., trcks, gilt edge.

ROPER.—Hand-Book of the Locomotive:

Including the Construction of Engines and Boilers, and the Construction, Management, and Running of Locomotives. By STEPHEN ROPER. Eleventh edition. 18mo., tucks, gilt edge. \$2.50

ROPER.—Hand-Book of Modern Steam Fire-Engines.

ROPER.—Questions and Answers for Engineers.

This little book contains all the Questions that Engineers will be asked when undergoing an Examination for the purpose of procuring Licenses, and they are so plain that any Engineer or Fireman of or dinary intelligence may commit them to memory in a short time. By STEPHEN ROPER, Engineer. Third edition \$2.00

ROPER.—Use and Abuse of the Steam Boiler.

ROSE.—The Complete Practical Machinist:

Embracing Lathe Work, Vise Work, Drills and Drilling, Taps and Dies, Hardening and Tempering, the Making and Use of Tools Tool Grinding, Marking out Work, Machine Tools, etc. By Joshua Rose. 395 Engravings. Nineteenth Edition, greatly Enlarged with New and Valuable Matter. 12mo., 504 pages. \$2.50

ROSE.—Mechanical Drawing Self-Taught:

Comprising Instructions in the Selection and Preparation of Drawing struments, Elementary Instruction in Practical Mechanical Draw-

ing, together with Examples in Simple Geometry and Elementary Mechanism, including Screw Threads, Gear Wheels, Mechanical Motions, Engines and Boilers. By JOSHUA ROSE, M. E. Illustrated by 330 engravings. 8vo., 313 pages \$4.00
ROSE.—The Slide-Valve Practically Explained: Embracing simple and complete Practical Demonstrations of the operation of each element in a Slide-valve Movement, and illustrating the effects of Variations in their Proportions by examples carefully selected from the most recent and successful practice. By JOSHUA ROSE, M. E. Illustrated by 35 engravings \$1.00
ROSS.—The Blowpipe in Chemistry, Mineralogy and Geology: Containing all Known Methods of Anhydrous Analysis, many Working Examples, and Instructions for Making Apparatus. By LIEUTCOLONEL W. A. Ross, R. A., F. G. S. With 120 Illustrations, 12mo
SHAW.—Civil Architecture: Being a Complete Theoretical and Practical System of Building, containing the Fundamental Principles of the Art. By EDWARD SHAW, Architect. To which is added a Treatise on Gothic Architecture, etc. By THOMAS W. SILLOWAY and GEORGE M. HARDING, Architects. The whole illustrated by 102 quarto plates finely engraved on copper. Eleventh edition. 4to. \$6.00
SHUNK.—A Practical Treatise on Railway Curves and Location, for Young Engineers. By W. F. Shunk, C. E. 12mo. Full bound pocket-book form \$2.00
SLATER.—The Manual of Colors and Dye Wares. By J. W. SLATER. 12mo
SLOAN.—American Houses: A variety of Original Designs for Rural Buildings. 26 colored engravings, with descriptive references. SLOAN, Architect. 8vo
SLOAN.—Homestead Architecture: Containing Forty Designs for Villas, Cottages, and Farm-houses, with Essays on Style, Construction, Landscape Gardening, Furniture, etc., etc. Illustrated by upwards of 200 engravings. By SAMUEL SLOAN, Architect. 8vo. \$250
BLOANE.—Home Experiments in Science. By T. O'CONOR SLOANE, E. M., A. M., Fh. D. Illustrated by 91 engravings. 12mo
SMEATON.—Builder's Pocket-Companion: Containing the Elements of Building, Surveying, and Architecture; with Practical Rules and Instructions connected with the subject. By A. C. SMEATON, Civil Engineer, etc. 12mo.
8MITH.—A Manual of Political Economy. By E. PESHINE SMITH. A New Edition, to which is added a full Index. 12mo. \$1 25

SMITH.—Parks and Pleasure-Grounds:
Or Practical Notes on Country Residences, Villas, Public Parks, and
Gardens. By CHARLES H. J. SMITH, Landscape Gardener and
Garden Architect, etc., etc. 12mo \$2.00
SMITH.—The Dyer's Instructor:
Comprising Practical Instructions in the Art of Dyeing Silk, Cotton,
Wool, and Worsted, and Woolen Goods; containing nearly 800
Receipts. To which is added a Treatise on the Art of Padding; and the Printing of Silk Warps, Skeins, and Handkerchiefs, and the
various Mordants and Colors for the different styles of such work.
Ry David Smith Pottern Duer 12mo \$1.50
BY DAVID SMITH, Pattern Dyer. 12mo. \$1.50 SMYTH.—A Rudimentary Treatise on Coal and Coal-Mining.
By WARRINGTON W. SMYTH, M. A., F. R. G., President R. G. S.
of Cornwall. Fifth edition, revised and corrected. With numer-
ous illustrations. 12mo
SNIVELY.—Tables for Systematic Qualitative Chemical Anal-
ysis.
By John H. Snively, Phr. D. 8vo \$1.00
SNIVELY.—The Elements of Systematic Qualitative Chemical
Analysis:
A Hand-book for Beginners. By JOHN H. SNIVELY, Phr. D. 16mo.
\$2.00
STOKES.—The Cabinet-Maker and Upholsterer's Companion:
Comprising the Art of Drawing, as applicable to Cabinet Work;
Veneering, Inlaying, and Buhl-Work; the Art of Dyeing and Stain
ing Wood, Ivory, Bone, Tortoise-Shell, etc. Directions for Lacker
ing, Japanning, and Vurnishing; to make French Polish, Glues
Cements, and Compositions; with numerous Receipts, useful to work
men generally. By STOKES. Illustrated. A New Edition, with
an Appendix upor ench Polishing, Staining, Imitating, Varnishing,
etc., etc. 12mo
STRENGTH AND OTHER PROPERTIES OF METALS:
Reports of Experiments on the Strength and other Properties of
Metals for Cannon. With a Description of the Machines for Testing
Metals, and of the Classification of Cannon in service. By Officers of the Ordnance Department, U. S. Army. By authority of the Secre-
tary of War. Illustrated by 25 large steel plates. Quarto . \$5.00
SULLIVAN.—Protection to Native Industry.
By Sir EDWARD SULLIVAN, Baronet, author of "Ten Chapters on
Social Reforms." 8vo
SHERRATT.—The Elements of Hand-Railing:
Simplified and Explained in Concise Problems that are Easily Under-
stood. The whole illustrated with Thirty-eight Accurate and Origi-
nal Plates, Founded on Geometrical Principles, and Showing how to
Make Rail Without Centre Joints, Making Better Rail of the Same
Material, with Half the Labor, and Showing How to Lay Out Stairs
of all Kinds. By R. J. SHERRATT. Folio

SYME.—Outlines of an Industrial Science.
By DAVID SYME. 12mo, \$2.00
TABLES SHOWING THE WEIGHT OF ROUND,
SQUARE, AND FLAT BAR IRON, STEEL, ETC.,
By Measurement. Cloth 63
THALLNER.—Tool-Steel:
A Concise Handbook on Tool-Steel in General. Its Treatment in
the Operations of Forging, Annealing, Hardening, Tempering, etc.,
and the Appliances Therefor. By OTTO THALLNER, Manager in
Chief of the Tool-Steel Works, Bismarckhütte, Germany. From the
German by WILLIAM T. BRANNT. Illustrated by 69 engravings.
194 pages. 8vo. 1902
TEMPLETON.—The Practical Examinator on Steam and the
Steam-Engine:
With Instructive References relative thereto, arranged for the Use of
Engineers, Students, and others. By WILLIAM TEMPLETON, En
gineer. 12mo
gineer. 12mo. \$1.00 FHAUSING.—The Theory and Practice of the Preparation of
Malt and the Fabrication of Beer:
With especial reference to the Vienna Process of Brewing. Elab-
orated from personal experience by Julius E. Thausing, Professor
at the School for Brewers, and at the Agricultural Institute, Mödling,
near Vienna. Translated from the German by WILLIAM T. BRANNT,
Thoroughly and elaborately edited, with much American matter, and
according to the latest and most Scientific Practice, by A. SCHWARZ
and Dr. A. H. BAUER. Illustrated by 140 Engravings. 8vo., 815
pages \$10.00
THOMPSON.—Political Economy. With Especial Reference
to the Industrial History of Nations:
By ROBERT E. THOMPSON, M. A., Professor of Social Science in the
University of Pennsylvania. 12mo \$1.50
THOMSON.—Freight Charges Calculator:
By Andrew Thomson, Freight Agent. 24mo \$1.25
TURNER'S (THE) COMPANION:
Containing Instructions in Concentric, Elliptic, and Eccentric Turn-
ing; also various Plates of Chucks, Tools, and Instruments; and
Directions for using the Eccentric Cutter, Drill, Vertical Cutter, and
Circular Rest; with Patterns and Instructions for working them.
I2mo \$1.00
TURNING: Specimens of Fancy Turning Executed on the
Hand or Foot-Lathe:
With Geometric, Oval, and Eccentric Chucks, and Elliptical Cutting
Frame. By an Amateur. Illustrated by 30 exquisite Photographs.
4to (Scarce.)

VAILE.—Galvanized-Iron Cornice-Worker's Manual: Containing Instructions in Laying out the Different Mitres, and Making Patterns for all kinds of Plain and Circular Work. Also Tables of Weights, Areas and Circumferences of Circles, and othe Matter calculated to Benefit the Trade. By CHARLES A. VAILE Illustrated by twenty-one plates. 4to (Scarce.
VILLE.—On Artificial Manures: Their Chemical Selection and Scientific Application to Agriculture A series of Lectures given at the Experimental Farm at Vincennes during 1867 and 1874-75. By M. GEORGES VILLE. Translated and Edited by WILLIAM CROOKES, F. R. S. Illustrated by thirty-one engravings. 8vo., 450 pages
VILLE.—The School of Chemical Manures: Or, Elementary Principles in the Use of Fertilizing Agents. From the French of M. Geo. VILLE, by A. A. FESQUET, Chemist and Engineer. With Illustrations. 12mo. \$1.2
VOGDES.—The Architect's and Builder's Pocket-Companion and Price-Book: Consisting of a Short but Comprehensive Epitome of Decimals, Duodecimals, Geometry and Mensuration; with Tables of United States Measures, Sizes, Weights, Strengths, etc., of Iron, Wood, Stone, Brick, Cement and Concretes, Quantities of Materials in given Sizes and Dimensions of Wood, Brick and Stone; and full and complete Bills of Prices for Carpenter's Work and Painting; also, Rules for Computing and Valuing Brick and Brick Work, Stone Work, Painting, Plastering, with a Vocabulary of Technical Terms, etc. By Frank W. Vogdes, Architect, Indianapolis, Ind. Enlarged, revised, and corrected. In one volume, 368 pages, full-bound, pocket-book form, gilt edges Cloth VAN CLEVE.—The English and American Mechanic: Comprising a Collection of Over Three Thousand Receipts, Rules, and Tables, designed for the Use of every Mechanic and Manufacturer. By B. Frank Van Cleve. Illustrated. 500 pp. 12mo. \$2.00
VAN DER BURG.—School of Painting for the Imitation of Woods and Marbles: A Complete, Practical Treatise on the Art and Craft of Graining and Marbling with the Tools and Appliances. 36 plates. Folio, 12 x 20 inches. \$10.00
WAHNSCHAFFE.—A Guide to the Scientific Examination of Soils: Comprising Select Methods of Mechanical and Chemical Analysis and Physical Investigation. Translated from the German of Dr. F. WAHNSCHAFFE. With additions by WILLIAM T. BRANNT. Illustrated by 25 engravings. 12mo. 177 pages

WARE.—The Sugar Beet.

Including a History of the Beet Sugar Industry in Europe, Varietle of the Sugar Beet, Examination, Soils, Tillage, Seeds and Sowing, Yield and Cost of Cultivation, Harvesting, Transportation, Conservation, Feeding Qualities of the Beet and of the Pulp, etc. By LEWIS. WARE, C. E., M. E. Illustrated by ninety engravings. 8vo.

\$4.00

WARN.—The Sheet-Metal Worker's Instructor:

For Zinc, Sheet-Iron, Copper, and Tin-Plate Workers, etc. Containing a selection of Geometrical Problems; also, Practical and Simple Rules for Describing the various Patterns required in the different branches of the above Trades. By REUBEN H. WARN, Practical Tin-Plate Worker. To which is added an Appendix, containing Instructions for Boiler-Making, Mensuration of Surfaces and Solids, Rules for Calculating the Weights of different Figures of Iron and Steel, Tables of the Weights of Iron, Steel, etc. Illustrated by thirty two Plates and thirty-seven Wood Engravings. 8vo. \$3.00

WARNER.—New Theorems, Tables, and Diagrams, for the Computation of Earth-work:

WILSON.—Carpentry and Joinery:

By JOHN WILSON, Lecturer on Building Construction, Carpentry and Joinery, etc., in the Manchester Technical School. Third Edition, with 65 full-page plates, in flexible cover, oblong. . (Scarce.)

WATSON .- A Manual of the Hand-Lathe:

Comprising Concise Directions for Working Metals of all kinds, Ivory, Bone, and Precious Woods; Dyeing, Coloring, and French Polishing; Inlaying by Veneers, and various methods practised to produce Elaborate work with Dispatch, and at Small Expense. By EGBERT P. WATSON, Author of "The Modern Practice of American Machinists and Engineers." Illustrated by 78 engravings. \$1.50

WATSON.—The Modern Practice of American Machinists and Engineers:

Including the Construction, Application, and Use of Drills, Lathe Tools, Cutters for Boring Cylinders, and Hollow-work generally, with the most Economical Speed for the same; the Results verified by Actual Practice at the Lathe, the Vise, and on the floor. Together

with Workshop Management, Economy of Manufacture, the Steam Engine, Boilers, Gears, Belting, etc., etc. By EGBERT P. WATSON. Illustrated by eighty-six engravings. 12mo. . . . \$2.50

WATT .- The Art of Soap Making:

WEATHERLY.—Treatise on the Art of Boiling Sugar, Crystallizing, Lozenge-making, Comfits, Gum Goods,

And other processes for Confectionery, including Methods for Manufacturing every Description of Raw and Refined Sugar Goods. A New and Enlarged Edition, with an Appendix on Cocoa, Chocolate, Chocolate Confections, etc. 196 pages, 12mo. (1903) . \$1.50

WILL.—Tables of Qualitative Chemical Analysis:

With an Introductory Chapter on the Course of Analysis. By Professor Heinrich Will, of Giessen, Germany. Third American, from the eleventh German edition. Edited by CHARLES F. HIMES, Ph. D., Professor of Natural Science, Dickinson College, Carlisle, Pa. 8vo.

WILLIAMS .- On Heat and Steam:

Embracing New Views of Vaporization, Condensation and Explosion. By Charles Wye Williams, A. I. C. E. Illustrated. 8vo.

WILSON.—First Principles of Political Economy:

WILSON.—The Practical Tool-Maker and Designer:

A Treatise upon the Designing of Tools and Fixtures for Machine Tools and Metal Working Machinery, Comprising Modern Examples of Machines with Fundamental Designs for Tools for the Actual Production of the work; Together with Special Reference to a Set of Tools for Machining the Various Parts of a Bicycle. Illustrated by 189 engravings. 1898.

CONTENTS: Introductory. Chapter I. Modern Tool Room and Equipment. II. Files, Their Use and Abuse. III. Steel and Tempering. IV. Making Jigs. V. Milling Machine Fixtures. VI. Tools and Fixtures for Screw Machines. VII. Broaching. VIII. Punches and Dies for Cutting and Drop Press. IX. Tools for Hollow-Ware. X. Embossing: Metal, Coin, and Stamped Sheet-Metal Ornaments. XI. Drop Forging. XII. Solid Drawn Shells or Ferrules; Cupping or Cutting, and Drawing; Breaking Down Shells. XIII. Annealing, Picking, and Cleaning, XIV. Tools for Draw Bench. XV. Cutting and Assembling Pieces by Means of Ratchet Dial Plates at One Operation. XVI. The Header. XVII. Tools for Fox Lathe. XVIII. Suggestions for a Set of Tools for Machining the Various Parts of a Bicycle. XIX. The Plater's Dynamo. XX. Conclusion—With a Few Random Ideas. Appendix. Index.

WOODS.—Compound Locomotives:

By ARTHUR TANNATT WOODS. Second edition, revised and enlarged by DAVID LEONARD BARNES, A. M., C. E. 8vo. 330 pp. \$3.00

WOHLER.-A Hand-Book of Mineral Analysis:

By F. Wöhler, Professor of Chemistry in the University of Göttingen. Edited by Henry B. Nason, Professor of Chemistry in the Renssalaer Polytechnic Institute, Troy, New York. Illustrated. 12mo. \$2.50

WORSSAM.—On Mechanical Saws:

From the Transactions of the Society of Engineers, 1869. By S. W. WORSSAM, JR. Illustrated by eighteen large plates. 8vo. \$1.50

RECENT ADDITIONS.

BRANNT.—Varnishes, Lacquers, Printing Inks and Sealing-Waxes:

Their Raw Materials and their Manufacture, to which is added the Art of Varnishing and Lacquering, including the Preparation of Putties and of Stains for Wood, Ivory, Bone, Horn, and Leather. By WILLIAM T. BRANNT. Illustrated by 39 Engravings, 338 pages. 12mo.

BRANNT-The Practical Scourer and Garment Dyer:

Comprising Dry or Chemical Cleaning; the Art of Removing Stains; Fine Washing; Bleaching and Dyeing of Straw Hats, Gloves, and Feathers of all kinds; Dyeing of Worn Clothes of all fabrics, including Mixed Goods, by One Dip; and the Manufacture of Soaps and Fluids for Cleansing Purposes. Edited by WILLIAM T. BRANNT, Editor of "The Techno-Chemical Receipt Book." Illustrated. 203 pages. 12mo. \$2.00

BRANNT .- Petroleum .

Its History, Origin, Occurrence, Production, Physical and Chemical Constitution, Technology, Examination and Uses; Together with the Occurrence and Uses of Natural Gas. Edited chiefly from the German of Prof. Hans Hoefer and Dr. Alexander Veith, by WM. T. BRANNT. Illustrated by 3 Plates and 284 Engravings. 743 pp. 8vo.

BRANNT.—A Practical Treatise on the Manufacture of Vinegar and Acetates, Cider, and Fruit-Wines;

Preservation of Fruits and Vegetables by Canning and Evaporation; Preparation of Fruit-Butters, Jellies, Marmalades, Catchups, Pickles, Mustards, etc. Edited from various sources. By WILLIAM T. BRANNT. Illustrated by 79 Engravings. 479 pp. 8vo. \$5.00

BRANNT.—The Metal Worker's Handy-Book of Receipts and Processes:

Being a Collection of Chemical Formulas and Practical Manipulations for the working of all Metals; including the Decoration and Beautifying of Articles Manufactured therefrom, as well as their Preservation. Edited from various sources. By WILLIAM T. BRANNT. Illustrated. 12mo. \$2.50

DEITE.—A Practical Treatise on the Manufacture of Perfumery:
Comprising directions for making all kinds of Perfumes, Sache Powders, Furnigating Materials, Dentifrices, Cosmetics, etc., with a full account of the Volatile Oils, Balsams, Resins, and other Natural and Artificial Perfume-substances, including the Manufacture of Fruit Ethers, and tests of their purity. By Dr. C. Deite, assisted by L. Borcher, F. Eichbaum, E. Kugler, H. Toeffner, and other experts. From the German, by Wm. T. Brannt. 28 Engravings. 358 pages. 8vo. \$3.00 DWARDS.—American Marine Engineer, Theoretical and Practical:
With Examples of the latest and most approved American Practice. By EMORY EDWARDS. 85 illustrations. 12mo \$2.50
EDWARDS.—goo Examination Questions and Answers: For Engineers and Firemen (Land and Marine) who desire to obtain a United States Government or State License. Pocket-book form, gilt edge \$1.50
FLEMMING.—Practical Tanning: A Handbook of Modern Processes, Receipts, and Suggestions for the Treatment of Hides, Skins, and Pelts of Every Description. By Lewis A. Flemming. American Tanner. 472 pp. 8vo. (1903) \$4.00.
POSSELT.—The Jacquard Machine Analysed and Explained: With an Appendix on the Preparation of Jacquard Cards, and Practical Hints to Learners of Jacquard Designing. By E. A. Posselt. With 230 illustrations and numerous diagrams. 127 pp. 4to. \$3.00
POSSELT.—Recent Improvements in Textile Machinery, Part III:
Processes Required for Converting Wool, Cotton, Silk, from Fibre to Finished Fabric, Covering both Woven and Knit Goods; Construction of the most Modern Improvements in Preparatory Machinery, Carding, Combing, Drawing, and Spinning Machinery, Winding, Warping, Slashing Machinery Looms, Machinery for Knit Goods, Dye Stuffs, Chemicals, Soaps, Latest Improved Accessories Relating to Construction and Equipment of Modern Textile Manufacturing Plants. By E. A. Posselt. Completel Illustrated. 4to. \$7.50
A Practical and Scientific Treatise, giving Improved Methods of Shoeing, with Special Directions for Shaping Shoes to Cure Different Diseases of the Foot, and for the Correction of Faulty Action in Trotters. By George E. Rich. 62 Illustrations. 153 pages.

RICHARDSON.—Practical Blacksmithing: A Collection of Articles Contributed at Different Times by Skilled Workmen to the columns of "The Blacksmith and Wheelwright," and Covering nearly the Whole Range of Blacksmithing, from the Simplest Job of Work to some of the Most Complex Forgings. Compiled and Edited by M. T. RICHARDSON.
Vol. I. 210 Illustrations. 224 pages. 12mo \$1.00
Vol. II. 230 Illustrations. 262 pages. 12mo \$1.00
Vol. III. 390 Illustrations. 307 pages. 12mo \$1.00
Vol. IV. 226 Illustrations. 276 pages, 12mo \$1.00
RICHARDSON:—The Practical Horseshoer:
Being a Collection of Articles on Horseshoeing in all its Branches
which have appeared from time to time in the columns of "?he Blacksmith and Wheelwright," etc. Compiled and edited by M. T.
Blacksmith and Wheelwright," etc. Compiled and edited by M. T.
RICHARDSON. 174 illustrations
ROPER.—Instructions and Suggestions for Engineers and
Firemen:
By Stephen Roper, Engineer. 18mo. Morocco . \$2.00
ROPER.—The Steam Boiler: Its Care and Management:
By STEPHEN ROPER, Engineer. 12mo., tuck, gilt edges. \$2.00
ROPER.—The Young Engineer's Own Book:
Containing an Explanation of the Principle and Theories on which
the Steam Engine as a Prime Mover is Based. By STEPHEN ROPER.
Engineer. 160 illustrations, 363 pages. 18mo., tuck . \$2.50
DOOD Madam Otaam Daminaa
ROSE.—Modern Steam-Engines:
An Elementary Treatise upon the Steam-Engine, written in Plain
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office.
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. To-
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc.,
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operations of gether with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation: of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By Joshua Rose, M. E.
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By JOSHUA ROSE, M. E. Illustrated by 422 engravings. Revised. 358 pp
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By JOSHUAR SEE. M. E. Illustrated by 422 engravings. Revised. 358 pp
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By JOSHUA ROSE, M. E. Illustrated by 422 engravings. Revised. 358 pp
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By Joshua Rose, M. E. Illustrated by 422 engravings. Revised. 358 pp
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By Joshua Rose. M. E. Illustrated by 422 engravings. Revised. 358 pp
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By Joshua Rose. M. E. Illustrated by 422 engravings. Revised. 358 pp. \$6.00 ROSE.—Steam Boilers: A Practical Treatise on Boiler Construction and Examination, for the Use of Practical Boiler Makers, Boiler Users, and Inspectors; and embracing in plain figures all the calculations necessary in Designing or Classifying Steam Boilers. By Joshua Rose, M. E. Illustrated by 73 engravings. 250 pages. 8vo. \$2.50
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By JOSHUA ROSE, M. E. Illustrated by 422 engravings. Revised. 358 pp
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By JOSHUA ROSE. M. E. Illustrated by 422 engravings. Revised. 358 pp. \$6.00 ROSE.—Steam Boilers: A Practical Treatise on Boiler Construction and Examination, for the Use of Practical Boiler Makers, Boiler Users, and Inspectors; and embracing in plain figures all the calculations necessary in Designing or Classifying Steam Boilers. By JOSHUA ROSE, M. E. Illustrated by 73 engravings. 250 pages. 8vo. \$2.50 SCHRIBER.—The Complete Carriage and Wagon Painter: A Concise Compendium of the Art of Painting Carriages, Wagons,
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By Joshua Rose, M. E. Illustrated by 422 engravings. Revised. 358 pp
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By Joshua Rose, M. E. Illustrated by 422 engravings. Revised. 358 pp
An Elementary Treatise upon the Steam-Engine, written in Plain language; for Use in the Workshop as well as in the Drawing Office. Giving Full Explanation; of the Construction of Modern Steam-Engines: Including Diagrams showing their Actual operation. Together with Complete but Simple Explanations of the operations of Various Kinds of Valves, Valve Motions, and Link Motions, etc., thereby Enabling the Ordinary Engineer to clearly Understand the Principles Involved in their Construction and Use, and to Plot out their Movements upon the Drawing Board. By Joshua Rose, M. E. Illustrated by 422 engravings. Revised. 358 pp

.





pre c

.

• •

B89089668503A







b89089668503a